

3M™ Dyneon™ Fluoroplastic PFA 6510GV15WZ

Product Description

3M™ Dyneon™ Fluoroplastic PFA 6510GV15WZ is an off-white fluorothermoplastic compound consisting of a fully fluorinated copolymer of tetrafluoroethylene and perfluorovinylether and glass fibers.

Special Features

- Wide service temperature range
- Extremely high weathering resistance and UV stability
- High limiting oxygen index: Does not support combustion
- Good low-friction properties
- Extremely high wear resistance
- Good resistance to solvents and chemicals
- Good electrical properties
- Good non-stick characteristics
- Good form stability

Properties	Test method	Unit	Value*
Specific Gravity	DIN EN ISO 12086	g/cm ³	2.2
Melting Point	DIN EN ISO 12086	°C	308
Melt Flow Index (372 °C/5 kg)	DIN EN ISO 1133	g/10 min	10
Tensile strength at Break (23 °C)	ASTM D638	MPa	17

* typical values

3M™ Dyneon™ Fluoroplastic PFA 6510GV15WZ

Typical Properties

3M Dyneon Fluoroplastic PFA 6510GV15WZ is an off-white glass fiber reinforced 3M Dyneon Fluoroplastic PFA compound that shows exceptional temperature resistance, excellent electrical properties and excellent chemical and weather resistance combined with high wear resistance and form stability.

Typical Applications

3M Dyneon Fluoroplastic PFA 6510GV15WZ, with a Melt-Flow-Index (372 °C/5 kg) of 10 g/10 min, is a material with a medium viscosity and is used in high shear processes for the production of injection moulded parts that require high wear resistance and form stability.

Processing Recommendations

3M Dyneon Fluoroplastic PFA 6510GV15WZ can be processed according to the known processing methods for thermoplastic polymers. All machine parts coming into contact with the melt or fumes of 3M Dyneon Fluoroplastic PFA 6510GV15WZ should be made from highly corrosion resistant materials – usually high-nickel alloys such as Inconel® 625, Haynes® 242, Hastelloy® C, and Reiloy®. Off-gases and decomposition products during processing shall be managed via an appropriate exhaust fume management system, especially at the extruder die. For safe processing of 3M Dyneon Fluoroplastic PFA 6510GV15WZ please also check safety instructions below.

Typical processing temperatures for 3M Dyneon Fluoroplastic PFA 6510GV15WZ lie between 360 °C and 390 °C. The medium melt viscosity makes 3M Dyneon Fluoroplastic PFA 6510GV15WZ an ideal material for injection moulding, when high wear resistance and form stability are required.

Injection moulding:

Detailed processing information with typical processing parameters and processing equipment recommendations please find in Dyneon's "Injection Moulding Guide".

Hastelloy®, Haynes® 242, and Reiloy® are registered trademarks of Haynes International.

Inconel® is a registered trademark of Special Metals Corporation.

Storage and Handling

3M™ Dyneon™ Fluoroplastic PFA 6510GV15WZ can be stored for a relatively long period of time provided it is stored in a clean, dry place. 3M™ Dyneon™ Fluoroplastic PFA6510GV15WZ is hydrophobic and generally does not require drying before processing unless high humidity conditions create surface moisture absorption (opened containers should be tightly resealed to prevent dust contamination from static charge accumulation and moisture ingress).

Safety Instructions

Follow the normal precautions observed with all fluorothermoplastic materials.

Please consult the Material Safety Data Sheet and Product Label for information regarding the safe handling of the material. By following all precautions and safety measures, processing these products poses no known health risks. General handling/processing precautions include:

1) Process only in well-ventilated areas. 2) Do not smoke in areas contaminated with powder/residue from these products. 3) Avoid eye contact. 4) If skin comes into contact with these products during handling, wash with soap and water afterwards. 5) Avoid contact with hot fluoropolymer.

Potential hazards, including release of toxic vapours, can arise if processing occurs under excessively high temperature conditions. Vapour extractor units should be installed above processing equipment. When cleaning processing equipment, do not burn off any of this product with a naked flame or in a furnace.

Delivery Form

3M™ Dyneon Fluoroplastic PFA 6510GV15WZ is delivered in pellet form.

Packaging sizes are:

- 50 kg cardboard box, containing two PE-bags with 25 kg content each

3M™ Dyneon™ Fluoroplastic PFA 6510GV15WZ

Important Notice

All information set forth herein is based on our present state of knowledge and is intended to provide general notes regarding products and their uses. It should not therefore be construed as a guarantee of specific properties of the products described or their suitability for a particular application. Because conditions of product use are outside Dyneon's control and vary widely, user must evaluate and determine whether a Dyneon product will be suitable for user's intended application before using it.

The quality of our products is warranted under our General Terms and Conditions of Sale as now are or hereafter may be in force.

Technical information, test data, and advice provided by Dyneon personnel are based on information and tests we believe are reliable and are intended for persons with knowledge and technical skills sufficient to analyze test types and conditions, and to handle and use raw polymers and related compounding ingredients.

No license under any Dyneon or third party intellectual rights is granted or implied by virtue of this information.

General recommendations on health and safety in processing, on work hygiene and on measures to be taken in the event of accident are detailed in our material safety data sheets.

You will find further notes on the safe handling of fluoropolymers in the brochure "[Guide for the safe handling of Fluoropolymers Resins](#)" (download link) by PlasticsEurope, Box 3, B-1160 Brussels, Tel. +32 (2) 676 17 32.

You can also download it with your smartphone using the QR code below.



Customer Service

Europe
Phone: 00 800 396 366 27
Fax: 00 800 396 366 39
Italy
Phone: 800 7 910 18
Fax: 800 7 810 19
USA
Phone: +1 800 810 8499
Fax: +1 800 635 8061

Technical Service Fluoroplastics

Dyneon GmbH
3M Advanced Materials Division
Industrieparkstraße 1
84508 Burgkirchen
Germany
Phone: +49 8679 7 4709
Fax: +49 8679 7 5037

Technical Service Fluoroelastomers & Polymer Processing Additives

3M Belgium N.V.
3M Advanced Materials Division
Canadastraat 11,
Haven 1005
2070 Zwijndrecht
Belgium
Phone: +32 3 250 7868
Fax: +32 3 250 7905

Technical Service PTFE Compounds

Dyneon B.V.
3M Advanced Materials Division
Tunnelweg 95
6468 EJ Kerkrade
The Netherlands
Phone: +31 45 567 9600
Fax: +31 45 567 9619

We will gladly supply further contact details for our full network of global sales offices. Alternatively, find them [here](#).



Web Site: www.dyneon.eu

Printed in Germany
© Dyneon 2013
Status: Jul. 2013

3M, Dyneon and Dynamar are Trademarks of 3M Company.
All Rights reserved. The present edition replaces all previous versions. Its content is being continuously adjusted to reflect the current level of knowledge. Please make sure and inquire if in doubt whether you have the latest edition.