

3M™ Dyneon™

Fluoroelastomer FPO 3731 High Fluorine Peroxide Curable

Product Description

Dyneon Fluoroelastomer FPO 3731 is a high fluorine content peroxide curable extrusion grade, which has been developed for hose applications. The grade provides excellent physical properties and is extremely resistant against fuels and different biodiesel grades (RME or SME).

Special Features

- Composition: terpolymer of vinylidene fluoride, hexafluoropropylene and tetrafluoroethylene plus cure site monomer
- Excellent scorch safety
- Process target: extrusion
- Excellent physical properties
- Excellent flow
- Outstanding resistance against biodiesel

Typical Applications

Dyneon Fluoroelastomer FPO 3731 can be used for manufacturing parts such as fuel line hoses, filler neck hoses, or fuel injector O-rings, among others.

Typical Polymer Properties

Property	Test method	Unit	Value
Colour			Opaque, Off-white
Fluorine Content	QCM 50.18.3C	%	69.8
Mooney Viscosity (raw gum) ML 1 + 10 @ 121°C	QMC 2.14.4C	Mooney Unit	35
Solubility			Ketones and Esters
Specific Gravity	QCM 14.10		1.89
Tg		°C	-9

Storage and Handling

Store and use all Dyneon Fluoroelastomers only in well-ventilated areas under cool and dry conditions.

The shelf life of Dyneon Fluoroelastomer FPO 3731 is 3 years from date of manufacturing.

Delivery Form

Dyneon Fluoroelastomer FPO 3731 is delivered in slab form.

Packaging sizes are:

- 25 kg cardboard box
- 600 kg returnable bulk shipping container systems comprised of 48 PE bags, containing 12.5 kg of product each

Processing Recommendations

Dyneon Fluoroelastomer FPO 3731 can be compounded using standard water-cooled internal mixers or two-roll mills with standard fillers and ingredients utilized in typical fluoroelastomer formulations. The “dry” ingredients should be blended before adding to the masticated gum. For best results, FPO 3731 should be banded on the mill several minutes prior to adding the blended dry ingredients. Once mixed, the compounded stocks have good scorch resistance and storage stability.

3M™ Dyneon™
Fluoroelastomer FPO 3731
High Fluorine Peroxide Curable

Typical Properties

Compound	Amount (in Parts/100)
FPO 3731	100
Carbon Black MT N-990	30
TAIC (70 %)	2.85
Trigonox 101-50D	2.5

Typical Rheological Properties

Alpha Technologies Moving Die Rheometer (MDR 2000), 100 cpm, 0.5° Arc, (QCM 2.19.1)
 Test Condition, 6' @ 180 °C

Property	Unit	Value
ML, Minimum Torque	dNM	0.9
MH, Maximum Torque	dNM	19.7
ts2	Minutes	0.5
t'50, Time to 50 % cure	Minutes	0.6
t'90, Time to 90 % cure	Minutes	1.6

Typical Physical Properties

Press Cured 15° @ 180 °C
 Post Cured 2 hours @ 180 °C

Property	Unit	Value
----------	------	-------

Physical Properties DIN 53504 (S2 DIE)

100 % Modulus	MPa	7.3
Tensile	MPa	20.9
Elongation at break	%	188
Hardness (ASTM D2240)	Shore A	72

Compression Set on buttons ASTM D395 method B

70 hours @ 200 °C	%	35
-------------------	---	----

Compression Set on 2 mm disks; 50% deformation VDA 675218

22 hours @ 150 °C	%	65
-------------------	---	----

Lower Temperature Property

TR10 (ASTM D1329)	°C	- 6
-------------------	----	-----

3M™ Dyneon™ Fluoroelastomer FPO 3731 High Fluorine Peroxide Curable

Safety Instructions

Follow the normal precautions observed with all fluoropolymer materials.

Please consult the Material Safety Data Sheet and Product Label for information regarding the safe handling of the material. By following all precautions and safety measures, processing these products poses no known health risks. General handling/processing precautions include: 1) Process only in well-ventilated areas. 2) Do not smoke in areas contaminated with powder/residue from these products. 3) Avoid eye contact. 4) If any skin comes into contact with these products during handling, wash with soap and water afterwards. 5) Avoid contact with hot fluoropolymer.

Potential hazards, including release of toxic vapours, can arise if processing occurs under excessively high temperature conditions. Vapour extractor units should be installed above processing equipment. When cleaning processing equipment, do not burn off any of this product with a naked flame or in a furnace.

Important Notice

All information set forth herein is based on our present state of knowledge and is intended to provide general notes regarding products and their uses. It should not therefore be construed as a guarantee of specific properties of the products described or their suitability for a particular application. Because conditions of product use are outside Dyneon's control and vary widely, user must evaluate and determine whether a Dyneon product will be suitable for user's intended application before using it.

The quality of our products is warranted under our General Terms and Conditions of Sale as now are or hereafter may be in force.

Technical information, test data, and advice provided by Dyneon personnel are based on information and tests we believe are reliable and are intended for persons with knowledge and technical skills sufficient to analyze test types and conditions, and to handle and use raw polymers and related compounding ingredients.

No license under any Dyneon or third party intellectual rights is granted or implied by virtue of this information.

General recommendations on health and safety in processing, on work hygiene and on measures to be taken in the event of accident are detailed in our material safety data sheets.

You will find further notes on the safe handling of fluoropolymers in the brochure "[Guide for the safe handling of Fluoropolymers Resins](#)" (download link) by PlasticsEurope, Box 3, B-1160 Brussels, Tel. +32 (2) 676 17 32.

You can also download it using the QR code below with your smartphone.



Customer Service

Europe
Phone: 00 800 396 366 27
Fax: 00 800 396 366 39
Italy
Phone: 800 7 910 18
Fax: 800 7 810 19
USA
Phone: +1 800 810 8499
Fax: +1 800 635 8061

Technical Service Fluoroplastics

Dyneon GmbH
3M Advanced Materials Division
Industrieparkstraße 1
84508 Burgkirchen
Germany
Phone: +49 8679 7 4709
Fax: +49 8679 7 5037

Technical Service Fluoroelastomers & Polymer Processing Additives

3M Belgium N.V.
3M Advanced Materials Division
Canadastraat 11,
Haven 1005
2070 Zwijndrecht
Belgium
Phone: +32 3 250 7868
Fax: +32 3 250 7905

Technical Service PTFE Compounds

Dyneon B.V.
3M Advanced Materials Division
Tunnelweg 95
6468 EJ Kerkrade
The Netherlands
Phone: +31 45 567 9600
Fax: +31 45 567 9619

We will gladly supply further contact details for our full network of global sales offices. Alternatively, find them [here](#).

