



Acrylic Foam Tape 5390


Technical Data Sheet

December 2008

Supersedes Technical Data Sheet dated November 2008


General Description 3M™ Acrylic Foam Tape (AFT) 5390 is a thick, gray, double-coated acrylic foam tape used in a variety of automotive applications. 3M AFT 5390 is used for applications where bonding surface contours are poorly matched and a thick foam is required. The acrylic foam core of 3M AFT 5390 has unique viscoelastic properties that allow it to elongate and relax when put under load, minimizing stress on the adhesive bond line. 3M AFT 5390 has AR-7 adhesive on both sides of the foam for bonding to a variety of automotive surfaces.

Applications



Shelf Life One year from date of receipt by customer when stored at 22°C (72°F) and 50% relative humidity.

Product Construction



Physical Properties Values shown are typical values not to be used for specification purposes.

Thickness	2.3 mm (± 0.23 mm) (0.090 in ± 0.009 in)
Density	688 kg/m ³ (± 80 kg/m ³) (43 lb/ft ³ ± 5 lb/ft ³)

Roll Width and Length (Planetary)

3M™ Acrylic Foam Tapes are available in the following standard widths. Millimeter widths rounded to the nearest whole numbers (7, 8, 9 mm . . .) and 1/8 inch increments starting with 1/4 inch (0.25, 0.375, 0.50, 0.625 inch . . .).

Minimum widths:
4 mm Levelwound
6 mm Planetary

Roll Width	Roll Width Tolerance	Roll Length (maximum)
Planetary Rolls		
6 - 9 mm (0.236 - 0.375 in)	+/- 0.38 mm (+/-0.015 in.)	33 meters (36 yards)
10 - 18 mm (0.394 - 0.709 in)	+/- 0.38 mm (+/-0.015 in.)	66 meters (72 yards)
> 18 mm (> 0.709 in.)	+/- 0.76 mm (+/- 0.030 in.)	66 meters (72 yards)
Levelwound Rolls		
4 - 16 mm (0.157 - 0.630 in.)	+/- 0.38 mm (+/-0.015 in.)	500 meters (547 yards)

Technical Data Sheet

3M™ Acrylic Foam Tape 5390

Page 2

Performance Properties

Performance tests are run using standard test procedures. These values presented are typical values not to be used for specification purposes.

1. Breakaway and Continuing Peel



72 hrs at 22°C (72°F)	Breakaway Peel	124 N/12.7 mm	(28 lbs/.5 in)
	Continuing Peel	53 N/12.7 mm	(12 lbs/.5 in)
72 hrs at 70°C (158°F)	Breakaway Peel	156 N/12.7 mm	(35 lbs/.5 in)
	Continuing Peel	571 N/12.7 mm	(16 lbs/.5 in)
72 hrs at 38°C /100% RH (100°F/100%RH)	Breakaway Peel	111 N/12.7 mm	(25 lbs/.5 in)
	Continuing Peel	49 N/12.7 mm	(11 lbs/.5 in)

Breakaway and continuing peel tests are run with 12.7 mm (0.5 in) wide tape on PVC test bars. Tests were run on base coat/clear coat paint at a separation rate of 305 mm/min (12 in/min).



2. Static Shear

Exceeds 100 hours at 70°C (158°F). Static shear tests are run with 12.7 mm (0.5 in) wide by 50.8 mm (2 in) long tape on PVC test bars, 6.8 kg (15 lbs) roll-down against stainless steel. Static weight is 250 gm (0.55 lbs).

Contact Information

The information provided in this technical document is intended as a guide for this product. For more information, and help selecting a 3M product for an application, please contact a 3M technical service representative.

Regulatory

IMDS# 335785. This is a published material entry on www.mdssystem.com.

3M is a Trademark of 3M Company.

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



Automotive Division
3M Center, Building 223-1S-02
St. Paul, MN 55144-1000
www.3M.com/autosolutions

© 3M 2008
74-3466-3894-5
Printed in U.S.A.



ISO/TS 16949:2002
File No. A2109