## **3M High Strength Double Coated Tape with Adhesives 300LSE and 200MP** 9496LE

Technical Data	April, 2013
Product Description	3M <sup>TM</sup> Double Coated Tape 9496LE with 3M <sup>TM</sup> Low Surface Energy Acrylic Adhesive 300LSE provides high bond strength to most surfaces, including many low surface energy plastics such as polypropylene and powder coated paints. The acrylic adhesive also provides excellent adhesion to surfaces contaminated lightly with oil typically used with machine parts. 3M <sup>TM</sup> Double Coated Tape 9496LE offers the added feature of 3M <sup>TM</sup> High Performance Acrylic Adhesive 200MP on one side to provide excellent bond strength to a variety of high surface energy substrates.

Construction Information	Product Number	Faceside <sup>1</sup> Adhesive Type/ Thickness	Carrier Type/ Thickness	Backside <sup>2</sup> Adhesive Type/ Thickness	Liner Color, Type, Print	Liner Caliper	Total Tape Thickness (w/o liner)
	3M <sup>™</sup> Double Coated Tape 9496LE <sup>3</sup>		Clear PET 0.0020" (0.005mm)	300LSE/ 0.0020" (0.005mm)	<sup>4</sup> Faceside Liner/ Tan, 58# Polycoated Kraft, "3M 467MP" Backside liner/ Tan, 58#, Polycoated Kraft, "3M 300LSE"	0.0042" (0.11mm)/ 0.0042" (0.11mm)	0.0067" (0.17mm)

Note 1: Faceside (FS) adhesive is on the interior of the roll, exposed when unwound.

Note 2: Backside (BS) adhesive is on the exterior of the roll, exposed when liner is removed.

**Note 4:** The caliper listed is based on a calculation from manufacturing controlled adhesive coat weights using a density of 1.012 g/cc.

**Note 5:** Backside liner is primary (stays with die-cut part); Faceside is secondary (removed first).

## 3M<sup>™</sup> High Strength Double Coated Tape with Adhesives 300LSE and 200MP

9496LE

Typical Physical Properties and Performance Characteristics	Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.			
	Product Number	3M™ Double Coated Tape 9496LE		
	Adhesion to stainless steel ASTM D3330 - 90 degree	Oz/in (N/100 mm)		
	- 15 minutes RT (FS/BS)	49/59 (54/65)		
	- 72 hour RT (FS/BS)	98/76 (107/83)		
	- 72 hour 158°F (70°C) (FS/BS)	111/112 (121/123)		
	Shear Strength - ASTM D3654 modified - (.5 inch <sup>2</sup> sample size)			
	1000 grams at 72°F (22°C)	>10,000 min		
	500 grams at 158°F (70°C)	>10,000 min		
	Relative High Temperature Operating Ranges:			
	Long Term (days, weeks)	200°F (93°C)		
	Short Term (minutes, hours)	300°F (149°C)		
	Relative Solvent Resistance	Very Good		

Available Sizes	Roll length, width, slitting tolerance, core size.			
	Maximum Length in:			
	1/2" to 63/64"	_		
	1" to 3"	_		
	3" to 48"	_		
	48" to 54"			
	Tolerance	_		
	Core ID	_		
	Sheet Size	24" x 36"		

## 3M<sup>™</sup> High Strength Double Coated Tape with Adhesives 300LSE and 200MP

9496LE

Features	• This tape has a moisture resistant polycoated kraft liner which can withstand high humidity conditions with minimal cockling or wrinkling.				
	• This tape has a film liner which can add dimensional stability to foams and other substrates and also makes it easier to handle the tape during slitting and die-cutting.				
	• Features a dual liner for ease in selective die-cutting.				
	• The bond strength of 3M <sup>™</sup> Adhesive 300LSE increases as a function of time and temperature, and has very high initial adhesion.				
Application Techniques	Bond strength is dependent upon the amount of adhesive to surface contact developed. Firm application pressure and moderate heat, from 100°F (38°C) to 130°F (54°C), will assist the adhesive in developing intimate contact with the bonding surface.				
	To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane.*				
	Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.				
	*Carefully read and follow the manufacturer's precautions and directions for use when working with solvents. These cleaning recommendations may not be compliant with the rules of certain Air Quality Management Districts in California; consult applicable rules before use.				
Environmental Performance	Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.				
	<b>Humidity Resistance:</b> High humidity has minimal effect on adhesive performance. No significant reduction in bond strength is observed after exposure for seven days at 90°F (32°C) and 90% relative humidity.				
	<b>UV Resistance:</b> When properly applied, nameplates and decorative trim parts are not adversely affected by exposure to direct sunlight.				
	Water Resistance: Immersion in water has no appreciable effect on the bond strength. After 100 hours at room temperature, the high bond strength is maintained.				
	<b>Temperature Cycling Resistance:</b> High bond strength is maintained after cycling four times through: 4 hours at 158°F (70°C) 4 hours at -20°F (-29°C) 4 hours at 73°F (22°C)				
	<b>Chemical Resistance:</b> When properly applied, nameplate and decorative trim parts will hold securely after exposure to numerous chemicals including oil, mild acids and alkalis.				

## 3M<sup>™</sup> High Strength Double Coated Tape with Adhesives 300LSE and 200MP

9496LE

<b>Application Ideas</b>	<ul> <li>Foam to powder coated painted surfaces.</li> </ul>				
	• Low surface energy substrates.				
	• Graphic attachment of high surface energy and low surface energy substrates.				
Storage	Store at room temperature conditions of 70°F (21°C) and 50% relative humidity.				
Shelf Life	If stored properly, product retains its performance and properties for 18 months from date of shipment.				
Recognition/ Certification	<b>TSCA:</b> These products are defined as articles under the Toxic Substances Control Act and therefore, are exempt from inventory listing requirements.				
	<b>MSDS:</b> These products are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, the products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards.				
	<b>Note:</b> One of 3M's core values is to respect our social and physical environment. 3M is committed to comply with ever-changing, global, regulatory and consumer environmental, health, and safety (EHS) requirements. As a service to our customers, 3M is providing information on the regulatory status of many 3M products. Further regulation information including that for OSHA, USCPSI, FDA, California Proposition 65, READY and RoHS, can be found at 3M.com/regs.				
Technical Information	The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.				
Product Use	Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.				
Warranty, Limited Remedy, and Disclaimer	Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.				
Limitation of Liability	Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.				
3M	This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.				
Industrial Adhesives and Terra					
Industrial Adhesives and Tape Converter Markets					
3M Center, Building 225-3S-06 St. Paul MN 55144 1000	Recorded Paper				

3M Center, Building 225-3S-06 St. Paul, MN 55144-1000 800-223-7427 • 651-778-4244 (fax) www.3M.com/converter



Recycled Paper 40% pre-consumer 10% post-consumer 3M is a trademark of 3M Company. Printed in U.S.A. ©3M 2013 70070940195 (4/13)