

#### **Commercial Solutions Division**

# 3M™ Scotchcal™ Translucent Graphic Film

#### Series 3632GPS

# Product Description

These cast films are perfect for durable, dimensional stable backlit applications. The low-gloss surface of 3632GPS eliminates glare and provides a uniform color with both, reflected and transmitted light.

Film series 3632GPS is based on film series 3630 with the addition of a GPS (Graphic Protection System) top coat for increased durability and cleanability.

Film series 3632GPS is recommended for fluorescent lighting applications.

The film is suitable for electronic cut or thermoform applications.

Product Line Illuminated signage 3632GPS-X X = color code, translucent, semi-matte, permanent

adhesive (clear). Wide selection out of large color range.

Special colors available on request.

# Product Characteristics

These are indicative values for unprocessed products.

Contact your 3M representative for a custom specification.

cast vinyl

Physical & Application Material

 $\begin{array}{ll} \text{Surface finish} & \text{semi-matte} \\ \text{Thickness (film)} & 50 \ \mu\text{m} \ (0.05 \ \text{mm}) \\ \text{Adhesive type} & \text{pressure-sensitive} \\ \end{array}$ 

Adhesive appearance clea

Liner transparent synthetic

Adhesion 15 N/25 mm 180° peel, substrate: aluminium; cond:

24 h 23°C/50%RH

Application method wet or dry

Applied shrinkage < 0.3 mm FTM 14

Application temperature +16°C for flat surfaces

(minimum air and substrate)

+16°C for curved to corrugated surfaces, with and without rivets

Service temperature -44°C to +77°C (not for extended periods of time at the extremes) (after application)

Surface type flat to simple curved

Substrate type glass, PMMA, PC\*, PETG\*, flexible sign making substrates

\*Might require drying with heat before use

Graphic removal Fair to remove with heat and/or chemicals from supported substrates.

No liability is given for ease or speed of removal of any graphic. Pay attention to

page 1 of 4

adequate air and substrate temperature.

The values above are the results of illustrative lab test measurements and shall not be considered as a commitment from 3M.

Storage Shelf life Use within three years from the date of manufacture on the sealed original box.

Use within one year after opening the box.

Storage conditions +4°C to +40°C, out of sunlight, original container in clean and dry area.

Product Bulletin 3632

The shelf life as defined above remains an indicative and maximum data, subject to many external and non-controllable factors. It may never be interpreted as warranty.

#### Flammability

Flammability standards are different from country to country. Ask your local 3M contact for details, please.

#### **Durability**

The durabilities mentioned in the table below are the results of illustrative lab tests. The values show the best performance expected from these products, provided that the film will be processed and applied professionally according to 3M's recommendations.

The durability statements do not constitute warranties of quality, life and characteristics.

The durability of products is also influenced by:

- the type of substrate and thorough preparation of the surface (with 3M™ Surface Preparation System)
- application procedures
- environmental factors
- the method and the frequency of cleaning

Unprocessed film The following durability data are given for unprocessed film only!

Climatic zones Graphic durability is largely determined by the climate and the angle of exposure.

Find below a table showing the durability of a product according to the angle of

exposure and the geographical location of the application.

Zone 1 Northern Europe, Italy (north of Rome), Russia

Zone 2 Mediterranean area without North Africa, South Africa

Zone 3 Gulf area, Africa

Exposure types Vertical:



The face of the graphic is ±10° from vertical.

Interior: Interior means an application inside a building without direct

exposure to sunlight.

Vertical outdoor	Zone 1	Zone 2	Zone 3
exposure white/black	10 years	7 years	5 years
colors	10 years	7 years	5 years
metallics	5 years	4 years	3 years
Interior application	Zone 1	Zone 2	Zone 3
interior	12 years	12 years	12 years

3M™ Performance Guarantee and MCS™ Warranty In addition, 3M provides a guarantee/warranty on a finished applied graphic within the framework of 3M<sup>™</sup> Performance Guarantee and/or 3M<sup>™</sup> MCS<sup>™</sup> warranty programs.

For detailed graphic construction and application options along with specific Warranty periods, please see the Warranty matrices and Warranty information on 3M Graphic Solutions/Warranties.

Visit <u>www.3mgraphics.com</u> for getting more details about 3M's comprehensive graphic solutions.

#### Limitations of End Uses

3M specifically does not recommend or warrant the following uses, but please contact us to discuss your needs to recommend other products.

Graphics applied to

- 2nd surface to 3M™ Envision™ Flexible Substrate FS-1 and 3M™ Panagraphics™ III Wide Width Flexible Substrate not recommended.
- application to competitive flexible sign substrates.
- low surface energy substrates or substrates with low surface energy coating.
- other than flat or moderate curved/corrugated surfaces.
- stainless steel.
- surfaces that are not clean and smooth.

Graphics subjected to

- ed to gasoline vapors or spills.
- Important Notice 3M Commercial Solutions products are not tested against automotive manufacturer specifications!

- Graphics with more than two layers of film except as described in this bulletin are not recommended.
- Non vertical applications will have a significant decrease in durability!
- 3M accepts no liability for glass breakage. See instruction bulletin 5.1 for details.
- To avoid color variations all pieces of applied film of one colored area should be processed out of one lot of material.

### **Graphics** Manufacturing

Flat, or rolled film side out on 130 mm (5 inch) or larger core. These methods help to prevent the liner from wrinkling or application tape, if used, from popping off.

Three layer film constructions

A third layer of film is warranted only if the top layer is 3M™ Scotchcal™ Gloss Overlaminate 3640/3642. In addition, just two of the three layers should be aligned to the edge of the substrate.



Film Layer 2

Film Layer 1

Extend protective laminate minimum 25 mm beyond edges of film layers.

Extend protective laminate minimum 25 mm beyond edges of film layers and wrap it around the back of substrate.



Align protective layer to the edge of the substrate and cut one of the two film layers minimum 25 mm smaller.

#### Converting Information

Based upon cutting evaluations the minimum height for text is 25 mm using upper and lowercase Helvetica Medium. The stroke width should not be lower than 1 mm.

**Electronic Cutting** 

The variable characteristics of electronically controlled cutting equipment require users to verify their specific requirements.

Sharpness of knife blade

Dull blades impart a serrated look to the edge of the cut film.

Weight of knife blade

The ideal weight slightly scores the liner. Too little weight does not cut completely through the film and the adhesive. Excessive weight cuts the liner and causes the blade to drag, accelerating wear and creating a serrated cut edge on the film.

Weeding

The excess film should be weed (removed) as soon after cutting as practical. This is to minimize the effect of possible adhesive flow.

humidity

Temperature and relative Temperature and relative humidity are minor considerations, but avoid extreme or rapid fluctuating conditions.

Roll storage Store the film in the same environment as the cutting equipment.

Further information For more details refer to our instruction bulletin 4.1 'Sheeting, Scoring, Film Cutting', please.

>Instruction Bulletin 4.1'Sheeting, Scoring, Film cutting'<

### Converting **Information**

There are unique health and safety considerations that must be understood prior to vacuum forming faces using translucent films.

**Thermoforming** 

Refer to Instruction Bulletin 5.16 'Thermoforming' for special recommendations, limitations and processing requirements when forming with applied films.

>Instruction Bulletin 5.16 'Thermoforming'<

Elongation limit Forming of applied film on sheets should not exceed 50% elongation.

## **Application**

See product bulletin ATR 'application tape recommendations' for information about selection and use of suitable application tapes for this product, please.

> Product Bulletin Application Tape Recommendations <

Refer to Instruction Bulletin 5.1 'select and prepare substrates for graphic application', for general application information.

>Instruction Bulletin 5.1 'select and prepare substrates for graphic application'<

#### Maintenance and Cleaning

Use a cleaner designed for high-quality painted surfaces. The cleaner must be wet, non-abrasive, without strong solvents, and have a pH value between 3 and 11 (neither strongly acidic nor strongly alkaline).

Refer to Instruction Bulletin 6.5 'storage, handling, maintenance and removal of films and sheetings', for general maintenance and cleaning information.

>Instruction Bulletin 6.5 'Storage, Handling, Maintenance and Removal of Films and Sheetings'<

### **Important** Safety Remark

Application to glass

The application of colored or printed film onto glass with sunlight exposure can lead to glass breakage through thermal expansion of the glass. The local conditions must be examined for the danger of glass break by uneven heat absorption through sun exposure. Type of glass (insulation glass, float glass, LSG, toughened safety glass, semi-tempered glass, etc.), glass dimension, joint condition, flexibility of the sealant, quality of the edge finishing, geographical orientation and partial shadow during sun exposure are the determining factors. Light color designs and application on the outside of the window are to be preferred. A free nonapplied framework of 4 mm around the entire window front can help to dissipate the absorbed warmth. According to common knowledge a thermal crack can occur at temperature differences of approx. 130°C (toughened safety glass), approx. 40°C (float glass) or approx. 110°C (semi-tempered glass). Coldest place is usually under the framework in the embedded joined window part, the warmest place is typically on the darkest place in the format. Because of the many above mentioned factors, glass breakage cannot be fully predicted, therefore 3M does not accept liability for glass breakage when using this film for window graphics.

### Remarks

This bulletin provides technical information only.

Important notice

All questions of warranty and liability relating to this product are governed by the terms and conditions of the sale, subject, where applicable, to the prevailing law.

Before using, the user must determine the suitability of the product for its required or intended use, and the user assumes all risk and liability whatsoever in connection therewith.

As outdoor graphics age, natural weathering occurs causing a gradual reduction in gloss, slight color changes, some lifting of the graphic at the edges or around rivets, and ultimately a minor amount of cracking.

These changes are not evidence of product failure and are not covered by a 3M warranty.

Additional information Visit the web site of your local subsidiary at www.3Mgraphics.com for getting:

- more details about 3M™ MCS™ Warranty and 3M™ Performance Guarantee
- additional instruction bulletins
- a complete product overview about materials 3M is offering

3M, Controltac, Envision, Scotchcal, Comply, MCS and Panagraphics are trademarks of 3M Company. All other trademarks are the property of their respective owners.

The use of trademark signs and brand names in this bulletin is based upon US standards. These standards may vary from country to country outside the USA.

#### 3M United Kingdom PLC

Commercial Solutions Division Cain Road Bracknell, RG12 8HT UK

www.3m.co.uk/graphics-and-signage-uk/

© 3M 2020. All rights reserved.

3M Ireland (Dublin)

The Iveagh Building The Park, Carrickmines Dublin 18 Ireland

www.3m.co.uk/graphics-and-signage-uk/