

	Corrosion Prevention and Protection	Surface Preparation	Metal Working
<b>Personal Protective Equipment</b>	Wear latex, nitrile or fabric gloves dedicated to aluminum repair to prevent surface contamination from skin contact. See #1 below. <b>Please note that you need to read and understand each product label and SDS for important health and safety information regarding PPE. This section relates only to not cross-contaminating surfaces, not to the full PPE gear required for each type of repair.</b>		
<b>Shop Environment</b>	Use segregated repair areas for aluminum repairs according to OEM recommendation and follow all OSHA guidelines.		
<b>Hand Tools</b>	Use separate hand tools designed for aluminum repairs (e.g., hammers, dolleys, clamps, files, drill bits, saw blades, etc.).		
	<b>Heat Usage:</b> Heat is recommended when straightening aluminum to avoid over stretching and cracking of the panel. Aluminum has a much lower melting point than steel and care must be taken to avoid permanent damage. Generally, a propane torch is sufficient to reach the 400°F area. It's best to follow OEM recommendations for specific temperatures.		
<b>Pneumatic Tools</b>	Use air tools dedicated to aluminum repairs OR tools that have been thoroughly cleaned with compressed air to remove any steel particles. See #2 below.		
<b>Abrasives</b>	Use separate piece of abrasive on dissimilar substrates. See #2 below.	Do not use grinding or sanding abrasives coarser than grade 80.	
<b>Adhesives</b>	Apply and spread adhesives to cover all prepared metal surfaces. Use wipes dedicated to aluminum substrates. Ensure proper squeeze out and tooling of squeeze out to cover all metal surfaces.	Prepare bonding surfaces using grade 80 abrasive or equivalent Scotch-Brite™ abrasive grade. See #4 below.	Use caution when heating the panel near bonded joints. See #5 below.
	<b>Heat Usage: Replace:</b> Use heat to de-bond observing OEM temperature limits. <b>Repair:</b> Use caution when applying heat near bonded joints to avoid bond failures. See #3 below.		
<b>Sealers</b>	Follow standard surface preparation procedures. Use wipes dedicated to aluminum substrates. Apply 3M™ Cavity Wax Plus to panel interior prior to final assembly.	Follow product use recommendations for DTM or non-DTM seam sealers.	—
<b>Coatings</b>	Follow standard surface preparation procedures. Use wipes dedicated to aluminum substrates. Apply 3M™ Cavity Wax Plus to panel interior prior to final assembly.	Remove loose debris, abrade and properly clean prior to coating application.	Apply 3M™ Cavity Wax Plus to panel interior prior to final assembly.
<b>Filler &amp; Glaze</b>	Follow standard surface preparation procedures. Use wipes dedicated to aluminum substrates. Apply filler or glaze within 1 hour. See #4 below.	Prepare surface using grade 80 abrasive or equivalent Scotch-Brite graded abrasives. See #4 below.	
<b>Visit 3MCollision.com for more SOPs and videos</b>			

**Note: Statements and recommendations within this matrix should be considered general practices. Follow specific OEM recommendations, when they exist.**

1	2	3	4	5
Skin contact with open substrates can leave contamination that leads to corrosion.	Cleaning tools thoroughly and using separate abrasive will help prevent the possibility of galvanic corrosion caused by incidental contact of dissimilar metals.	To de-bond 3M™ Panel Bonding Adhesive, panel must be heated to above 400°F.	Oxidation forms immediately on exposed aluminum. Accumulated oxidation is detrimental to bond strength. After 1 hour of exposure, re-abrade aluminum surface to maximize bond strength.	Panel bond adhesive degradation begins at 300°F or higher. Use caution and heat indicators to monitor panel temperature when applying heat near bonded joints.

## Individual Product Instruction and Safety Information

For individual product instructions and applicable precautions see product labels and associated literature for the individual product at [3MCollision.com](http://3MCollision.com)

For product material safety data sheets see [3MCollision.com](http://3MCollision.com)

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.



3M Automotive Aftermarket Division  
3M Center, Building 223-6S-07  
St. Paul, MN 55144-1000  
U.S.A.

3M, Accuspray, Cubitron, E-A-R, Hookit, Platinum, PPS, Rocker Gard, Roloc, Scotch, Scotchblok, Scotch-Brite, Skull Screws, Trizact and Virtua are trademarks of 3M Company. All other trademarks are property of their respective owners.

Web [3MCollision.com](http://3MCollision.com)

Please recycle. Printed in U.S.A. © 3M 2019. All rights reserved. Rev 7/19.

60-4402-8062-0