



Adhesive Transfer Tapes

6035PC • 6035PL • 6038PC • 6038PL

Technical Data

October 2017

Product Description 3M™ Adhesive Transfer Tapes 6035 and 6038 with 3M™ Acrylic Adhesive 300MP are pressure-sensitive transfer tapes which are specially formulated to be good adhesion to many lower surface energy materials. These tapes are ideal for use in automotive interior applications.

Product Construction	Adhesive Transfer Tape 6035PC		Adhesive Transfer Tape 6038PC	
	Product		Product	
	Adhesive:	5.0 mils (127 microns) #300MP Acrylic Adhesive	Adhesive:	8.0 mils (203 microns) #300MP Acrylic Adhesive
	Liner:	4.2 mils (107 microns) 58# Polycoated Kraft Paper	Liner:	4.2 mils (107 microns) 58# Polycoated Kraft Paper
Product Construction	Adhesive Transfer Tape 6035PL		Adhesive Transfer Tape 6038PL	
	Product		Product	
	Adhesive:	5.0 mils (127 microns) #300MP Acrylic Adhesive	Adhesive:	8.0 mils (203 microns) #300MP Acrylic Adhesive
Liner:	6.2 mils (157 microns) 83# Polycoated Kraft Paper	Liner:	6.2 mils (157 microns) 86# Polycoated Kraft Paper	

Features

- Meet OEM fogging specifications.
- Provide excellent bond to a wide variety of smooth surfaces.
- Excellent shear and peel values to both high and low energy surfaces (PP, ABS, painted metal).
- High initial tack for quick and easy assembly line application.
- High temperature resistance to withstand environmental conditions normally associated with automotive interiors.

Application Ideas

- Attaching a wide variety of vibration and sound damping materials
- Attaching the wiring harness to the automobile headliner
- Attaching interior panels
- Attaching glass to rearview mirror assembly

3M™ Adhesive Transfer Tapes

6035PC • 6035PL • 6038PC • 6038PL

Typical Physical Properties and Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Flammability Test: (FMVSS 302/SAE J369)	Pass
Automotive Fogging Test: SAE J1756 @ 100°C	99
Adhesion:	ASTM D-3330 (modified) 90° Peel, 12"/minute (305 mm/minute), 2 mil aluminum foil to various surfaces

3M™ Adhesive Transfer Tapes 6035PC & 6035PL

Surface	15 Minute Dwell		72 Hour Dwell		72 Hour Dwell @ 158°F	
	Oz./In.	N/100 mm	Oz./In.	N/100 mm	Oz./In.	N/100 mm
Stainless Steel	102	112	131	143	166	182
Polycarbonate (High Surface Energy Plastic)	89	97	96	105	67	73
Polypropylene (Low Surface Energy Plastic)	NA	NA	73	80	63	69
ABS	NA	NA	93	102	78	85

3M™ Adhesive Transfer Tapes 6038PC & 6038PL

Surface	15 Minute Dwell		72 Hour Dwell		72 Hour Dwell @ 158°F	
	Oz./In.	N/100 mm	Oz./In.	N/100 mm	Oz./In.	N/100 mm
Stainless Steel	165	181	210	230	247	270
Polycarbonate (High Surface Energy Plastic)	125	137	146	160	106	116
Polypropylene (Low Surface Energy Plastic)	NA	NA	96	105	82	90
ABS	NA	NA	143	157	120	131

Environmental Performance

Temperature Resistance:	Short term: 250°F (121°C).
Humidity Resistance:	No adverse effect on the bond after exposure to 100% relative humidity at 100°F (38°C).
U.V. Resistance:	Adhesive is resistant to oxidation and ozone when exposed to air or ultraviolet light.
Bond Build-up:	The bond strength of the adhesive increases as a function of time and temperature.
Shelf Life:	Product retains its performance properties for two years from date of manufacture if properly stored at room temperature conditions of 72°F (22°C) and 50% relative humidity.

3M™ Adhesive Transfer Tapes

6035PC • 6035PL • 6038PC • 6038PL

Environmental Performance (continued)

Properties defined below are based on sample attachment to a stainless steel faceplate material with a 0.002 inch aluminum foil backing. Values are listed based on a 90° peel at 12 inches/minute (305 mm/minute) after a 24 hour dwell. This data is provided as a guideline for the effects on adhesion at the following conditions and should not be used for specification purposes.

Test Condition	3M™ Adhesive Transfer Tapes			
	6035PC & 6035PL		6038PC & 6038PL	
	Oz./In.	N/100 mm	Oz./In.	N/100 mm
Unleaded Gas - 1 hr. @ R.T.	65	71	127	139
Methyl Ethyl Ketone - 1 hr. @ R.T.	39	43	93	102
Oil (10W30) - 72 hrs. @ 120°F (49°C)	114	124	179	196
Weak Acid (pH 4) - 4 hrs. @ R.T.	89	97	139	152
Weak Base (pH 10) - 4 hrs. @ R.T.	81	89	132	145
Water - 100 hrs. @ R.T.	134	147	139	152
7 days @ 90°F (32°C) and 90 R.H.	140	153	215	235
Sodium Chloride Solution (5%) - 72 hrs. @ R.T.	113	124	203	222
Ultraviolet Light - 30 days exposure	191	209	220	241
Temperature Cycling - 4 hrs. @ 158°F (70°C); 4 hrs. @ -20°F (-29°C); 16 hrs. @ R.T. - repeated three times	134	147	200	219

Available Sizes

1" - 3" (25.4 mm - 76.2 mm) Width: 60 yds (54.8 m) maximum roll size
 3" - 5" (76.2 mm - 127 mm) Width: 180 yds (165 m) maximum roll size
 5" - 60" (127 mm - 1524 mm) Width: 360 yds (329 m) maximum roll size
 Standard core size: 3" (76.2 mm) diameter
 Width tolerance: ± 1/32" (0.79 mm)
 Sizes other than above are negotiable.

Application Techniques

- For maximum bond strength the surface should be thoroughly cleaned and dried. Typical cleaning solvents are heptanes or isopropyl alcohol. Follow the manufacturer's precautions and directions for use when using solvents.
- Bond strength can also be improved with firm application pressure and moderate heat causing the adhesive to develop intimate contact with the bonding surface.
- Ideal adhesive application temperature range is 70°F to 100°F (21°C to 38°C). This is not recommended for application to surfaces at temperatures below 50°F (10°C) because the adhesive becomes too firm to adhere readily. Once properly applied, low temperature holding is satisfactory.

3M™ Adhesive Transfer Tapes

6035PC • 6035PL • 6038PC • 6038PL

Technical Information

The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy and Disclaimer

Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

ISO 9001

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.



Industrial Adhesives and Tapes Division
Converter Markets

3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
800-223-7427 • 651-778-4244 (fax)
www.3M.com/converter

3M is a trademark of 3M Company.
©3M 2017 E70-0709-3852-0 (10/17)