

3M Advanced Materials Division

# 3M™ Dyneon™ Cure-in-Place Gasket CIPG 1951

## Features and Benefits

- Provides excellent chemical resistance (except to amines, bases & polar organic solvents.)
- Helps create a barrier and extends fuel cell service life.
- Contains no silicones.
- Roll format enables automation & scaling resulting in improved productivity in gasket application.
- Has a smooth surface and lies flat for a level fuel stack.

**Note:** Data in this document are not for specification purposes.

## Typical Physical Properties (Not for specification purposes)

Property	Test Method	Value
Adhesion to Steel	ASTM D3330	8 oz./in width (0.9 N/cm)
Tensile strength at break	ASTM D3759	40 lbs/in. width
Elongation at break	ASTM D3759	200%
PTFE backing thickness	ASTM D2652	5.0 mils (0.13 mm)
Total gasket thickness	ASTM D2652	7.5 mils (0.19 mm)

## Product Description

3M™ Dyneon™ Cure-in-Place Gasket CIPG 1951 consists of a PTFE film backing with a fluoroelastomer adhesive layer.

## Product Form and Packaging

**Backing:** Extruded PTFE (polytetrafluoroethylene)

**Adhesive:** Fluoroelastomer

**Release liner:** Polyester, non-silicone liner

**Color:** Tan

**Standard Roll Dimensions:**  
1.36 in (wide) × 36 yds (long)  
(34.5 mm × 32.9 m)

## Shelf Life

To maintain best performance, store product at recommended storage conditions and use product within 12 months from date of manufacture.

## Storage

Rolls of Dyneon CIPG 1951 must be shipped and stored at temperatures of 35°–40°F (2°–4°C).


## Safety and Toxicology

This is a fluoroplastic material, so normal precautions observed with fluoroplastics should be followed. Before processing this product, be sure to read and follow all precautions and directions for use contained in the product label and the Safety Data Sheet. General handling/processing precautions include:

1. Wear protective gloves when handling.
2. Wash thoroughly after handling.

For optimal sealing performance, the gasket needs to be cured after application to the substrate. Recommended curing conditions are noted in the chart below:

Curing temperature		Curing time (min)
(°C)	(°F)	
90	194	107
110	230	9.7
130	266	1.2
150	302	0.2



**Important Notice and Disclaimer:** This 3M product is an experimental or developmental product that has not been introduced or commercialized for general sale, and its formulation, performance characteristics and other properties, specifications (if any), availability, and pricing are not guaranteed and are subject to change or withdrawal without notice. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. User is solely responsible for evaluating third party intellectual property rights and for ensuring that user's use of 3M product does not violate any third party intellectual property rights. This 3M product is sold or made available "AS IS." 3M MAKES NO WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OF NON-INFRINGEMENT OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE.

**Limitation of Liability:** Except where prohibited by law, 3M will not be liable for any loss or damages arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

**Technical Information:** Technical information, recommendations, and other statements contained in this document or provided by 3M personnel are based on tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.



**3M Advanced Materials Division**  
 Oakdale, MN 55128  
 Phone 1-800-810-8499  
 Web [www.3m.com/advancedmaterials](http://www.3m.com/advancedmaterials)

3M and Dyneon are trademarks of 3M Company. Used under license.

Please recycle. Printed in USA © 3M 2016.  
 All rights reserved. Issued: 2/16 11379HB  
 98-0050-0048-8 Rev. B