


PROTEMP® II TECHNIQUE



STEP 1:

Before preparing teeth, make impression and trim after set.




STEP 2:

Cut interdental grooves out of impression.



STEP 3:

If edentulous gap exists, cut grooves between abutment teeth.




STEP 4:

After teeth have been prepared, cleaned and dried; mix equal amounts of base/catalyst and place into syringe. Gently extrude keeping syringe tip immersed in material.




STEP 5:

Gently position impression matrix into patient's mouth.



STEP 6:

Monitor set of material in mouth and remove between 2 and 3 minutes after mixing.




STEP 7:

Remove temporary restoration and allow it to bench set for approximately 2 minutes.



STEP 8:

Trim and finish temporary restoration.



STEP 9:

Cement temporary restoration using standard temporary cement.

PROTEMP® II

Self-curing, bis-acryl composite provisional material with audible-click base/catalyst delivery system for direct chairside temporary restorations.

INDICATIONS

- Multiple-unit bridges
- Full and partial crowns
- Inlays and onlays
- Veneers

ADVANTAGES

- Easy-to-extrude, audible-click base/catalyst delivery system
- Exceptionally tight marginal seal with precision fit
- Secure removal from mouth without tearing, distortion or sticking
- No unpleasant odor or taste
- Reliable, long-lasting and wear resistant restorations with fewer repairs
- Outstanding aesthetics and polishability with great color stability
- Available in a range of three Vita® shades: A1 extra light/A3 light/B3 yellow

*Vita is a registered trademark of Vita Zahnfabrik

TO PLACE AN ORDER, CALL YOUR
AUTHORIZED ESPE DISTRIBUTOR
OR CALL ESPE AT 1-800-344-8235.



PACKAGING

Type of Package:

PROTEMP II Bis-Acryl Provisional Material

	<i>Item Number</i>
INTRO PACK A1 EXTRA LIGHT /A3 LIGHT - (1) Base (28g) each - A1 and A3, (1) Catalyst (4.8g), (1) Pad, (1) Syringe	.046001
INTRO PACK A3 LIGHT/B3 YELLOW - (1) Base (28g) each - A3 and B3, (1) Catalyst (4.8g), (1) Pad, (1) Syringe	.046011
DOUBLE PACK A1 EXTRA LIGHT - (2) Base A1 (28g), (1) Catalyst (4.8g), (1) Pad, (1) Syringe	.046091
DOUBLE PACK A3 LIGHT - (2) Base A3 (28g), (1) Catalyst (4.8g), (1) Pad, (1) Syringe	.046101
DOUBLE PACK B3 YELLOW - (2) Base B3 (28g), (1) Catalyst (4.8g), (1) Pad, (1) Syringe	.046111
GIANT PACK A1 EXTRA LIGHT - (10) Base A1 (28g), (5) Catalysts (4.8g), (5) Pads, (5) Syringes	.046121
GIANT PACK A3 LIGHT - (10) Base A3 (28g), (5) Catalysts (4.8g), (5) Pads, (5) Syringes	.046131
GIANT PACK B3 YELLOW - (10) Base B3 (28g), (5) Catalysts (4.8g), (5) Pads, (5) Syringes	.046141
(1) CATALYST (4.8g)	.046431
(5) SYRINGES	.072071

Working Time (including mixing time): 2 minutes

Setting Time (from start of mix): 7 minutes