

3M Advanced Materials Division

3M™ Ceramic Microspheres

Introduction

3M™ Ceramic Microspheres are unique, semi-transparent, white-colored, fine particle size, high-strength microspheres. Formulating to low VOC is a major driving factor in the coatings industry. Our ceramic microspheres are used by formulators to reduce VOC levels; increase filler loadings; improve hardness; and add burnish, scrub and abrasion resistance to a variety of coating formulations. Due to the ceramic chemistry of these products, they are also UV transparent down to 250 nm and have utility in radiation-curable and thin-film powder coatings.

3M™ Ceramic Microspheres Formulating Information

3M ceramic microspheres are best dispersed by using sand, ball and roller mills. For optimal dispersion, microspheres should be added to the grind stage along with pigments and other filler materials. Use of a dispersant can aid in the wet-out and dispersion of these products.

Product Safety and Handling

Please read and follow the precautions and directions for use in the product label and Safety Data Sheet before using this product. Safety Data Sheets for this product are available from 3M Customer Service at 800-367-8905 or from your local 3M sales representative.

Material Description (Not for specification purposes.)

Property	3M™ Ceramic Microspheres
Shape	Uniquely shaped fillers
Composition	Alkali Alumino Silicate Ceramic
Color, unaided eye	White

Typical Physical Properties (Not for specification purposes.)

Property	3M™ Ceramic Microspheres
True density (g/cc)	2.4 (20.0 lbs/gal)
Bulk density (g/cc)	1.5 (12.6 lbs/gal)
Whiteness ("L" Value)	90+ (Hunter L,a,b scale)
Crush strength, 80% survival by volume (psi)	> 4,200 kg/cm ² (> 60,000 psi)
pH (at 5 wt% loading in water)	9.0 – 12.0
Hardness	6 (Mohs scale)
Softening point	1,020°C (1,870°F)
Refractive index: Predominant	1.53
Dielectric constant	3.19
UV light transmission	UV Transparent down to 250 nm
Thermal conductivity (W/mK)	2.3

3M Advanced Materials product realization process and manufacturing sites are aligned to ISO 9001 Quality Systems. Test data is generated by following documented procedures and test methods.

Typical Physical Properties (Not for specification purposes.)

Property		3M™ Ceramic Microspheres		
		W-210	W-410	W-610
Particle size (microns)	90 th Percentile	12	21	32
	50 th Percentile	6	9	13
	10 th Percentile	2	2	2
Oil absorption*		46	44	28

*gm oil/100cc microspheres



Additional Information

3M™ Ceramic Microspheres are supported by global sales, technical and customer service resources, with fully-staffed technical service laboratories in the U.S., Europe, Japan, Latin America and Southeast Asia. Users benefit from 3M's broad technology base and continuing attention to product development, performance, safety and environmental issues.

For additional technical information on 3M ceramic microspheres in the United States, call 3M Advanced Materials Division, **800-367-8905**. For other 3M global offices, and information on additional 3M products, visit our web site at: www.3M.com/paintsandcoatings.

Warranty, Limited Remedy, and Disclaimer: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. User is solely responsible for evaluating third party intellectual property rights and for ensuring that user's use of 3M product does not violate any third party intellectual property rights. Unless a different warranty is specifically stated in the applicable product literature or packaging insert, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OF NON-INFRINGEMENT OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damages arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

Technical Information: Technical information, recommendations, and other statements contained in this document or provided by 3M personnel are based on tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.



3M Advanced Materials Division

3M Center
St. Paul, MN 55144 USA

Phone 1-800-367-8905
Web www.3M.com/paintsandcoatings

3M is a trademark of 3M Company.
Used under license by 3M subsidiaries
and affiliates.

Please recycle. Printed in USA. © 3M 2017.
All rights reserved. Issued: 5/17 12503HB
98-0212-4187-6 Rev. B