



GMW 16443 Type 1

Adhesion Performance Requirements for Adhesive Backed Light Trim and Foam Automotive Interior Spec Testing

Technical Bulletin

April 2020

3M tested the following adhesive tapes to the Automotive OEM Spec: GMW 16443 Type 1 Adhesion Performance Requirements for Adhesive Backed Light Trim and Foam. The results of the testing are provided in the following information. Adhesives not listed on this document have not been tested to this spec.

Note: The GMW16443 specification is adhesive and foam specific. Performance testing should be completed before recommending an adhesive and a foam combination for this specification.

Automotive specification testing was performed on lab substrates and not on actual automotive production parts. Additional testing by the converter, tier or supplier is needed to show that parts and adhesives meet such specification. Please carefully read the automotive specification for further information.

Revision	Date	Comments
Original release	September 2019	Testing and bulletin completed
Add lab substrate language and revision table	April 2020	

3M™ Reinforced Adhesive Transfer Tape L1+RT

3M™ Double Coated Polyester Tape L1+DCP

3M™ Double Coated Polyester Tape L2+DCP

3M™ Adhesive Transfer Tape L2+T5

3M™ Adhesive Transfer Tape L3+T5

Test	Test Condition / Environment
180° Peel Adhesion on ABS 300mm / 12 in per min	3.5.3 As Received - 24 hour dwell @ Room Temp
	3.5.4 Heat Age – 168 hours @ 176°F / 80°C
	3.5.5 Humidity GMW14729 – 168 hours @ 40°C / 104°F + 100% RH
	3.5.6 Cycle Exposure – GMW14124 cycle M (not required for type I)

GMW 16443 Type 1: Adhesion Performance Requirements for Adhesive Backed Light Trim and Foam

Adhesive		PU Ester	PU Ether	XLPE Foam	Microcellular Urethane	EPDM Foam	Nitrile Foam	Neoprene Foam	EPDM Rubber	Neoprene Rubber	Santoprene™ Rubber	Butyl Rubber
L1 + RT	As received	F	F	P	F	N/A	N/A	N/A	N/A	N/A	N/A	N/A
	Heat Age	P	P	P	F	N/A	N/A	N/A	N/A	N/A	N/A	N/A
	Humidity	P	F	P	F	N/A	N/A	N/A	N/A	N/A	N/A	N/A
	Cycle	P	P	P	F	N/A	N/A	N/A	N/A	N/A	N/A	N/A
L1 + DCP	As Received	P	P	P	P	N/A	N/A	N/A	N/A	N/A	N/A	N/A
	Heat Age	P	P	P	F	N/A	N/A	N/A	N/A	N/A	N/A	N/A
	Humidity	F	F	P	F	N/A	N/A	N/A	N/A	N/A	N/A	N/A
	Cycle	P	F	P	F	N/A	N/A	N/A	N/A	N/A	N/A	N/A
L2 + DCP	As Received	P	P	P	P	P	P	P	N/A	N/A	N/A	N/A
	Heat Age	P	P	P	P	P	F	P	N/A	N/A	N/A	N/A
	Humidity	P	P	P	P	P	F	F	N/A	N/A	N/A	N/A
	Cycle	P	P	P	F	P	F	F	N/A	N/A	N/A	N/A
L2 + T5	As Received	P	P	P	P	P	P	P	N/A	N/A	N/A	N/A
	Heat Age	P	P	P	P	P	F	P	N/A	N/A	N/A	N/A
	Humidity	P	P	P	P	P	P	P	N/A	N/A	N/A	N/A
	Cycle	P	P	P	P	P	F	P	N/A	N/A	N/A	N/A
L3 + T5	As Received	P	P	P	P	P	P	P	P	P	P	P
	Heat Aged	P	P	P	P	P	P	P	F	P	P	F
	Humidity	P	P	P	P	P	P	P	F	P	P	F
	Cycle	P	P	P	P	P	P	P	F	F	F	F

P = Pass, F = Fail, N/A = Not Tested

GMW 16443 Type 1: Adhesion Performance Requirements for Adhesive Backed Light Trim and Foam

L1 + RT

3.5.3 As Received - 24 hour dwell @ Room Temp						
	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
L1+RT Adhesive	PU Ester Foam	ABS	381	34.82	Clean Peel	Fail
	PU Ether Foam		511	46.71	Clean Peel	Fail
	XLPE Foam		219	20.02	Foam Tear	Pass
	Microcellular Urethane Foam		478	43.69	100% Cohesive	Fail

3.5.4 Heat Age – 168 hours @ 176°F / 80°C						
	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
L1+RT Adhesive	PU Ester Foam	ABS	814	74.40	Clean Peel	Pass
	PU Ether Foam		577	52.74	Clean Peel	Pass
	XLPE Foam		206	18.83	Foam Tear	Pass
	Microcellular Urethane Foam		487	44.51	Clean Peel	Fail

3.5.5 Humidity GMW 14729 – 168 hours @ 40°C / 104°F + 100% RH						
	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
L1+RT Adhesive	PU Ester Foam	ABS	624	57.03	Clean Peel	Pass
	PU Ether Foam		490	44.79	Clean Peel	Fail
	XLPE Foam		231	21.11	Foam Tear	Pass
	Microcellular Urethane Foam		330	30.16	Clean Peel	Fail

3.5.6 Cycle Exposure – GMW 14124 Cycle M (not required for type I)						
	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
L1+RT Adhesive	PU Ester Foam	ABS	689	62.97	Clean Peel	Pass
	PU Ether Foam		577	52.74	Clean Peel	Pass
	XLPE Foam		221	20.20	Foam Tear	Pass
	Microcellular Urethane Foam		440	40.22	Cohesive	Fail

GMW 16443 Type 1: Adhesion Performance Requirements for Adhesive Backed Light Trim and Foam

L1 + DCP

3.5.3 As Received – 24 hour dwell @ Room Temp						
L1+DCP Adhesive	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
	PU Ester Foam	ABS	780	71.29	Clean Peel	Pass
	PU Ether Foam		632	57.76	Clean Peel	Pass
	XLPE Foam		238	21.75	Foam Tear	Pass
	Microcellular Urethane Foam		530	48.44	Clean Peel	Pass

3.5.4 Heat Age – 168 hours @ 176°F / 80°C						
L1+DCP Adhesive	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
	PU Ester Foam	ABS	551	50.36	Clean Peel	Pass
	PU Ether Foam		532	48.62	Clean Peel	Pass
	XLPE Foam		214	19.56	Foam Tear	Pass
	Microcellular Urethane Foam		484	44.24	Clean Peel	Fail

3.5.5 Humidity GMW 14729 – 168 hours @ 40°C / 104°F + 100% RH						
L1+DCP Adhesive	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
	PU Ester Foam	ABS	399	36.47	Clean Peel	Fail
	PU Ether Foam		400	36.56	Clean Peel	Fail
	XLPE Foam		250	22.85	Foam Tear	Pass
	Microcellular Urethane Foam		413	37.75	Clean Peel	Fail

3.5.6 Cycle Exposure – GMW 14124 Cycle M (not required for type I)						
L1+DCP Adhesive	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
	PU Ester Foam	ABS	548	50.09	Clean Peel	Pass
	PU Ether Foam		431	39.39	Clean Peel	Fail
	XLPE Foam		244	22.30	Foam Tear	Pass
	Microcellular Urethane Foam		388	35.46	Clean Peel	Fail

GMW 16443 Type 1: Adhesion Performance Requirements for Adhesive Backed Light Trim and Foam

L2 + DCP

3.5.3 As Received – 24 hour dwell @ Room Temp						
	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
L2+DCP Adhesive	PU Ester Foam	ABS	584	53.38	Clean Peel	Pass
	PU Ether Foam		660	60.32	Foam Tear	Pass
	XLPE Foam		241	22.03	Foam Tear	Pass
	Microcellular Urethane Foam		596	54.47	Foam Tear	Pass
	EPDM Foam		219	20.02	Foam Tear	Pass
	Nitrile Foam		586	53.56	Cohesive	Pass
	Neoprene Foam		950	86.83	Clean Peel	Pass

3.5.4 Heat Age – 168 hours @ 176°F / 80°C						
	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
L2+DCP Adhesive	PU Ester Foam	ABS	959	87.65	Clean Peel	Pass
	PU Ether Foam		606	55.39	Clean Peel	Pass
	XLPE Foam		199	18.19	Foam Tear	Pass
	Microcellular Urethane Foam		688	62.88	Foam Tear	Pass
	EPDM Foam		235	21.48	Foam Tear	Pass
	Nitrile Foam		159	14.53	Clean Peel	Fail
	Neoprene Foam		626	57.22	Clean Peel	Pass

3.5.5 Humidity GMW 14729 – 168 hours @ 40°C / 104°F + 100% RH						
	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
L2+DCP Adhesive	PU Ester Foam	ABS	732	66.90	Clean Peel	Pass
	PU Ether Foam		661	60.41	Foam Tear	Pass
	XLPE Foam		218	19.92	Foam Tear	Pass
	Microcellular Urethane Foam		632	57.76	Foam Tear	Pass
	EPDM Foam		228	20.84	Foam Tear	Pass
	Nitrile Foam		231	21.11	Cohesive	Fail
	Neoprene Foam		112	10.24	Cohesive	Fail

GMW 16443 Type 1: Adhesion Performance Requirements for Adhesive Backed Light Trim and Foam

3.5.6 Cycle Exposure – GMW 14124 Cycle M (not required for type I)						
	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
L2+DCP Adhesive	PU Ester Foam	ABS	659	60.23	Clean Peel	Pass
	PU Ether Foam		601	54.93	Foam Tear	Pass
	XLPE Foam		191	17.46	Foam Tear	Pass
	Microcellular Urethane Foam		475	43.41	Clean Peel	Fail
	EPDM Foam		212	19.38	Foam Tear	Pass
	Nitrile Foam		40	3.66	Cohesive	Fail
	Neoprene Foam		87	7.95	Cohesive	Fail

L2 + T5

3.5.3 As Received – 24 hour dwell @ Room Temp						
	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
L2+T5 Adhesive	PU Ester Foam	ABS	937	85.64	Foam Tear	Pass
	PU Ether Foam		628	57.40	Foam Tear	Pass
	XLPE Foam		202	18.46	Foam Tear	Pass
	Microcellular Urethane Foam		666	60.87	Clean Peel	Pass
	EPDM Foam		211	19.28	Foam Tear	Pass
	Nitrile Foam		941	86.01	Foam Tear	Pass
	Neoprene Foam		1170	106.94	Foam Tear	Pass

3.5.4 Heat Age – 168 hours @ 176°F / 80°C						
	Substrate	Substrate	AVG Peel N/m	Avg Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
L2+T5 Adhesive	PU Ester Foam	ABS	939	85.82	Foam Tear	Pass
	PU Ether Foam		595	54.38	Foam Tear	Pass
	XLPE Foam		168	15.35	Foam Tear	Pass
	Microcellular Urethane Foam		1080	98.71	Foam Tear	Pass
	EPDM Foam		218	19.92	Foam Tear	Pass
	Nitrile Foam		480	43.87	Clean Peel	Fail
	Neoprene Foam		1400	127.96	Foam Tear	Pass

GMW 16443 Type 1: Adhesion Performance Requirements for Adhesive Backed Light Trim and Foam

3.5.5 Humidity GMW 14729 – 168 hours @ 40°C / 104°F + 100% RH						
	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
L2+T5 Adhesive	PU Ester Foam	ABS	916	83.72	Foam Tear	Pass
	PU Ether Foam		632	57.76	Foam Tear	Pass
	XLPE Foam		224	20.47	Foam Tear	Pass
	Microcellular Urethane Foam		750	68.55	Foam Tear	Pass
	EPDM Foam		223	20.38	Foam Tear	Pass
	Nitrile Foam		719	65.72	Clean Peel	Pass
	Neoprene Foam		910	83.17	Clean Peel	Pass

3.5.6 Cycle Exposure – GMW 14124 Cycle M (not required for type I)						
	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
L2+T5 Adhesive	PU Ester Foam	ABS	1050	95.97	Foam Tear	Pass
	PU Ether Foam		558	51.00	Foam Tear	Pass
	XLPE Foam		178	16.27	Foam Tear	Pass
	Microcellular Urethane Foam		894	81.71	Foam Tear	Pass
	EPDM Foam		231	21.11	Foam Tear	Pass
	Nitrile Foam		510	46.61	Clean Peel	Fail
	Neoprene Foam		532	48.62	Clean Peel	Pass

GMW 16443 Type 1: Adhesion Performance Requirements for Adhesive Backed Light Trim and Foam

L3 + T5

3.5.3 As Received – 24 hour dwell @ Room Temp						
L3+T5 Adhesive	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m or 47.98 oz/in or foam tear
	PU Ester Foam	ABS	1030	94.14	Foam Tear	Pass
	PU Ether Foam		593	54.20	Foam Tear	Pass
	XLPE Foam		211	19.28	Foam Tear	Pass
	Microcellular Urethane Foam		605	55.30	Clean Peel	Pass
	EPDM Foam		200	18.28	Foam Tear	Pass
	Nitrile Foam		867	79.24	Clean Peel	Pass
	Neoprene Foam		1250	114.25	Foam Tear	Pass
	EPDM Rubber		276	25.23	Clean Peel	Fail
	Neoprene Rubber		1120	102.37	Clean Peel	Pass
	Santoprene™ Rubber		623	56.94	Clean Peel	Pass
	Butyl Rubber		749	68.46	Clean Peel	Pass

3.5.4 Heat Age – 168 hours @ 176°F / 80°C						
L3+T5 Adhesive	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
	PU Ester Foam	ABS	946	86.46	Foam Tear	Pass
	PU Ether Foam		590	53.93	Foam Tear	Pass
	XLPE Foam		204	18.64	Foam Tear	Pass
	Microcellular Urethane Foam		754	68.91	Foam Tear	Pass
	EPDM Foam		249	22.76	Foam Tear	Pass
	Nitrile Foam		1230	112.42	Clean Peel	Pass
	Neoprene Foam		1670	152.64	Foam Tear	Pass
	EPDM Rubber		93	8.50	Clean Peel	Fail
	Neoprene Rubber		726	66.36	Clean Peel	Pass
	Santoprene™ Rubber		622	56.85	Clean Peel	Pass
	Butyl Rubber		296	27.05	Clean Peel	Fail

GMW 16443 Type 1: Adhesion Performance Requirements for Adhesive Backed Light Trim and Foam

3.5.5 Humidity GMW 14729 – 168 hours @ 40°C / 104°F + 100% RH						
L3+T5 Adhesive	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
	PU Ester Foam	ABS	849	77.60	Foam Tear	Pass
	PU Ether Foam		625	57.12	Foam Tear	Pass
	XLPE Foam		229	20.93	Foam Tear	Pass
	Microcellular Urethane Foam		657	60.05	Foam Tear	Pass
	EPDM Foam		246	22.48	Foam Tear	Pass
	Nitrile Foam		1200	109.68	Foam Tear	Pass
	Neoprene Foam		1110	101.45	Foam Tear	Pass
	EPDM Rubber		156	14.26	Cohesive	Fail
	Neoprene Rubber		850	77.69	Clean Peel	Pass
	Santoprene Rubber		706	64.53	Clean Peel	Pass
	Butyl Rubber		502	45.88	Clean Peel	Fail

3.5.6 Cycle Exposure – GMW 14124 Cycle M (not required for type I)						
L3+T5 Adhesive	Substrate	Substrate	AVG Peel N/m	AVG Peel oz/in	Observation	Requirement 525 N/m / 47.98 oz/in or foam tear
	PU Ester Foam	ABS	877	80.16	Foam Tear	Pass
	PU Ether Foam		558	51.00	Foam Tear	Pass
	XLPE Foam		177	16.18	Foam Tear	Pass
	Microcellular Urethane Foam		803	73.39	Foam Tear	Pass
	EPDM Foam		226	20.66	Foam Tear	Pass
	Nitrile Foam		940	85.92	Clean Peel	Pass
	Neoprene Foam		1430	130.70	Clean Peel	Pass
	EPDM Rubber		86	7.86	Clean Peel	Fail
	Neoprene Rubber		515	47.07	Clean Peel	Fail
	Santoprene™ Rubber		377	34.46	Clean Peel	Fail
	Butyl Rubber		76	6.95	Clean Peel	Fail

GMW 16443 Type 1: Adhesion Performance Requirements for Adhesive Backed Light Trim and Foam

Technical Information

The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, the customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer

Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

ISO 9001:2000

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.



Industrial Adhesives and Tapes Division

Converter Markets

3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
800-362-7427 • 651-778-4244 (Fax)
www.3M.com/converter

3M is a trademark of 3M Company.
Santoprene is a trademark owned by
Exxon Mobil Corporation.
© 3M 2019
E70-0713-4629-3 (09/19)