

3M

Scotch-Weld™

Structural Adhesive Primer

EC-1660 (5%)

Technical Data

May, 2002

Introduction

3M™ Scotch-Weld™ Structural Adhesive Primer EC-1660 (5%) is a primer for film adhesives in those applications where it is desired to obtain improved adhesion, or improved resistance to environmental exposure. Scotch-Weld EC-1660 (5%) is especially suggested for use with 3M™ Scotch-Weld™ Structural Adhesive Films AF 30 and AF 32.

Primer EC-1660 (5%) offers the following advantages:

- Ensures complete wetting of film adhesive to adherend surfaces.
- Simplifies production scheduling by protecting the cleaned surfaces until the bonding operations can be completed.
- Imports corrosion protection to metal

Description

Color:	Green
Base:	Synthetic resin-elastomer
Solvent:	Methyl isobutyl ketone (MIBK), cyclohexanone and toluene
Viscosity:	10-30 cps (Brookfield RVF, 20 rpm, No.1 Spindle @ 77 ± 2°F [25 ± -17°C])
Solids Content:	4-5% (3-5 gram sample at 160°F [71°C] for 24 hours)
Flash Point:	63°F (17°C) (Closed Cup)

Contains photochemically reactive solvent; Southern California APCD Rule 102 (Jan. 9, 1976).

Application

A thoroughly cleaned, dry, grease free surface is essential for maximum performance. Cleaning methods which will produce a breakfree water film on metal surfaces are generally satisfactory. Surface preparations should be fully evaluated with the adhesive, especially if resistance to specific environments are anticipated.

Scotch-Weld™

Structural Adhesive Primer

EC-1660 (5%)

Surface Preparation Suggested Cleaning Procedure for Aluminum

1. Vapor Degrease – Perchloroethylene condensing vapors for 5-10 minutes.
2. Alkaline Degrease – Oakite 164 solution (9-11 oz./gallon of water) at 180-200°F (82-93°C) for 10-20 minutes. Rinse immediately in large quantities of cold running water.
3. Acid Etch – Place panels in the following solution for 10 minutes at 150 ± 5°F (66 ± 2°C).

Caution: Use adequate respiratory, eye and skin protection when using etch solutions.

Sodium Dichromate (Na ₂ Cr ₂ O ₇ ·2H ₂ O)	4.1 - 4.9 oz./gallon
Sulfuric Acid, 66° Be	38.5 - 41.5 oz./gallon
2024T-3 aluminum (dissolved)	0.2 oz./gallon minimum
Tap Water	Balance

4. Rinse – Rinse panels in clear running water.
5. Dry – Air dry 15 minutes; force dry 10 minutes at 150 ± 10°F (66 ± 5°C).
6. It is advisable to coat the freshly cleaned surfaces with 3M™ Scotch-Weld™ Structural Adhesive Primer EC-1660 (5%) within 4 hours after surface preparation.
7. Care should be taken to avoid contaminating the cleaned aluminum by any substance which will hinder the wetting action of Primer EC-1660 (5%).

Primer Application

The following procedure is suggested to obtain optimum results: Stir well before using. Brush coat to maximum of .0001 inches (dry) or use the following spray procedure.

Spray gun	Binks No. 62, Siphon Feed
Air Cap	66S
Fluid Tip and Needle	66-365
Line Pressure	20-25 psi
Cup Pressure	O, (Siphon Feed)
Fan Adjustment	Wide Open
Fluid Adjustment	One turn open
Distance from Panel	6-9 inches
Primer Thickness	.0001 inch

Primer Cleanup:

Excess primer and equipment may be cleaned up prior to curing with ketone* type solvents.

***Note:** When using solvents, extinguish all ignition sources and follow the manufacturer's precautions and directions for use.

Storage

Avoid heat and dampness in storage. Store new shipments behind older lots. Refrigerated storage @ 40 ± 5°F (4 ± 2°C) is suggested for Primer EC-1660 (5%). Rotate stock on a "first in-first out" basis.

Caution: Primer should be permitted to thoroughly warm to room temperature before being used in order to prevent moisture condensation.

Scotch-Weld™

Structural Adhesive Primer

EC-1660 (5%)

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

For Additional Information

For additional information call 1-800-235-2376. For Technical Service assistance, call (651) 736-5954. Address correspondence to 3M Aerospace Lab, Technical Service, 3M Center, Building 209-2S-32, St. Paul, MN 55144-1000.

Important Notice

3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's method of application. Please remember that many factors can affect the use and performance of a 3M Engineered Adhesives Division product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Limitation of Remedies and Liability

If the 3M product is proved to be defective, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.

ISO 9002

This Engineered Adhesives Division product was manufactured under a 3M quality system registered to ISO 9002 standards.



Aerospace Department
Engineered Adhesives Division

3M Center, Building 220-8E-05
St. Paul, MN 55144-1000
www.3M.com/aerospace



Recycled Paper
40% pre-consumer
10% post-consumer

Printed in U.S.A.
©3M 2002 78-6900-0472-2 (5/02)