

# Apply, bond and go.

Meet the future of bracket bonding. This revolutionary, two-part structural paste adhesive instantly holds parts in place with no sag, no mess and no installation fixtures required. You'll reduce waste, save money and increase productivity.

- ▶ Fast and easy to apply
- ▶ Cures within 90 minutes to handling strength
- ▶ Fewer steps – simplifies your process
- ▶ High mechanical strength
- ▶ Qualified to Aerospace OEM specifications





## Strong.

Excellent shear and peel strength on substrates used in the aerospace and transportation sectors.



## Fast.

Ideal for bonding fasteners, brackets, studs and standoffs.



## Neat.


Easy-to-use cartridges ensure precise, neat and consistent application.



## Safe.

Low-flow adhesive can be safely used in vertical and overhead applications.

### Easy 3-step process:



#### Step 1:

Apply adhesive to bracket



#### Step 2:

Bond to desired surface



#### Step 3:

Go – no support needed

### Product information:

Properties	Part B	Part A	Test method
Chemical base	Modified epoxy	Modified amine	
Colour	Yellow	Dark grey	
Consistency	Paste	Paste	
Density	1.10 g/cm <sup>3</sup>	1.07 g/cm <sup>3</sup>	ISO 2811
Mix ratio by volume	100	50	
Viscosity @ 73°F (23°C)	440 Pa·s	270 Pa·s	Rheometer (AITM 3-0004)
Cure time to handling	435 psi (3 MPa) after 90 min at 73°F (23°C)		EN 2243-1
Shear strength	Up to 5,075 psi (35 MPa)		ISO 4587
Overlap shear strength*	60 min 43.5 psi (0.3 MPa) 90 min 470 psi (3.3 MPa) 104 min 2,132 psi (14.7 MPa) 120 min 2,944 psi (20.3 MPa) 150 min 4,409 psi (30.4 MPa)		EN 2243-1
Temperature range	-67°F to 185°F (-55°C to 85°C)		
Colour in mixed state	Olive green		
Work life	10 min @ 73°F (23°C)		Internal test method**
Extrudability [50 ml Cartridge, 73°F (23°C)]	20 min extrudable from mixing nozzle (EPX Quadro, Art. 300 346: 5.3/16)		
Available packaging	50 ml duo-pack cartridge, others on request		
Dispenser	Scotch-Weld EPX Manual Dispenser III for 50ml cartridges		
Nozzles	Scotch-Weld EPX Quadro Structural Adhesive Nozzles		

\*Test conditions: Clad Al 2024 T3, thickness 1.6 mm, surface treatment: CAA + primer BR127, test speed: 10 mm/min.

\*\*Time during which the adhesive can be applied properly.

**Product Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

**Warranty and Limited Remedy:** 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER EXPRESS OR IMPLIED WARRANTIES OR CONDITIONS, INCLUDING ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If the 3M product does not conform to this warranty, the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted.

### 3M Aerospace and Commercial Transport Division

3M United Kingdom PLC  
3M Centre, Cain Road  
Bracknell, Berkshire RG12 8HT  
Tel: 0870 6080 060  
www.3M.co.uk/ec7202  
aerospaceuk@mmm.com

3M Ireland Limited  
The Iveagh Building  
The Park, Carrickmines  
Dublin 18  
Tel: 1 800 303 437

Please recycle. Printed in the UK.  
© 3M 2018. 3M and Scotch-Weld  
are trademarks of the 3M company.  
All rights reserved. J438374

