



5490 "PTFE" Plastic Film Tape

Product Data Sheet

Updated : September 2022
Supersedes : March 1996

Product Description

A low friction film which is resistant to wear. The extruded film is more suitable for applications on flat surfaces due to its resistance to curl.

Physical Properties

Not for specification purposes

Adhesive Type	Silicone	
Backing	Extruded film made of DuPont's "Teflon" PTFE (Polytetrafluorethylene) film.	
Film Thickness (ASTM D-3652)	50 µm	
Total Thickness	90 µm	
Tape Colour	Blue-black	
Shelf Life	12 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	

Performance Characteristics

Not for specification purposes

Adhesion to Stainless Steel ASTM D-3330	2.9 N/10mm	
Tensile Strength ASTM D-3759	38.5 N/10mm	
Elongation at Break ASTM D-3759	150 %	
Temperature Range Maximum Minimum	204 °C -53 °C	

<p>Additional Product Information</p>	<p>No. 5490 is an extruded, calendered film. This process provides an exceptionally smooth surface when applied. Resists curl on unwind and lays flat.</p> <p>Chemical resistance of No. 5490 is excellent. The silicone adhesive will be attacked by commercial organic solvents and should not be used for applications requiring organic solvent resistance.</p>	<p>Shelf life of No. 5490 is excellent with no noticeable deterioration after normal storage of one year. Applied tape can be considered permanent in inherent limits of the backing or adhesive are not exceeded.</p>	<p>CAUTION</p> <p>The characteristics of "Teflon" Film are such that at temperatures above 204°C, the film gives off small quantities of toxic fumes. Therefore, when using 3M Brand "Teflon" Tapes above 204° C adequate ventilation must be provided.</p>
<p>Application Techniques</p>	<p>To prevent wrinkling or bubbling of the backing on "Teflon" film tapes when subjected to temperature above 120°C, pre-heat the surface the tape will be</p>	<p>applied to. Pre-heat the surface to at least 65°C, preferably 80°C, to obtain the best results.</p>	<p>While always ensuring surface is dry, clean and with no loose surface. Firm even pressure should always be applied.</p>
<p>Applications</p>	<p>Easy release surface provided by wrapping rollers, plates, belts etc., where build-up of sticky materials, ink and paints normally occur.</p>	<p>Chemical resistant surface provided by lining hoods, bins, chutes and wrapping pipes, cables, conduit etc.</p>	
	<p>FEATURES</p> <p>Extruded "Teflon" Film.</p> <p>Silicone adhesive.</p>	<p>ADVANTAGES</p> <p>Exceptionally smooth surface. Resists edge curl. Lays Flat.</p> <p>High temperature performance. Long ageing.</p>	<p>BENEFITS</p> <p>Ease of clean-up. Stays in place. Higher productivity.</p> <p>High productivity.</p>

Automotive Disclaimer

Automotive Applications: This product is an industrial product and has not been designed or tested for use in certain automotive applications, including, but not limited to, automotive electric powertrain battery or high voltage applications. This product does not fully adhere to typical automotive design or quality system requirements, such as IATF 16949 or VDA 6.3. This product may not be manufactured in an IATF certified facility and may not meet a Ppk of 1.33 for all properties. The product may not undergo an automotive production part approval process (PPAP). Customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's automotive application and for conducting incoming inspections before use of the product. Failure to do so may result in injury, death, and/or harm to property. No written or verbal statement, report, data or recommendation by 3M related to automotive use of the product shall have any force or effect unless in an agreement signed by the Technical Director of 3M's Automotive Division. Customer assumes all responsibility and risk if customer chooses to use this product in an automotive electric powertrain battery or high voltage application, and 3M will not be liable for any loss or damage arising from or related to the 3M product or customer's use of the product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity or recall costs), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability. In no event shall 3M be liable for any damages in excess of the purchase price paid for the product.

NOTWITHSTANDING ANY OTHER STATEMENT TO THE CONTRARY, 3M MAKES NO REPRESENTATIONS, WARRANTIES OR CONDITIONS WHATSOEVER, EXPRESS OR IMPLIED, REGARDING THE PRODUCT IF USED IN AN AUTOMOTIVE ELECTRIC POWERTRAIN BATTERY OR HIGH VOLTAGE APPLICATION, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY ON PERFORMANCE, LONGEVITY, SUITABILITY, COMPATIBILITY, OR INTEROPERABILITY, OR ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE.

3M is a trademark of the 3M Company.
"Teflon" is a trademark of DuPont.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



Industrial Adhesives & Tapes Division 3M Belgium Hermeslaan 7 1831 Diegem Belgium	Industrial Adhesives & Tapes Division 3M Nederland Molengraafsingel 29 2629 JD Delft Nederland
---	--