

3M™ Scotch-Weld™ Elastomeric Coating EC-5816

Technical Data Sheet

Product Description

3M™ Scotch-Weld™ Elastomeric Coating EC-5816 is a one-part, abrasion and chemical resistant coating designed for the protection of fragile, porous, insulation materials (polyurethane foam, glass wool, cork, etc.). Scotch-Weld EC-5816 can be applied to primed metal substrates.

Features

- Forms a tough, flexible, abrasion resistant coating.
- Resists heat, flame, and weathering.
- Resists gasoline, aircraft fuel, hydraulic oil and water.
- Can be applied by spraying, brushing or flow coating.

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Base	Synthetic Elastomer
Color	White
Density	8.1 to 8.7 lb/gal (0.97 to 1.04 g/cc)
Consistency	Thin liquid
Viscosity (Brookfield RVF #2 at 20) rpm	50-500 cps
Solids Content	26.5 – 30.5%

Handling/Application Information

Prior to application, 3M™ Scotch-Weld™ Elastomeric Coating EC-5816 should be thoroughly agitated for 3-5 minutes on a paint shaker to insure proper dispersion of pigments.

For application to foam, spray application is recommended. Apply approximately a 3 to 5 mil coating by multiple spray coats. Allow at least 5 minutes dry between coats.

Scotch-Weld EC-5816 dries to a tack free condition in approximately 30 minutes. The coating should dry a minimum of 48 hours prior to placing in service. Accelerated drying at 160°F (71°C) for 2 hours is recommended to remove residual solvent in order to avert blistering if the coating is exposed to 200 to 300°F (93.3-149°C) service.

Coverage is approximately 50 sq. ft./gallon for a 5 mil film. Surfaces to be coated must be clean, dry and free of oil or grease. Clean up can be accomplished with methyl ethyl ketone (MEK)*.

***Note:** When using solvents, be sure to follow the manufacturer's precautions and directions for use.

Application Equipment Suggestions

Equipment

Gun: HVLP

Fluid Tip/Air Cap: 1.1 to 1.8 mm

SPRAY IN CLOSED, WELL VENTILATED AREA

Spray Procedure

1. Apply moderate to heavy continuous coats using the following settings.

Atomization Pressure:	45 psi (3.1 bar)
Pot Pressure:	10-12 psi (.69-.83 bar)
Fan:	Medium to Wide
Target:	6-10 inches (15-25 cm)

Allow a minimum of five minutes to a maximum of four hours dry time before proceeding to Step #2.

2. Apply repeated coats until a void free surface is obtained (approximately 3-5 mils dry), using the following settings:

Atomization Pressure:	30 psi (2.1 bar)
Pot Pressure:	3-5 psi (.21-.34 bar)
Fan:	Medium
Target:	10-12 inches (25-30 cm)

Note: It is very important that this application is void free before applying additional coats.

Allow a minimum dry time of five minutes to a maximum of 24 hours before applying additional coating.

3. Apply additional coating as specified in Step #1. Apply 2-4 coats and allow to dry a minimum of 20 minutes to a maximum of 24 hours before applying additional coating. If sagging occurs, the coating thickness per application is too heavy; reduce material output or the number of coats per application. Heavy coats can also result in porosity; if porosity develops, repeat Step #2.

4. Repeat Step #3 until desired dry film thickness is obtained.

Typical Coating Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Fluid Resistance:

Procedure: Polyurethane foam was coated with 3M™ Scotch-Weld™ Elastomeric Coating EC-5816 and cured for 7 days at 77 ± 2°F (25 ± 1°C). The coated foam was immersed in the following test fluids for 24 hours at 77 ± 2°F (25 ± 1°C).

Fluid	Result after 24 hours Immersion
Distilled H ₂ O	No effect
Mil-S-8802 Reference Fluid	No effect
Mil-L-3136A Hydrocarbon Fluid	No effect
JP-4, Commercial	No effect
Skydrol® 500 Hydraulic Oil	Some swelling of coating and some adhesion loss to foam
Mil-L-7808D Oil	No effect
Reg. Gasoline	No effect
5% H ₂ SO ₄	No effect
5% NaOH	No effect

Physical Properties:

Procedure: Scotch-Weld EC-5816 was coated on a release surface to give approximately a 5 mil film when dried. After curing for 4 days at 77 ± 2°F (25 ± 1°C) the following tests were run:

Test	Typical Value
Tensile Strength (ASTM D-638)	2000 psi (13.8 MPa)
Elongation (ASTM D-638)	350%
Tear Strength	250 lb/in (1112 N/25 mm)
Abrasion Index CS-17 Wheel, 1000 g. load, 100 cycles	10.0 milligrams
Moisture Vapor Transmission ASTM-E-96-63T, Procedure A	10.0 grams/sq. meter/24 hours

Additional Tests:

Fire Retardancy: Cured Scotch-Weld EC-5816 is self-extinguishing when applied to flame retardant urethane foam and tested per ASTM D 1360.

Heat Resistance: A film of Scotch-Weld EC-5816 when exposed 300 hours at 300°F (149°C) or 50 hours at 355°F (179°C) will discolor but the film retains flexibility to temperature as low as -65°F (-54°C).

Salt Spray Resistance: Scotch-Weld EC-5816 applied to 3M™ Scotch-Weld™ Structural Adhesive Primer EC-1945 B/A primed aluminum exhibits no appreciable blistering, softening, or loss of adhesion after 1000 hours exposure in a 20% salt fog environment.

Weathering: When subjected to 500 hours in an Atlas Twin Arc Weather-O-Meter, Scotch-Weld EC-5816 exhibits moderate yellowing and slight chalking. The physical integrity of the coating does not appear to be adversely affected.

Shelf life and Storage Conditions:

The shelf life of 3M™ Scotch-Weld™ Elastomeric Coating EC-5816 is 6 months from the date of shipment when stored at 80°F (27°C) or below in the original unopened container.

Precautionary Information

Refer to product label and Safety Data Sheet (SDS) for health and safety information before using this product. For SDS visit our website https://www.3m.com/3M/en_US/company-us/SDS-search/.

Additional Information

In the U.S. call toll free 1-800-235-2376, or fax 1-800-435-3082 or 651-737-2171. For U.S. Military, call 1-866-556-5714. If you are outside of the U.S., please contact your nearest 3M representative.

These products were manufactured under a 3M Quality Management System registered to the AS9100 standard

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information. **Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property. **Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price. **Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

5816
Issue date: 1/2019



Automotive & Aerospace Solutions Division
3M Center
St. Paul, MN 55144-1000
Phone 1-800-328-1684
Web www.3M.com/aerospace

3M and Scotch-Weld are trademarks of 3M Company. All other trademarks are the property of their respective owners.
© 3M 2018. All rights reserved.