



Automotive Aftermarket Division

3M™ 50410 Weld Thru Coating

1) Part Numbers

50410

2) Description and end uses

Weld Thru II: 377 ml Aerosol spray can

3M™ 50410 Weld Thru II Coating is a sprayable, weldable zinc-based coating designed to prevent corrosion from forming between welded metal panels.

- Fast drying
- Easy to weld through without altering welder settings
- Excellent and consistent spray-ability
- Efficient corrosion protection
- Good adhesion to bare metal

3M™ 50410 is designed to be used for both spot welding and MIG welding operations in the automotive repair process.

It helps restoring the original zinc based protection used in automotive construction and will dramatically reduce risk of corrosion development on welded steel parts and panels.

A 500 hours salt spray exposure (ASTM B117) showed significant reduction in corrosion over untreated metal

When compared to a copper-based weld through coating, after 250 hours salt spray exposure, the zinc-based 3M™ 50410 coating showed a far better protection of the metal sheet than the copper-based product.



Technical Data Sheet

Effective: 02/03/2020 Supersedes: 15/06/2007

3) Physical Properties

| | |
|--------------------|--|
| Colour | Silver grey |
| Packaging | 377ml (361g) aerosol can |
| Tack Free Time | 10 minutes (at 23°C, 50% RH) |
| Solvent | Acetone |
| Flash Point | -104°C, Closed cup |
| % Solids (Typical) | 64 % |
| V.O.C. | 700 g/l |
| Specific Gravity | 0.796 |
| Storage conditions | + 5°C to + 30°C |
| Shelf Life | 24 months under normal storage conditions (date of manufacturing in American style on bottom of can) |

4) Directions for Use

- Remove all paint, rust, oil and other contaminant from the surface to be coated. Sand remaining coatings with P60-P120 grit abrasive.
- Clean and degrease surface with 3M™ 08984.
- Shake can well for approx. 1 minute after agitator ball is heard. Shake frequently during use.
- Hold can about 15cm from surface to be coated. Apply to all bare surfaces and edges in the vicinity of the intended weld.
- Two thin layers are recommended to obtain the correct thickness and optimum corrosion protection.
- Weld after product has dried (about 10 to 20 minutes).
- Invert can and spray to purge nozzle.

Note:

- Do not apply filler or other top coat over 3M™ 50410 as this may causes lifting. It is recommended to remove 3M™ 50410 from any surfaces to be painted.
- Spot weld in the first 24 hours. Longer time reduces conductivity.

5) Storage

Store at room temperature in flammables storage area. Rotate stock on a “first-in-first-out” basis. When stored at the recommended conditions in original, unopened containers, this product has a shelf life see container for details. Use in a well-ventilated area.



Technical Data Sheet

Effective: 02/03/2020 Supersedes: 15/06/2007

6) Safety

Please refer to the Material Safety Data Sheet or contact your local 3M™ Toxicology Department.

Pressurised container. Protect from sunlight and do not expose to temperature exceeding 50°C. Do not pierce or burn, even after use. Do not spray on a naked flame or incandescent material.

3M™ 50410 Weld Thru II Coating is designed FOR PROFESSIONAL USE ONLY.

7) Disclaimer

All statements, technical information and recommendations are based on tests we believe to be reliable but the accuracy or completeness thereof is not guaranteed. Please ensure before using our product that it is suitable for your intended use. All questions of reliability relating to this product are governed by the Terms of Sale subject, where applicable, to the prevailing law.

For Additional Health and Safety Information

| |
|---|
| 3M South Africa & Sub-Saharan Africa, 146A Kelvin Drive, Woodmead, Sandton, South Africa, Tel: (0861) 225536 |
| 3M (East) AG Representation Office Tirane, Rruga Sami Frasheri, Pallati i Ri Perxhola Kati 2 Ap2, 1000 Albania |
| 3M Arabia, LLC, Building 24-25 3M Saudi Arabia Zone C, Business Gate, Airport Road, Riyadh, Saudi Arabia |
| 3M Bulgaria, Mladost 4, Business Park, bl.4, 2nd floor, Sofia 1766, Bulgaria |
| 3M Česko, spol. s r.o., V Parku 2343/24, 148 00 - Praha 4, Czech Republic |
| 3M (East) AG, Branch office Croatia, Avenija Većeslava Holjevca 40, 10 000 Zagreb, Croatia, Tel: +385 1 2499750, www.3m.com.hr |
| 3M Egypt, Finance Center , New Cairo , Plot 140 , Banking Sector , 5th settlement , Cairo , Egypt |
| 3M Hellas MEPE, Automotive Aftermarket Division, 20 Kifisias Avenue, 151 25 Marousi, Greece, Phone: +30 210 68 85 300, innovation.gr@mmm.com, www.3M.gr |
| 3M Hungária Kft, Neumann János u. 1/E, 1117 Budapest, Hungary |
| 3M Israel, 91 Medinat Hayehudim St., Herzliya, Israel |
| 3M Kenya Ltd, Victoria Towers, 3rd Floor, Kilimanjaro Av, Upperhill, Kenya |
| 3M Gulf Limited, Ein El Mreisseh, Saint Charles City Center, 4th. Floor, P.O.Box: 11-5025, Riad el Solh, Beirut 1107 2180 Lebanon |
| 3M Minnesota Mining & Manufacturing Nigeria Limited, No 2 Sheraton Opebi Link Road, Ikeja, Lagos Nigeria |
| 3M Pakistan, Islamic Chamber of Commerce Building, ST-2/A, Block 9, KDA Scheme 5, Clifton, Karachi, Pakistan |



Technical Data Sheet

Effective: 02/03/2020 Supersedes: 15/06/2007

| |
|--|
| 3M Poland, Al. Katowicka 117, Kajetany, 05-830 Nadarzyn, Poland, Telefon: +48 22 739 60 00, www.3m.pl/kontakt |
| 3M Gulf (Representation Office), Suhaim Bin Hamad St., Al Mana Towers Tower B, 2nd Floor, Office No.4, Doha Qatar, P.O.Box 14685 |
| 3M Romania, 12 Menuetului St., Bucharest Business Park, Building D, District 1 013713 Bucharest, Romania |
| 3M (East) AG, Representation Office Serbia, Airport City, Omladinskih brigada 90B, 11070 Belgrade, Serbia, Tel: +381 11 2209 400, www.3m.co.rs/3M/sr_RS/3m-south-east-europe/ |
| 3M Slovensko s.r.o., Polus Tower 2, Vajnorská 100/B, 83104 Bratislava |
| 3M (East) AG, Branch office Slovenia, Cesta v Gorice 8, 1000, Ljubljana, Slovenia, Tel: +386 1 2003 630, www.3m.com/3M/sl_SI/3m-south-east-europe/ |
| 3M Sanayi ve Ticaret As, Barbaros Mah., Mor Sümbül Sok., No:7/3F, 27-51, Nidakule Ataşehir Güney, 34746 Ataşehir, İstanbul, Turkey |
| 3M Gulf Limited, Dubai Internet City, Building No. 11, 3rd Floor, U.A.E |

© 3M 2019. 3M is a trademark of the 3M company. All rights reserved