

3M Advanced Materials Division

# 3M™ Evaporation Boats 3.0

## Introduction

3M is a leading manufacturer of evaporation boats for metallizing applications. 3M™ Evaporation Boats 3.0 (EB 3.0) are a new generation of two-component boats with improved material formulation. They are designed for high efficiency and consistent product quality.

These high-performance evaporation boats are easy to run and provide high evaporation rates combined with a long service life and reduced energy consumption.

3M Evaporation Boats 3.0 are made of 3M™ Titanium Diboride (electrically conductive with high resistance to chemicals and heat) and 3M™ Boron Nitride (thermally conductive with high electrical resistivity).

In comparison with previous generations of evaporation boats, the new 3M Evaporation Boats 3.0 provide:

- Robustness even under harsh process conditions and high temperatures
- New cavity design/evaporation surface for minimum spitting
- Energy consumption reduced versus legacy 3M boats
- Long service life even at high evaporation rates
- Uniform and consistent quality of metallized film – a truly operator friendly evaporation boat

**Storage conditions:** At or above 5°C, in original packaging

### Additional products for metallizing

- 3M™ Boron Nitride Suspension WS
- 3M™ Graphite Suspension
- 3M™ Graphite Tape



## Hot Resistivity Groups

(Not for specification purposes.)

2-component	Hot Resistivity (m $\Omega$ )	2-component	Hot Resistivity (m $\Omega$ )
R2	3700 $\pm$ 300	R4	2700 $\pm$ 300
R3	3200 $\pm$ 300	R5	2300 $\pm$ 200

## Typical Physical Properties

(Not for specification purposes.)

Property	3M™ Evaporation Boats 3.0
Density, $\rho$ (g/cm <sup>3</sup> )	>2.75
Porosity, P (%)	<5
Maximum water uptake (%) at 38°C, 90% RH	<0.2
Phase composition	TiB <sub>2</sub> , BN
Color	Grey
<b>Electrical Properties*</b>	
Resistivity <sup>1</sup> at 1500°C, $\rho$ (10 <sup>-6</sup> $\Omega$ cm)	1300-4800
<b>Mechanical Properties at Room Temperature*</b>	
Brinell hardness (HB 2.5/31.25)	60
Flexural strength, 4-point bending, $\sigma$ (MPa)	95
Young's modulus, E (GPa)	54
Fracture toughness <sup>2</sup> K <sub>1c</sub> (MPa $\sqrt$ m)	2.3
<b>Thermal Properties*</b>	
Maximum thermal extension at 25–1500°C (%)	<0.8
Coefficient of thermal expansion at 25–1500°C, $\alpha$ (10 <sup>-6</sup> /K)	4.8
Specific heat at 25°C, c <sub>p</sub> (J/g•K)	0.73
Thermal conductivity at 25°C, $\lambda$ (W/m•K)	66

\* These figures are intended as a guide and should not be used in preparing specifications. They are subject to production tolerances and are in accordance with the current state of the art.

1. Dependent on resistivity group 2. SENB (single-edge notched bending)

## Product Development and Manufacturing

We work closely with our customers and with equipment manufacturers to develop optimal, cost-effective solutions for metallizing applications. 3M™ Evaporation Boats are the result of intensive research and development, the use of modern processing and manufacturing techniques, and high-quality 3M advanced ceramic materials. Our manufacturing processes are optimized to ensure reliable and repeatable product performance, even for large lot sizes. Key raw materials are produced in-house, and we perform quality control checks after each production step. The ceramic powders are hot pressed into homogenous sinter billets, which are then cut to customer specifications in our fully equipped precision diamond cutting and grinding facilities. In the last step of the process, the cavities are machined.

## About 3M Advanced Ceramics

3M is one of the world's leading manufacturers of advanced ceramic products and materials for industrial applications. Our extensive range of ceramic materials includes borides ( $\text{TiB}_2$ ,  $\text{ZrB}_2$ ), carbides ( $\text{SiC}$ ,  $\text{B}_4\text{C}$ ) and nitrides ( $\text{Si}_3\text{N}_4$ ,  $\text{BN}$ ). We offer these products in a variety of forms, including functional additives and final articles such as bearings, seal rings, blast nozzles and crucibles.

3M advanced ceramic products are manufactured at fully dedicated, ISO 9001 and 14001 certified facilities. Our manufacturing processes are optimized for quality, efficiency and consistency – helping ensure reliable and repeatable product performance. We have more than 85 years of experience in designing and manufacturing cutting-edge ceramic solutions, and we continually work to develop new applications for ceramic materials in cooperation with our customers and with research institutions. To learn more about our high-performance ceramic products, contact us at **+49 (0)831 5618-0**.

**Warranty, Limited Remedy, and Disclaimer:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. User is solely responsible for evaluating third party intellectual property rights and for ensuring that user's use of 3M product does not violate any third party intellectual property rights. Unless a different warranty is specifically stated in the applicable product literature or packaging insert, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OF NON-INFRINGEMENT OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except where prohibited by law, 3M will not be liable for any loss or damages arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

**Technical Information:** Technical information, recommendations, and other statements contained in this document or provided by 3M personnel are based on tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.



### 3M Advanced Materials Division

3M Technical Ceramics  
Zweigniederlassung der 3M Deutschland GmbH  
Max-Schaidhauf-Str. 25  
87437 Kempten, Germany  
Phone +49 (0)831 5618-0  
[www.3M.com/advancedceramics](http://www.3M.com/advancedceramics)

The management system has been certified according to DIN EN ISO 9001, DIN EN ISO 50001, DIN EN ISO 14001.

3M is a trademark of 3M Company. Used under license by 3M subsidiaries and affiliates.

Please recycle. Printed in USA © 3M 2020.  
All rights reserved. Issued: 3/20 16099HB  
98-0213-6868-7