



# Nastro Mascheratura Anodizzazione 8985L

## Bollettino Tecnico

Date: March 2020  
Supersedes: NEW

### Product Description

3M™ Anodization Masking Tape 8985L is a purple printed polyester tape with a rubber adhesive and non-silicone release liner. Designed specifically for masking components that are subjected to anodization bath processes.

### Key Features

- Strong backing provides very good abrasion, tear, scratch, puncture and moisture resistance to help protect surfaces.
- The purple translucent backing allows for visual inspection without tape removal.
- Provides good initial tack and holding strength.
- Rubber adhesive specially formulated to resist the harshest of chemical bath chemistries and provide clean removal when finished.
- Non-silicone adhesive allows use on many parts where subsequent painting or bonding is necessary.
- Non-silicone liner allows for die-cuts.

### Product Construction

Backing	Polyester, purple printed
Adhesive	Rubber
Liner	Polyester
Backing Thickness ASTM D3652	0.076 mm
Total Thickness (without Liner) ASTM D3652	0.099 mm
Liner Thickness ASTM D3652	0.051 mm

### Performance Characteristics

Adhesion to Stainless Steel ASTM D3330	23 N / 100 mm
Tensile Strength ASTM D3759	1234N / 100 mm
Elongation at Break ASTM D359	126 %
Temperature Use Range	Up to 93 °C

---

## Application Ideas

- Masking during anodization operations.
- 

## Surface Preparation

Clean surfaces prior to masking, such as alkaline clean and deoxidize.

- Improve masking success by chemfilm surface prior to masking.

## Masking

- Optimal adhesion is obtained when both the tape and intended surface are within a temperature range of 16° to 27 °C.
- To apply the tape, remove a portion of the liner from one end of the tape and firmly tack it down to the surface.

Gently pull liner away from tape at an angle as it is being

applied by hand.

- Once the tape has been applied, firmly apply pressure to improve bond strength to surface. Additional tools (wipers, rollers, etc.) may be needed to achieve proper bond.
- Squeegee out any air bubbles that may be trapped between the tape and the surface. Special attention to masking edges for better sealing from chemicals.

## Removal Techniques

- Allow masking tape to dwell greater than four hours after part processing before removal.

## Plotter Suggestions

- Plotter Test Plot: Imperative to test and verify that the blade cuts all the way through the tape
  - Plotter Pressure: Validate pressures are set to cut through the tape (backing and adhesive) to the liner. Pressure settings may need to be increased depending on the thickness of the product and what material was run on the plotters previously.
  - Blade Angle: 45- or 60-degree angle preferred
  - Blade Adjustment: If the blade is too far into the housing it isn't exposing enough blade to cut through down to the liner. Adjust the blade to expose more in order to cut through the material.
  - Fresh Blade: Blades need to be routinely changed in order to remain sharp to cut through the material correctly.
  - Plotter Maintenance: Routine maintenance should be performed on plotters when inconsistent cuts are observed. (cutter protection strip, blade holder, etc)
-

---

**Storage & Shelf Life**

Store at 16°C – 25 °C and 40-65 % relative humidity in its original packaging material. The product can be stored up to 12 months after production.

---

**For Additional Information**

To request additional product information or to arrange for sales assistance, call.....  
Address correspondence to: 3M

---

**Important Notice**

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

---

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

---

3M is a trademark the 3M Company.

**Insert Company Information Before Issue**