

3M Advanced Materials Division

# 3M™ Ionomers

## 800EW Ionomer

### Features and Benefits

- High power output
- High proton conductivity at low relative humidity
- Low gas permeation
- Good mechanical strength at high relative humidity
- High thermal stability
- High chemical resistance
- Solid format provides maximum flexibility to customize product formulations
- Room-temperature dispersible in common solvent systems

*Note: Data in this document are not for specification purposes.*

### Typical Values

Property	Test Method	800EW
Visual Aspect		Off-White Granules
Ionomer Equivalent Weight	3M Internal Method*	800*
Ion Exchange Capacity (meq/g)		1.25
Viscosity mPa-s @ 20C°/1s-1	3M Internal Method** (60/40 n-propanol/water dispersion)	50-300 20% solids

\* FT-IR of polymer SO<sub>2</sub>F content

\*\*Rotational viscometer

### Product Description

3M™ Ionomer 800EW are copolymers of tetrafluoroethylene and perfluorobutanesulfonylfluoride vinyl ether, offered in an equivalent weight of 800EW. It is an excellent for use in membranes and electrode formulations in PEM fuel cells and in other electrochemical applications.

The high proton conductivity of 3M ionomers creates the potential to achieve higher energy output with a smaller fuel cell stack. They may also allow a reduction in the amount of expensive platinum catalyst used in electrode applications, and in turn could reduce system cost. 3M ionomers feature a linear side chain and stabilized end groups for improved chemical durability – even in demanding electric vehicle applications.

### Product Form and Packaging

This product is supplied in solid form and is packaged in plastic containers. It is available in 1kg, 10kg, and 25kg packages.

### Storage and Material Handling

3M Ionomers should be stored under clean, dry conditions in the unopened original containers received from 3M. It is recommended to store the product at room temperature away from direct sunlight or other sources of heat or irradiation. These ionomers are hygroscopic and moisture content needs to be considered when preparing dispersions based on these materials. Keep containers tightly sealed to avoid moisture absorption.

## Safety and Toxicology

This is a fluoroplastic material, so normal precautions observed with fluoroplastics should be followed. Before processing this product, be sure to read and follow all precautions and directions for use contained in the product label and the Safety Data Sheet. General handling/processing precautions include:

1. Process only in well-ventilated areas.
2. Do not smoke in areas contaminated with powder/residue from this product.
3. Avoid eye contact.
4. After handling this product, wash any contacted skin with soap and water.

Potential hazards, including evolution of vapors, can exist if processing occurs under excessively high temperature conditions. Vapor extractor units should be installed above processing equipment. When cleaning processing equipment, do not burn off any of this product with an open flame or in a furnace.

**Warranty, Limited Remedy, and Disclaimer:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. User is solely responsible for evaluating third party intellectual property rights and for ensuring that user's use of 3M product does not violate any third party intellectual property rights. Unless a different warranty is specifically stated in the applicable product literature or packaging insert, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OF NON-INFRINGEMENT OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except where prohibited by law, 3M will not be liable for any loss or damages arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

**Technical Information:** Technical information, recommendations, and other statements contained in this document or provided by 3M personnel are based on limited information and the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.



### 3M Advanced Materials Division

3M Center  
St. Paul, MN 55144 USA

Phone 1-800-810-8499  
Web [www.3M.com/Ionomers](http://www.3M.com/Ionomers)

3M is a trademark of 3M Company. Used under license.

© 3M 2022.  
All rights reserved. Issued: 3/22  
98-0050-0051-2 Rev. C