


ABSTRACT

Test Material:	3M Fire Dam 150+ Caulk		
Test Standard:	ASTM E84-00a Standard Test Method for SURFACE BURNING CHARACTERISTICS OF BUILDING MATERIALS (ANSI 2.5, NFPA 255, UBC 8-1, UL 723)		
Test Date:	August 28, 2000		
Test Sponsor:	3M Company		
Test Results:	FLAME SPREAD INDEX	=	0
	SMOKE DEVELOPED INDEX	=	0

The description of the test procedure and specimen evaluated, as well as the observations and results obtained, contained herein are true and accurate within the limits of sound engineering practice. These results are valid only for the specimen(s) tested and may not represent the performance of other specimens from the same or other production lots.


Omega Point Laboratories, Inc. authorizes the client named herein to reproduce this report only if reproduced in its entirety.

The test specimen identification is as provided by the client and Omega Point Laboratories accepts no responsibility for any inaccuracies therein.



Guy A. Haby
Fire Testing Technologist

Date: August 29, 2000



William E. Fitch, P.E. No. 55296
Executive Vice President

Date: August 29, 2000

