



## Automotive Aftermarket Division

### 3M™ Bodygard Textured Coating, Anti-chip Coating, White

---

#### 1) Part Numbers

08875 3M™ Bodygard Textured Coating, Anti-chip coating White

#### 2) Description and end use

3M™ Anti-chip Coating White, PN08875 is an alkyd resin-based stone-block protector, with excellent anticorrosive and soundproofing properties. Over paintable and quick drying.

Key Features:

- Excellent stone-chip resistance.
- Excellent anti-corrosive and soundproofing properties
- Tack free time in 10-15 minutes.
- Can be painted over with air drying and low bake paints after two hours at room (23°C) temperatures. The application of a primer can be done if recommended.
- Different 3M spray applicators can be used as Standard 3M 08996 or Pressure Pot 3M 08991 or 3M™ Accuspray™ HGP system to achieve a variation of textures from one gun

#### 3) Physical Properties

Container	1 kg
Base	Alkyd resin-based
Density kg/litre (Approx.)	1.3
Color	White
Capacity	4 m <sup>2</sup> /kg with thickness 100/120 µm
Solids Content (Approx.)	59 +/- 1%
Tack free	30 minutes
Over paintable after	30 minutes
Shelf Life	18 Months



## 4) Directions for Use

### Product uses:

Developed for application to lower auto body panels for stone chip protection. For best results this coating must be applied to primer or paint coated surfaces and top coated with automotive type paint systems.

Use with the following applicator: 3M™ Body Schutz™ Applicator PN 08996 or Pressure Pot 08991 or 3M™ Accuspray™ HGP PN 16587.

### Directions for use:

1. Surfaces must be degreased and clean.
2. Shake the can well before use.
3. Make sure that the safety holes of the gun are free to avoid possible breakage of the tin due to excessive pressure.
4. Remove the plastic protection by pulling the ring on the top of the package.
5. Pierce the container with a screwdriver or similar.
6. Spray the product with constant speed at a distance of about 20/40 cm using a pressure of 3/5 bar.
7. Best results are obtained with the 3M 08996 spray gun or Pressure Pot 08991 or 3M™ Accuspray™ HGP PN 16587.
8. The product can be overpainted about 30 minutes after application.

## 5) Storage

For maximum shelf life, store the product at a temperature between 15°C and 30°C. Higher temperatures reduce the shelf life, while lower temperatures result in increased temporary viscosity. Carry out stock rotation according to the "FIFO" criteria: "first in - first out".

## 6) Safety

Refer to Product Label and Material Safety Data Sheet for Health and Safety Information before using this product.

**3M™ 08875 Bodygard Textured Coating, Anti-chip Coating is designed FOR PROFESSIONAL INDUSTRIAL USE ONLY.**



## 7) Disclaimer

All statements, technical information and recommendations are based on tests we believe to be reliable as at the date of hereof, but the accuracy or completeness thereof is not guaranteed. Please ensure before using the product that it is suitable for your intended use. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, other than for fraudulent misrepresentation, 3M expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information.



# Technical Data Sheet

Effective: 05/01/22 Supersedes: New

## For Additional Health and Safety Information

3M South Africa & Sub-Saharan Africa, 146A Kelvin Drive, Woodmead, Sandton, South Africa, Tel: (0861) 225536
3M (East) AG Representation Office Tirane, Rruga Sami Frasheri, Pallati i Ri Perxhola Kati 2 Ap2, 1000 Albania
3M Arabia, LLC, Building 24-25 3M Saudi Arabia Zone C, Business Gate, Airport Road, Riyadh, Saudi Arabia
3M Bulgaria, Mladost 4, Business Park, bl.4, 2nd floor, Sofia 1766, Bulgaria
3M Česko, spol. s r.o., V Parku 2343/24, 148 00 - Praha 4, Czech Republic
3M (East) AG, Branch office Croatia, Avenija Većeslava Holjevca 40, 10 000 Zagreb, Croatia, Tel: +385 1 2499750, www.3m.com.hr
3M Egypt, Finance Center , New Cairo , Plot 140 , Banking Sector , 5th settlement , Cairo , Egypt
3M Hellas MEPE, Automotive Aftermarket Division, 20 Kifisias Avenue, 151 25 Marousi, Greece, Phone: +30 210 68 85 300, innovation.gr@mmm.com, www.3M.gr
3M Hungária Kft, Neumann János u. 1/E, 1117 Budapest, Hungary
3M Israel, 91 Medinat Hayehudim St., Herzliya, Israel
3M Kenya Ltd, Victoria Towers, 3rd Floor, Kilimanjaro Av, Upperhill, Kenya
3M Gulf Limited, Ein El Mreisseh, Saint Charles City Center, 4th. Floor, P.O.Box: 11-5025, Riad el Solh, Beirut 1107 2180 Lebanon
3M Minnesota Mining & Manufacturing Nigeria Limited, No 2 Sheraton Opebi Link Road, Ikeja, Lagos Nigeria
3M Pakistan, Islamic Chamber of Commerce Building, ST-2/A, Block 9, KDA Scheme 5, Clifton, Karachi, Pakistan
3M Poland, Al. Katowicka 117, Kajetany, 05-830 Nadarzyn, Poland, Telefon: +48 22 739 60 00, www.3m.pl/kontakt
3M Gulf (Representation Office), Suhaim Bin Hamad St., Al Mana Towers Tower B, 2nd Floor, Office No.4, Doha Qatar, P.O.Box 14685
3M Romania, 12 Menegetului St., Bucharest Business Park, Building D, District 1 013713 Bucharest, Romania
3M (East) AG, Representation Office Serbia, Airport City, Omladinskih brigada 90B, 11070 Belgrade, Serbia, Tel: +381 11 2209 400, www.3m.co.rs/3M/sr_RS/3m-south-east-europe/
3M Slovensko s.r.o., Polus Tower 2, Vajnorská 100/B, 83104 Bratislava
3M (East) AG, Branch office Slovenia, Cesta v Gorice 8, 1000, Ljubljana, Slovenia, Tel: +386 1 2003 630, www.3m.com/3M/sl_SI/3m-south-east-europe/
3M Sanayi ve Ticaret As, Barbaros Mah., Mor Sümbül Sok., No:7/3F, 27-51, Nidakule Ataşehir Güney, 34746 Ataşehir, İstanbul, Turkey
3M Gulf Limited, Dubai Internet City, Building No. 11, 3rd Floor, U.A.E

3M, Accuspray are trademarks of 3M Company, © 3M 2022, All rights reserved.