



Technical Data Sheet

3M™ Scotch-Weld™ Epoxy Potting Compound/Adhesive DP270 Clear



[Product Details](#)



[Regulatory Info/SDS](#)

Product Description

3M™ Scotch-Weld™ Epoxy Potting Compound/Adhesive DP270 (or 3M™ Scotch-Weld™ Epoxy Potting Compound/Adhesive 270 B/A) is a two-part, low viscosity epoxy resin system designed primarily for potting, sealing, and encapsulation of many electronic components and is available in clear or black. Scotch-Weld epoxy potting compound/adhesive DP270 is noncorrosive to copper and offers good thermal shock resistance and excellent retention of electrical insulation properties under high humidity conditions.

3M™ Scotch-Weld™ epoxy potting compound/adhesive DP270 has a work life of approximately 70 minutes, a tack-free time of about 3 hours and is fully cured after 48 hours at 73°F (23°C). This product produces no exotherm in 5-10 gram masses and a very slight exotherm in larger masses.

3M™ Scotch-Weld™ epoxy potting compound/adhesive DP270 is ideal for the potting and encapsulation of many heat sensitive or delicate components such as glass diodes and sensors as well as for transformers, coils, chokes, relays, etc. It is available in the convenient 3M™ EPX™ Applicator System for multi-station usage and in bulk containers for larger volume applications.

Available in bulk containers as Scotch-Weld epoxy potting compound/adhesive 270 B/A.

Product Features

- Good Thermal Shock Resistance
- Excellent Electrical Properties
- Meets UL 94 HB (File No. E61941)
- Noncorrosive to Copper
- Long Worklife
- Negligible Exotherm

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Uncured Physical Properties

Attribute Name	Value
Mix Ratio by Volume (B:A)	1:1
Mix Ratio by Weight (B:A)	1:0.85

Attribute Name	Temperature	Value
Base Color		Nearly Colorless
Accelerator Color		Amber
Base Resin		Epoxy
Accelerator Resin		Amine
Base Viscosity	22 °C (72 °F)	7000 — 16000 cP
Accelerator Viscosity	22 °C (72 °F)	6000 — 12000 cP

Typical Mixed Physical Properties

Attribute Name	Temperature	Value
Cure Shrinkage		0.08 %
Worklife	22 °C (72 °F)	60 — 70 min
Open Time		60 min ¹
Tack Free Time	22 °C (72 °F)	3 h

Attribute Name	Temperature	Value
Time to Handling Strength	22 °C (72 °F)	3 h ²
Time to Full Cure	22 °C (72 °F)	48 h ³

¹ Max time allowed after applying adhesive to a substrate before bond must be closed and fixed. Cure times approximate and depend on adhesive temperature. Hotmelts: The approx. bonding range of a 1/8" bead of molten adhesive on a non-metallic surface.

² Minimum time required to achieve 50 psi of overlap shear strength. Cure times are approximate and depend on adhesive temperature.

³ The cure time is defined as that time required for the adhesive to achieve a minimum of 80% of the ultimate strength as measured by aluminum-aluminum OLS.

Typical Physical Properties

Attribute Name	Value
Cured Color	Clear
UL Listing	94 HB (File No. E61941)

Typical Cured Characteristics

Attribute Name	Test Method	Temperature	Value
Compression Strength	ASTM D695	22 °C (72 °F)	8,100 lb/in ² ¹
Shore D Hardness	ASTM D2240	22 °C (72 °F)	83 ²
Refractive Index		22 °C (72 °F)	1.656
Weight Loss by Thermal Gravimetric Analysis (TGA)		122 °C (252 °F)	1 %
Weight Loss by Thermal Gravimetric Analysis (TGA)		175 °C (347 °F)	5 %
Weight Loss by Thermal Gravimetric Analysis (TGA)		210 °C (410 °F)	10 %

¹ 3M™ Scotch-Weld™ Epoxy Potting Compound/Adhesive DP270 and 270 B/A can be used for, potting, encapsulation, and adhesive applications.

² Tensile and Elongation. Samples were 51 mm (2") dumbbells with 3 mm (0.125") neck and 0.8 mm (0.03" sample thickness. Separation rate was 51 mm/min (2"/min)

Test Condition: Potted Washer Olyphant Test, 100°C [air] ~ -50°C [liquid]

Attribute Name	Test Method	Value
Thermal Shock Resistance	3M C3174	Pass 5 Cycles without cracking

Typical Performance Characteristics

Overlap Shear Strength

Surface Prep: MEK Wipe

Temperature: 22 °C (72 °F)

Dwell Time: 7 d

Test Method: ASTM D1002, ISO 4587

Substrate	Value
Copper	1700 — 1750 lb/in ² ¹
FR-4	1750 — 1800 lb/in ² ¹

¹ 3M™ Scotch-Weld™ Epoxy Potting Compound/Adhesive DP270 and 270 B/A can be used for, potting, encapsulation, and adhesive applications. The following shows typical shear and peel values determined on several common substrates. 0.005-0.008in bondline

Substrate: Aluminum to Etched Aluminum

Temperature: 22 °C (72 °F)

Attribute Name	Test Method	Value
T-Peel Adhesion	ASTM D1876	>2 lb/in width ¹

¹ 3M™ Scotch-Weld™ Epoxy Potting Compound/Adhesive DP270 and 270 B/A can be used for, potting, encapsulation, and adhesive applications.

Typical Environmental Performance

Solvent Resistance

Environmental Condition	Value
24hr @ RT + 2hr @ 71°C (160°F) + Isopropyl Alcohol 1hr	A ¹
24hr @ RT + 2hr @ 71°C (160°F) + Acetone 1hr	B ¹
24hr @ RT + 2hr @ 71°C (160°F) + 1, 1, 1 - Trichloroethane 1hr	A ¹
24hr @ RT + 2hr @ 71°C (160°F) + Freon TF 1hr	A ¹
24hr @ RT + 2hr @ 71°C (160°F) + Freon TMC 1hr	B ¹
24hr @ RT + 2hr @ 71°C (160°F) + RMA Flux 1hr	A ¹
24hr @ RT + 2hr @ 71°C (160°F) + Isopropyl Alcohol 1mo	B ¹
24hr @ RT + 2hr @ 71°C (160°F) + Acetone 1mo	C ¹
24hr @ RT + 2hr @ 71°C (160°F) + 1, 1, 1 - Trichloroethane 1mo	C ¹
24hr @ RT + 2hr @ 71°C (160°F) + Freon TF 1mo	A ¹
24hr @ RT + 2hr @ 71°C (160°F) + Freon TMC 1mo	C ¹
24hr @ RT + 2hr @ 71°C (160°F) + RMA Flux 1mo	B ¹

¹ Cured OLS samples immersed in solvent and after dwell, examined for surface attack compared to control.

A: Unaffected, no color or texture change

B: Slight attack, slight swelling of surface.

C: Moderate/severe attack, extreme swelling of surface.

Electrical and Thermal Properties

Attribute Name	Test Method	Temperature	Test Condition	Value
Glass Transition Temperature (Tg)			Onset	43 °C (109 °F) ¹
Glass Transition Temperature (Tg)			Mid-Point	49 °C (120 °F) ¹
Coefficient of Thermal Expansion			Below Tg (5°C to 30°C)	80 x 10 ⁻⁶ m/m/°C
Coefficient of Thermal Expansion			Above Tg (60°C to 125°C)	180 x 10 ⁻⁶ m/m/°C
Thermal Conductivity	C177	110 °F		4.25 x 10 ⁻⁴ Cal/s/cm/°C (0.178 W/m/K) (0.103 (btu-ft)/(h-ft ² -°F)) ²

¹ Glass Transition Temperature (Tg) determined using DSC Analyzer with a heating rate of 68°F (20°C) per minute. Second heat values given.

² Thermal conductivity determined using C-matic Instrument using 2 in. diameter samples.

Attribute Name	Test Method	Temperature	Test Condition	Value
Dielectric Constant	ASTM D150	22 °C (72 °F)	1 KHz	3.5
Dissipation Factor	ASTM D150	22 °C (72 °F)	1 KHz	0.018
Insulation Resistance			1000 hrs	2 x 10 ¹¹ Ω ¹
Insulation Resistance			Initial	3 x 10 ¹³ Ω ¹
Volume Resistivity	ASTM D257	22 °C (72 °F)		4.1 x 10 ¹⁴ Ω-cm

¹ 0.8 mm/0.8 mm comb pattern on FR-4, 60°C/96% R.H./100 volts d.c.

3M™ EPX™ Pneumatic Applicator Delivery Rates

Test Condition: 48.5/50 ml Applicator – Maximum Pressure 50 psi. 1/4 in. Nozzle

Attribute Name	Value
Pneumatic Applicator Delivery Rates	75.6 g/min ¹

¹ Tests were run at a temperature of 70°F ± 2°F (21°C ± 1°C) and at maximum applicator pressure.

Handling/Application Information

Directions for Use

1. For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. However, the amount of surface preparation directly depends on the required bond strength and the environmental aging resistance desired by user. For specific surface preparations on common substrates, see the section on surface preparation.

2. These products consist of two parts.

Mixing

For Duo-Pak Cartridges

3M™ Scotch-Weld™ epoxy potting compound/adhesive DP270 Clear and Black are supplied in a dual syringe plastic duo-pak cartridge as part of the 3M™ EPX™ Applicator systems. To use, simply insert the duo-pak cartridge into the EPX applicator and start the plunger into the cylinders using light pressure on the trigger. Next, remove the duo-pak cartridge cap and expel a small amount of adhesive to be sure both sides of the duo-pak cartridge are flowing evenly and freely. If mixing of Part A and Part B is desired, attach the EPX applicator mixing nozzle to the duo-pak cartridge and begin dispensing the adhesive. For hand mixing, expel the desired amount of material and mix thoroughly to obtain a uniform color.

For Bulk Containers

Mix thoroughly by weight or volume in the proportions specified in the typical uncured properties section to obtain a uniform color.

3. For maximum bond strength apply product evenly to both surfaces to be joined.

4. Application to the substrates should be made within 70 minutes. Larger quantities and/or higher temperatures will reduce this working time.

5. Join the adhesive coated surfaces and allow to cure at 60°F (16°C) or above until firm. Heat up to 200°F (93°C) will speed curing.

6. The following times and temperatures will result in a full cure of these products.

23°C (73°F) 48 Hours
50°C (122°F) 4 Hours
80°C (176°F) 60 Minutes
100°C (212°F) 30 Minutes

7. Keep parts from moving during cure. Contact pressure necessary. Maximum shear strength is obtained with a 3-5 mil bond line.

8. Excess uncured adhesive can be cleaned up with ketone type solvents*.

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

Adhesion Coverage:A 0.005 in thick bondline will yield a coverage of 320 sqft/gallon

Surface Preparation

For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. However, the amount of surface preparation directly depends on the required bond strength and the environmental aging resistance desired by user.

The following cleaning methods are suggested for common surfaces:

Steel

1. Wipe free of dust with oil-free solvent such as acetone, isopropyl or alcohol solvents.*
2. Sandblast or abrade using clean fine grit abrasives.
3. Wipe again with solvent to remove loose particles.
4. If a primer is used, it should be applied within 4 hours after surface preparation.

Aluminum

1. Alkaline Degrease: Oakite 164 solution (9-11 oz./gallon water) at 190°F ± 10°F (88°C ± 5°C) for 10-20 minutes. Rinse immediately in large quantities of cold running water.

2. Acid Etch: Place panels in the following solution for 10 minutes at 150°F ± 5°F (66°C ± 2°C).

Sodium Dichromate 4.1 - 4.9 oz./gallon

Sulfuric Acid, 66°Be 38.5 - 41.5 oz./gallon 2024-T3 aluminum (dissolved) 0.2 oz./gallon minimum Tap water as needed to balance

3. Rinse: Rinse panels in clear running tap water.

4. Dry: Air dry 15 minutes; force dry 10 minutes at 150°F ± 10°F (66°C ± 5°C).

5. If primer is to be used, it should be applied within 4 hours after surface preparation.

Plastics/Rubber

1. Wipe with isopropyl alcohol.*

2. Abrade using fine grit abrasives.

3. Wipe with isopropyl alcohol.*

Glass

1. Solvent wipe surface using acetone or MEK.*

2. Apply a thin coating (0.0001 in. or less) of 3M™ Scotch-Weld™ Metal Primer EC3901 to the glass surfaces to be bonded and allow the primer to dry 60 minutes before bonding.

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

Application Equipment

These products may be applied by spatula, trowel or flow equipment.

Two part mixing/proportioning/dispensing equipment is available for intermittent or production line use. These systems are ideal because of their variable shot size and flow rate characteristics and are adaptable to most applications.

Industry Specifications

UL 94 HB (File E61941)

Storage and Shelf Life

Store under normal conditions of 16° to 27°C (60° to 80°F) in the original, unopened packaging, out of direct sunlight. For best performance, use this product within 12 months from date of manufacture.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577

Automotive Disclaimer

Select Automotive Applications:

This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price. Warranty claims must be made within one (1) year from the date of 3M's shipment.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

ISO Statement

This product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M™ Industrial Adhesives and Tapes Division
3M Center, St. Paul, MN 55144-1000
3M.com/iatd

3M, Scotch-Weld and EPX are trademarks of 3M Company.
©3M 2024 (6/24)