



## Technical Data Sheet

### 3M™ Scotch-Weld™ Low Odor Instant Adhesive LO1000



Product Details



Regulatory Info/SDS

#### Product Description

3M™ Scotch-Weld™ Low Odor Instant Adhesives are formulated to have low volatility while maintaining bonding of a wide range of materials. Low volatility means that these products are not only low odor but also low blooming. White residues (chlorosis) of the joint area are eliminated to improve appearance in cosmetically critical applications. Lower odor can improve worker comfort in work areas where ventilation is limited. These products reduce the requirement for sophisticated ventilation systems that may be necessary when dispensing other cyanoacrylates.

#### Product Features

- 3M™ Scotch-Weld™ Low Odor Instant Adhesive LO1000 is a high viscosity low odor cyanoacrylate that has good gap-filling capability.

#### Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

#### Typical Uncured Physical Properties

Attribute Name	Value
Color	Clear <sup>1</sup>
Viscosity	850 — 1250 cP <sup>2</sup>
Base	Methoxyethyl

<sup>1</sup> Colors may vary from nearly white to yellow/amber. Adhesive performance is not affected by color variation.

<sup>2</sup> Cone-Plate viscosity, CP50 at 100/s shear rate

#### Typical Mixed Physical Properties

Attribute Name	Temperature	Value
Time to Full Cure	23 °C (73 °F)	24 h <sup>1</sup>
Time to Handling Strength		30 s <sup>2</sup>
Gap Fill		0.008 in
Percent of Initial Strength	23 °C (73 °F)	100 %
Percent of Initial Strength	75 °C (167 °F)	56 %
Percent of Initial Strength	100 °C (212 °F)	23 %
Percent of Initial Strength	125 °C (257 °F)	10 %

<sup>1</sup> The cure time is defined as that time required for the adhesive to achieve a minimum of 80% of the ultimate strength as measured by aluminum-aluminum OLS.

<sup>2</sup> Min time between bond creation and ability to support a 34 kPa (5 psi) tensile load. Open and set times determined by RT environment. Higher temps will lengthen open and set times, while lower temperatures will shorten open time and set time.

#### Typical Physical Properties

Attribute Name	Value
Appearance	Liquid
Specific Gravity	1.08 g/mL

## **Handling/Application Information**

### **Directions for Use**

1. Ensure that parts are clean, dry, and free from oil and grease.
2. An instant adhesive activator may be required if there are bonding gaps or porous substrate surfaces, if substrates are low surface energy plastics (e.g., polyethylene, polypropylene) or if substrates have acidic surfaces (e.g., paper, leather).
3. Bond speed is typically very fast so ensure that parts are properly aligned before dispensing.
4. Product is normally hand applied from the bottle. Apply sparingly to one surface and press parts firmly together until handling strength is achieved. As a general rule, as little cyanoacrylate as possible should be used. Over application will result in slower cure speed and lower bond strength.

### **Surface Preparation**

For optimum strength structural bonds, paint, oxide films, oils, dust, mold release agents, and all other surface contaminants must be completely removed. However, the amount of surface preparation depends on the required bond strength and the environmental aging resistance desired by the user. Typical quick surface preparation would include wiping with a clean solvent (such as isopropyl alcohol\*), abrading the surface with a clean fine abrasive, and then wiping again with a clean solvent to remove loose particles.

\*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

### **Cured Bond Characteristics**

1. Full bond strength will typically be achieved within a 24 hour cure time.
2. Low humidity or low temperature conditions will slow down the cure rate.
3. After curing, 3M™ Scotch-Weld™ Low Odor Instant Adhesive bonds are suitable for use up to about 160°F (71°C).
4. Cyanoacrylate bond resistance to most oils and solvents is excellent. Long term humidity, moisture, or water immersion may affect the strength of a cured cyanoacrylate bond depending on the substrates and the bond gap. Testing is recommended to evaluate the effect.

## **Storage and Shelf Life**

For short term storage (<30 days), store under normal conditions of 16° to 27°C (60° to 80°F) and 40 to 60% relative humidity in the original packaging, out of direct sunlight. Keep containers tightly covered and free of moisture. Refrigeration at 4°C (40°F) gives optimum long term storage stability. When stored under refrigerated conditions, use this product within 15 months from date of manufacture.

## **Precautionary Information**

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577

## **Automotive Disclaimer**

### **Select Automotive Applications:**

This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

## **Information**

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price. Warranty claims must be made within one (1) year from the date of 3M's shipment.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit [www.3M.com](http://www.3M.com).

## **ISO Statement**

This product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M™ Industrial Adhesives and Tapes Division  
3M Center, St. Paul, MN 55144-1000  
[3M.com/iatd](http://3M.com/iatd)

3M and Scotch-Weld are trademarks of 3M Company.  
©3M 2024 (9/24)