



# **Technical Data Sheet**

3M™ Adhesive Transfer Tape 9675

**English-US** Last Revision Date: September, 2024

Supersedes: June, 2024





Product Details

Regulatory Info/SDS

# **Product Description**

Finite Element Analysis (FEA)data is available for this product at: 3m.com/FEA

This 3M<sup>™</sup> Adhesive Transfer Tape with 3M<sup>™</sup> Adhesive 350 is a modified acrylic adhesive ideal for very high-bond strength to many surfaces. It has excellent chemical resistance and bold strength even at elevated temperatures. This tape is offered with a fiber reinforced adhesive which is important for roll stability in narrow widths. Tapes using adhesive 350 are designed for temperature exposure to 450°F (232°C) for short periods of time and up to 300°F (149°C) over long time frames. This adhesive is a good choice for applications which require adhesion to Low Surface Energy plastics, powder coatings and oily metals.

### **General Information**

- Excellent bond to metal and high surface energy plastics.
- Outstanding temperature and chemical resistance.
  Two adhesive thicknesses: 2 mil for thin profile labels and 5 mil for rougher surfaces.
- Available on various liners for specialized processing:
  55# Densified Kraft for rotary die-cutting

- 62# Polycoated Kraft for steel rule die-cutting 83# Polycoated Kraft for lay flat applications
- 78# Extensible Kraft for conformable applications

# **Technical Information Note**

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

# **Typical Physical Properties**

Attribute Name	Value	
Dispenser Selection	For assistance in helping you determine the best dispenser	
	for your application, contact your local 3M sales	
	representative, or the toll free 3M sales assistance number	
	at 1-800-362-3550.	

Attribute Name	Test Method	Value
Adhesive Type		350 Fibered Acrylic
Total Tape Thickness	ASTM D3652	0.127 mm (5 mil)
Liner		83# Polycoated Kraft lay flat
Liner Print		Green, 3M
Liner Thickness		0.16 mm (6.2 mil)
Primary Liner Color		Tan

# Typical Performance Characteristics

# 180° Peel Adhesion

Temperature: 23 °C (73 °F) Dwell Time: 72 h

Test Method: ASTM D3330

Substrate	Value
ABS	9.3 N/cm (85 oz/in) <sup>1</sup>
Acrylic (PMMA)	13.6 N/cm (125 oz/in) <sup>1</sup>
Aluminum	10 N/cm (95 oz/in) <sup>1</sup>
Ероху	13.1 N/cm (120 oz/in) <sup>1</sup>
Glass	15.8 N/cm (145 oz/in) <sup>1</sup>
High Density Polyethylene (HDPE)	3.8 N/cm (35 oz/in) <sup>1</sup>
Low Density Polyethylene (LDPE)	4.4 N/cm (40 oz/in) <sup>1</sup>
Painted Metal	15.8 N/cm (145 oz/in) <sup>1</sup>
Polycarbonate (PC)	15.8 N/cm (145 oz/in) <sup>1</sup>
Polypropylene (PP)	8.7 N/cm (80 oz/in) <sup>1</sup>
Polyvinyl chloride (PVC)	9.8 N/cm (90 oz/in) <sup>1</sup>
Stainless Steel	16.4 N/cm (150 oz/in) <sup>1</sup>

<sup>&</sup>lt;sup>1</sup> 304 mm/min (12 in/min)

# **Static Shear**

Temperature	Test Condition	Value
23 °C (73 °F)	1000 g	10,000 min <sup>1</sup>
70 °C (158 °F)	500 g	10,000 min <sup>1</sup>
93 °C (200 °F)	400 g	10,000 min <sup>1</sup>
121 °C (250 °F)	300 g	10,000 min <sup>1</sup>
149 °C (300 °F)	300 g	10,000 min <sup>1</sup>
177 °C (350 °F)	300 g	10,000 min <sup>1</sup>
232 °C (450 °F)	200 g	10,000 min <sup>1</sup>

 $<sup>^{\, 1} \,</sup>$  25 x 25 mm (1 in x 1 in) sample area, test terminated after 10,000 minutes

Attribute Name	Value
Short Term Temperature Resistance	232 °C (450 °F) ¹
Long Term Temperature Resistance	121 °C (250 °F) <sup>2</sup>
Minimum Long Term Temperature Resistance	-40 °C (-40 °F) <sup>2</sup>

<sup>&</sup>lt;sup>1</sup> Short Term (minutes, hour)

<sup>&</sup>lt;sup>2</sup> Long Term (day, weeks)

# Handling/Application Information

# **Application Examples**

Ideal adhesive application temperature range is 70°F to 100°F (21°C to 38°C). Initial application to surfaces at temperatures below 50°F (10°C) is not recommended for most pressure sensitive adhesives because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is satisfactory. For more specific information, contact our toll free 3M sales assistance number at 1-800-362-3550. 2 mil thick tapes may generally be used for joining materials that are relatively smooth, thin and have low residual

stress. For materials with a rough or textured surface, the thicker adhesive film of the 5 mil tapes would be more appropriate for evaluation.

#### **Application Techniques**

For maximum bond strength the surface should be thoroughly cleaned and dried. Typical cleaning solvents are heptane or isopropyl alcohol. Consult manufacturer's Material Safety Data Sheet for proper handling and storage instructions. Bond strength can also be improved with firm application pressure and moderate heat (for metal surfaces only), from 100°F (38°C) to 130°F (54°C), causing the adhesive to develop intimate contact with the bonding surfaces.

# **Storage and Shelf Life**

Store under normal conditions of 16° to 27°C (60° to 80°F) and 40 to 60% relative humidity in a sealed plastic bag, out of direct sunlight. For best performance, use this product within 24 months from date of manufacture.

#### **Available Sizes**

Attribute Name	Width	Value
Core Size (ID)		76.2 mm (3 in)
Maximum Available Width		48 in
Maximum Length	1/8 in to 3/8 in width	54.9 m (60 yd)
Maximum Length	3/8 in to 1/2 in width	165 m (180 yd)
Maximum Length	1/2 in to 1 in widths	329 m (360 yd)
Maximum Length	1 in to maximum	329 m (360 yd)
Normal Slitting Tolerance		± 0.8 mm (± 1/32 in)
Note		Subject to Minimum Order
		Requirements
Standard Roll Length		60 yd

### **Recognition/Certification**

MSDS:3M has not prepared a MSDS for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, these products should not present a health and safety hazard. However, use or processing of these products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards.

TSCA: These products are defined as articles under the Toxic Substances Control Act and therefore, are exempt from inventory listing requirements.

UL:Tapes 9442 and 9445 have been recognized by Underwriters Laboratories Inc. under Standard UL 969 Marking and Labeling in File MH26206. Tapes 9482PC and 9485PC have been recognized by Underwriters Laboratories Inc. under Standard UL

746C Polymeric Adhesives Systems, Electrical Equipment Component in File MH17478. If you require official recognition of any 350 adhesive under either UL 969 or UL 746C, please contact 3M-customer service at 1-800-362-3550. For more information on the UL Certification, please visit the website at http://www.3m.com/converter, select UL Recognized Materials, and then select the specific product area.

# **Automotive Disclaimer**

### **Select Automotive Applications:**

Select Automotive Applications:

This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

### Information

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price. Warranty claims must be made within one (1) year from the date of 3M's shipment.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

### **ISO Statement**

This product was manufactured under a 3M quality system registered to ISO 9001 standards.

#### For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit www.3M.com/converter.

3M™ Industrial Adhesives and Tapes Division 3M Center, St. Paul, MN 55144-1000 3M.com/iatd

©3M 2024 (9/24)