



Technical Data Sheet

3M™ VHB™ Architectural Panel Tape G90F



Product Details



Regulatory Info/SDS

Product Description

Finite Element Analysis (FEA) data is available for this product at: 3m.com/FEA

3M™ VHB™ Architectural Panel Tapes are durable, high performance double-sided pressure sensitive acrylic foam tapes. These tapes have been used for many applications in the construction industry, including the manufacture of architectural panels for curtain walls, exterior building cladding and interior panel and trim attachment. In many situations, 3M™ VHB™ Architectural Panel Tapes can replace rivets, spot welds, liquid adhesives, sealants and other permanent fasteners and provide immediate handling strength during the fabrication process.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Attribute Name	Test Method	Value
Adhesive Type		Multi-purpose
Adhesive Carrier		Acrylic Foam (closed cell)
Total Tape Thickness	ASTM D3652	2.3 mm (90 mil)
Density	ASTM D3574	720 kg/m ³ (45 lb/ft ³) ¹
Liner		Film
Color		Gray
Primary Liner Color		Red (printed)

¹ Foam with adhesive

Typical Performance Characteristics

Temperature: 22 °C (72 °F)

Attribute Name	Test Method	Substrate	Value
90° Peel Adhesion	ASTM D3330	Anodized Aluminum	52.5 N/cm (30 lb/in) ¹
Overlap Shear Strength	ASTM D1002	Anodized Aluminum	450 kPa (65 lb/in ²)
Normal Tensile	ASTM D897	Aluminum T-block	480 kPa (70 lb/in ²)

¹ 12 in/min (300 mm/min)

Static Shear

Test Method: ASTM D3654

Temperature	Value
22 °C (72 °F)	1000 g/3.2cm ² (2.2 lb/0.5 in ²) ¹
66 °C (150 °F)	500 g/3.2cm ² (1.1 lb/0.5 in ²) ¹
93 °C (200 °F)	500 g/3.2cm ² (1.1 lb/0.5 in ²) ¹

¹ Holds 10,000 min.

Attribute Name	Value
Minimum Application Temperature	15 °C (60 °F)
Short Term Temperature Resistance	121 °C (250 °F) ¹

Attribute Name	Value
Long Term Temperature Resistance	93 °C (200 °F) ²

¹ No change in room temperature dynamic shear properties following 4 hour conditioning at indicated temperature with 100 g/static load. (Represents minutes, hour in a process type temperature exposure).

² Maximum temperature where tape supports at least 250 g load per 0.5 in² in static shear for 10,000 minutes. (Represents continuous exposure for day or weeks).

Application Guidelines

Application Examples:

Typical applications include stiffener bonding, architectural panel bonding in cladding or curtain wall systems, interior panel bonding, break-metal bonding and decorative trim bonding. These tapes are not to be used for structural glazing applications.

Application Testing:

Typical applications include stiffener bonding, architectural panel bonding in cladding or curtain wall systems, interior panel bonding, break-metal bonding and decorative trim bonding. These tapes are not to be used for structural glazing applications.

Fabrication Guidelines:

A shop work environment is appropriate for bonding applications with 3M™ VHB™ Architectural Panel Tape. Tape application temperature should be at least 60°F (15°C). Field bonding may be considered if the exterior temperature meets this guideline. It is also important to provide adequate pressure to the tape after it has been applied to the first prepared substrate surface and after the two parts are joined together. A pressure of 15 lb/in² (100 kPa) or greater should be applied over the whole tape area to facilitate good contact of the adhesive to both substrates. Rigid surfaces may require 2 or 3 times more pressure to achieve >15 lb/in² (100 kPa) at the tape bond line. 3M channel partners are available to provide training of operators for 3M™ VHB™ Architectural Panel Tape bonding applications.

Design Considerations

Note: For tape area calculations the following guidelines can be used.

Dynamic Loads:

For dynamic tensile or shear loads, such as wind loads, a design strength of 12 lb/in² (85 kPa) is used for 3M™ VHB™ Architectural Panel Tapes. This design strength guideline provides a safety factor of at least 5 and was established based on material property testing as well as ASTM dynamic load testing for curtain wall applications.

Static Loads:

For static tensile or shear loads, such as dead weight loads with no mechanical support, snow loads and other long-term loads, a design strength of 0.25 lb/in² (1.7 kPa) is used for 3M™ VHB™ Architectural Panel Tapes. This means 4 in² of tape per 1 lb load (60 cm² of tape per 1 kg load) should be used to support constant stress loads. This guideline provides a safety factor of at least 5.

Differential Movement:

3M™ VHB™ Architectural Panel Tapes can tolerate shear movement up to 3 times its original thickness (300% shear strain). This means 0.090 in (2.3 mm) thick tapes can tolerate shear strain up to 0.27 in (6.9 mm), 0.062 in (1.6 mm) thick tapes can tolerate shear strain up to 0.19 in (4.8 mm), and 0.045 in (1.1 mm) thick tapes can tolerate shear strain up to 0.14 in (3.3 mm).

Force/Stress Types:

In general, when designing with 3M™ VHB™ Architectural Panel Tapes, forces acting on the tape should consist of either shear or tensile type stress loads. This allows the stress or force to be applied over the entire tape area. Applications placing cleavage or peel type stress on the tape should be avoided as this will place the stress on the leading edge of the peel or cleaving.

Storage and Shelf Life

3M™ VHB™ Architectural Panel Tapes have a shelf life of 24 months from date of manufacture when stored at 40°F to 100°F (4°C to 38°C) and 0-95% relative humidity. The optimum storage conditions are 72°F (22°C) and 50% relative humidity.

Available Sizes

Attribute Name	Value
Core Size (ID)	76.2 mm (3 in)
Normal Slitting Tolerance	± 0.8 mm (± 1/32 in)
Standard Roll Length	32.9 m (36 yd)
Standard Width	15, 20, 25, 30 mm (1/2, 5/8, 3/4, 7/8, 1, 1-1/8, 1-1/4 in)

Automotive Disclaimer

Select Automotive Applications: This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: 3M warrants for 24 months from the date of 3M manufacture that 3M™ VHB™ Tape will be free of defects in material and manufacture. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. This warranty does not cover damage resulting from the use or inability to use 3M™ VHB™ Tape due to misuse, workmanship in application, or application or storage not in accordance with 3M recommended procedures (except to the extent 3M approves and issues a specific application warranty, for which the customer must apply, receive 3M approval, and meet all applicable warranty and process requirements, the additional details, terms, and conditions of which are available from 3M). If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M
Industrial Adhesives and Tapes Division
3M Center, Building 225-35-06
St. Paul, MN 55144-1000
800-362-3550

3M and VHB are trademarks of 3M.
©3M 2022 (5/22)