



Technical Data Sheet

3M™ Thermal Transfer Polyimide Label Material 7812



[Product Details](#)



[Regulatory Info/SDS](#)

Product Description

3M™ Thermal Transfer Polyimide Label Material 7812 is a polyimide film product that offers ultra-high temperature performance. This label product utilizes 3M™ Adhesive 100, that can withstand up to 450°F (232°C) short-term heat resistance, has solvent resistance, and exhibits low outgassing characteristics.

Product Features

- Matte white thermal transfer topcoat for easy readability of barcodes and variable information.
- Adhesive will not degrade when exposed to a wide variety of harsh processing conditions. This adhesive also offers shear strength even at elevated temperatures.
- 50# densified kraft liner assures consistent die cutting.
- UL Recognized file MH16411

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Attribute Name	Value
Adhesive Type	100 Acrylic
Facestock	Polyimide Film and Matte White Kraft Thermal Transfer Printable Topcoat
Die-Cutting	Rotary die-cutting is recommended.

Attribute Name	Value
Adhesive Thickness	0.051 mm (2 mil)
Facestock Thickness	Polyimide Film: 0.051 Matte White Kraft Thermal Transfer Printable Topcoat: 0.025 mm (Polyimide Film: 2.0 Matte White Kraft Thermal Transfer Printable Topcoat: 1.1 mil)
Liner	50# Densified Kraft
Liner Thickness	0.076 mm (3.2 mil)

Attribute Name	Value
----------------	-------

Attribute Name	Value
Convertability	The shear strength of 3M™ Acrylic Adhesive 100 is the choice for high temperature applications such as printed circuit boards. Specifically designed to be compatible with thermal transfer technologies. Adhesive processing issues are not anticipated when proper roll tensions, handling and storage conditions are used. Please refer to the die cutting section of this data page or the “Guide to Converting and Handling Label Products” technical bulletin for additional information.

Typical Performance Characteristics

180° Peel Adhesion

Temperature: 23 °C (73 °F)

Dwell Time: 72 h

Test Method: ASTM D3330

Substrate	Value
Epoxy PC Board	6.8 N/cm (62 oz/in) ¹
Polycarbonate (PC)	6.3 N/cm (58 oz/in) ¹
Stainless Steel	5.8 N/cm (53 oz/in) ¹

¹ 304 mm/min (12 in/min)

Attribute Name	Value
Note	Calipers are nominal values

Typical Environmental Characteristics

Humidity Resistance

24 hours at 100°F (38°C) and 100% relative humidity: no significant change in appearance or adhesion

Temperature Resistance

530°F (277°C) for 30 seconds: no significant visual change

500°F (260°C) for 7 minutes: slight browning

-40°F (-40°C) for 24 hours: no significant visual change

Printing

Facestock is topcoated and is designed for thermal transfer printing.

- Recommended Ribbons
Ricoh; D110A
Union Chemicar; US300

The following ribbons can be used but may require higher burn temperatures:

- Sony; 5070
- Mid City Columbia; CGL-80HE Dai
- Nippon; R510

Printed Label Performance:

Samples were printed with a Ricoh D110A resin ribbon on Zebra 170xi printer at a rate of 2 in./min. and a burn setting of 22. Labels were printed with a 3:1 ratio barcode with 6 mil X-dimension. Printed labels were exposed to the listed conditions, which are representative of PCB assembly conditions. After chemical exposure, labels were rinsed with tap water, dried and examined.

Condition Printed Contrast Signal (PCS) Read Rate

3M™ Label Material 7812 Control 97 100

530°F, 30 sec. 97 100

500°F, 7 min. 94 100

IPA 75%, 106°F, 15 min. 97 100
 IPA 100%, RT 2 min. 97 100
 Deionized Water, 140°F, 5 min. 97 100
 Alconox® 10%, 135°F, 2 min. 97 100
 D-Limonene RT, 2 min. 97 100
 Monoethanolamine, 135°F, 2 min. 97 100
 BIOACT® EC-7R, 77°F, 10 min. 92 100
 BIOACT® EC-15, 77°F, 10 min. 92 100
 Wave Solder 95 100

The Print Contrast Signal, PCS, was determined using a PSC QUICKCHECK™ 850, with a 0.003" aperture, 660 nm wavelength. The read rate was determined using a PSC laser diode scanner, model 4100. Wave soldering was performed on an Electrovert Co., Microline 250 wave solder machine. Preheat temperature was 250°F (121°C), solder temperature was 470°F (243°C), line speed was 2 ft./min. Boards were pre-sprayed with a Kester Solder Co. 923 flux.

Handling/Application Information

Application Examples

- Printed circuit board tracking labels that see the following conditions:
 - Solder reflow;
 - Top and/or bottom side wave solder;
 - Most cleaning processes and chemicals.
- Labeling on parts exposed to high temperatures.

Application Techniques

For maximum bond strength, the surface should be clean and dry. Typical cleaning solvents are heptane and isopropyl alcohol.*

For best bonding conditions, application surface should be at room temperature or higher. Low temperature surfaces, below 50°F (10°C), can cause the adhesive to become so firm that it will not develop maximum contact with the substrate. Higher initial bonds can be achieved through increased rubdown pressure.

- When using solvents, read and follow the manufacturer's precautions and directions for use.

Industry Specifications

UL Recognized, File PGJ12.MH16411, Printing Materials - Component, ANSI/UL 969

Storage and Shelf Life

Store under normal conditions of 16° to 27°C (60° to 80°F) and 40 to 60% relative humidity in the original packaging, out of direct sunlight. For best performance, use this product within 24 months from date of manufacture.

Available Sizes

Attribute Name	Value
Packaging	Finished labels should be stored in plastic bags.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or

packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

ISO Statement

This product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M™ Industrial Adhesives and Tapes Division
3M Center, St. Paul, MN 55144-1000
3M.com/iatd

3M is a trademark of 3M Company.
BIOACT is a registered trademark of MicroCare.
PSC QUICKCHECK is a trademark of PSC.
Alconox is a registered trademark of Alconox, Inc.
409 is a registered trademark of Clorox.
©3M 2024 (9/24)