



Technical Data Sheet

3M™ Polyester Tape 8992

Product Description

3M™ Polyester Tape 8992 is a dark green polyester tape with silicone adhesive. It can be used in a large variety of high temperature applications including powdercoat masking, flashbreaker, and bag sealing applications. Additional applications include, splicing, tabbing, or roll closing silicone treated liners or materials.

Product Features

- Polyester films offer excellent thermal, abrasion, and chemical resistance while maintaining their flexibility.
- Green color makes tape placement obvious for both application and removal.
- Backing leaves a sharp paint line.
- Silicone adhesives offer high heat resistance compared to many rubber and acrylic adhesives, reducing failure due to softening, oozing, and adhesive transfer.
- Silicone adhesives adhere well to tough-to-stick-to surfaces like silicone liners and fixtures coated with mold release.
- Silicone adhesive removes cleanly from many surfaces.
- Lined version available for die-cuts.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

| Attribute Name | Test Method | Value |
|----------------------|-------------|-----------|
| Color | | Green |
| Adhesive Type | | Silicone |
| Backing | | Polyester |
| Backing Thickness | ASTM D3652 | 0.052 mm |
| Total Tape Thickness | ASTM D3652 | 0.082 mm |
| Liner | | Polyester |
| Liner Thickness | | 0.075 mm |

Typical Performance Characteristics

| Attribute Name | Test Method | Temperature | Value |
|---------------------|-------------|-------------|-----------------------|
| 180° Peel Adhesion | ASTM D3330 | 22 °C | 4.8 N/cm ¹ |
| Elongation at Break | ASTM D3759 | | 148 % |
| Tensile Strength | ASTM D3759 | | 99.8 N/cm |

¹ 12 in/min (300 mm/min)

Handling/Application Information

Application Examples

- Masking for powdercoat painting.
- Flashbreaker tape when pulling through cured coating such as epoxies.
- Holding and splicing difficult to stick to surfaces such as silicone liner.
- Holding parts or sealing vacuum bags during processing.

Storage and Shelf Life

Store under normal conditions of 16° to 27°C (60° to 80°F) and 40 to 60% relative humidity in the original packaging, out of direct sunlight. For best performance, use this product within 24 months from date of manufacture.

Available Sizes

| Attribute Name | Value |
|----------------------|--------|
| Standard Roll Length | 65.8 m |

Information

Precautionary Information: Refer to product label and Material Safety Data Sheet for health and safety information before using the product. For information, please contact your local 3M Office. You can click or scan QR code to see contact detail or visit www.3M.com Important Information: All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law. Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.

ISO Statement

This product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M™ Centre
Cain Rd, Binfield, Bracknell RG12 8HT, United Kingdom
3m.co.uk/iatd

3M is a trademark of 3M Company.
©3M 2024 (9/24)