



REACH
1907/2007/EC

Scotchcast™

Electrical Insulating Resin 470

Product Description

3M™ Scotchcast™ Resin 470 is a non filled, two component polyurethane resin for room temperature curing. The resin has been designed for electrical insulation and mechanical protection of electrical cables joints.

Once the hardening is complete, the resin provides impact resistance and durability against moisture and atmospheric corrosion.

Application

Mechanical protection and electrical insulation of low voltage electrical joints installed for indoor and outdoor, underground and submerged applications.

Features

Excellent hydrolytic stability

Available with Closed Mix and Pour Delivery System

Low exothermic reaction temperature.

Process Figures

Mixing Ratio (pbw)	A : B	100 : 50
Pot Life	At 5 °C	47 min
	At 23 °C	20 min
	At 40 °C	9 min

Typical Properties

Note: This data is not to be used for specifications.

Values listed are typical and should not be considered minimum or maximum.

Property	Value	Specification
Part A		
Density	1,01 g/cm ³	ISO 3675
Viscosity 23°C	1600 mPas	EN ISO 2555
Property	Value	Specification
Part B		
Density	1,22g/cm ³	ISO 3675
Viscosity 23°C	135 mPas	EN ISO 2555
Part A&B (mixed)		
Density	1,15 g/cm ³	ISO 3675
Viscosity 5°C	4400 mPas	EN ISO 2555
Viscosity 23°C	900 mPas	EN ISO 2555
Exothermic Reaction Temp 40°C	90 °C	HD 631.1 S2
Hydrophobic Behaviour	Passed	HD 631.1 S2
Volume Shrinkage	3,9 %	EN ISO 3521
Part A&B (cured*)		
<i>Mechanical properties</i>		
Hardness Shore D	59	EN ISO 868
Tensile Strength	13 MPa	EN ISO 527
Elongation at Break	90 %	EN ISO 527
Impact Strength (without notch)	No breakdown	EN ISO 179
<i>Electrical properties</i>		
Volume resistivity		IEC 60250
at 23 °C	2,0E+14 Ωcm	
at 80 °C	7,0E+10 Ωcm	
Dielectric Strength		EN 60243-1
at 23 °C	20 kV/mm	
Dissipation factor		IEC 60250
at 23 °C	0,02	
at 80 °C	0,04	
Dielectric constant		IEC 60250
at 23 °C	<6	
at 80 °C	9,5	

*curing and aging cycles according to Cenelec HD631.1 S2

Usage Information:

The resin will be supplied, in two-chamber plastic pouches with peelable barrier in the correct stoichiometric proportion. This type of packaging will assure the correct mixing ratio for applying the resin.

The packaging includes a Closed Mix and Pour Delivery System. The integrated pouring spout will be opened while attaching the mixed resin bag to the housing of the joint or by using the supplied opener.

For other information, relevant for the usage of the resin, like Gel-Time, Pot-Life, viscosity, density etc. please see above the typical properties.

Storage:

3M™ Scotchcast™ Resin 470 has a shelf life of 36 months when stored between 10°C and 40°C with a humidity level < 75 % in the originally sealed bag.

The expiration date of each product appears on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, it is the responsibility of the user to determine applicability of the resin.

Safety and Handling:

3M provides its customers with a product specific Material Safety Data Sheet (MSDS) to cover potential health effects, safe handling, storage, use and disposal information. 3M strongly encourages its customers to review the MSDS on its products prior to their use.

Product Stewardship:

3M has a fundamental concern for all who make, distribute and use its products, and for the environment in which we live. This concern is the basis of our philosophy and policies by which we assess the health and environmental information on our products and then take the appropriate steps to protect employee, the public health and the environment.

Customer Notice:

3M encourages its customers and potential users of 3M products to review their applications for such products from the standpoint of human health and environmental quality. To help ensure that 3M products are not used in ways for which they were not intended or tested. 3M personnel are available to assist customers in dealing with ecological and product safety considerations. Your 3M sales representative can arrange for the proper contacts.

Regulatory Status:

The 470 Resin is in compliance with all European directives and regulations, relevant for this product.

The 470 Resin is in compliance with EU regulation 1907/2007/EC (REACH).

3M and Scotchcast are trademarks of 3M Company.

Important Notice

All statements, technical information and recommendations related to the Seller's products are based on information believed to be reliable, but the accuracy or completeness thereof is not guaranteed. Before utilizing the product, the user should determine the suitability of the product for its intended use. The user assumes all risks and liability whatsoever in connection with such use.

Any statements or recommendations of the Seller which are not contained in the Seller's current publications shall have no force or effect unless contained in an agreement signed by an authorized office of the Seller.

The statements contained herein are made in lieu of all warranties, expressed or implied, including but not limited to the implied warranties of merchantability and fitness for a particular purpose which warranties are hereby expressly disclaimed.

SELLER SHALL NOT BE LIABLE TO THE USER OR ANY OTHER PERSON UNDER ANY LEGAL THEORY; INCLUDING BUT NOT LIMITED TO NEGLIGENCE OR STRICT LIABILITY; FOR ANY INJURY OR FOR ANY DIRECT; INDIRECT; INCIDENTAL OR CONSEQUENTIAL DAMAGES SUSTAINED OR INCURRED BY REASON OF THE USE OF ANY OF THE SELLER'S PRODUCTS.