

# 3M™ Dyneon™ PTFE Micropowder J24

## Features and Benefits

- Low molecular weight PTFE powder
- Non-friable, stable particle
- Relatively low specific surface area compared to other PTFE micropowders
- Little or no viscosity effect on matrix material
- Broad chemical resistance and temperature range of use

Used as an additive to:

- Reduce coefficient of friction or impart low surface energy

**Note:** Data in this document are not for specification purposes.

## Typical Properties

Property	Test Method	
Average Particle Size	Laser Diffraction	20 µm
Hegman Particle Size	Grind Gauge	15 µm
Minimum Bulk Density	ASTM D4895	400 g/l

## Processing Recommendations

3M™ Dyneon™ PTFE Micropowders can be used as additives in many applications and at concentrations typically from 5 to 20%. Homogeneous incorporation is the single most important process and application consideration. Due to poor flow properties of the micropowder it is recommended that the micropowder and matrix material both be at a temperature below 30°C (86°F). However, in the case of thermoplastic blends, the micropowder may be incorporated into the melt. Dyneon PTFE Micropowder J24 can be dispersed using a variety of mixing equipment. Depending upon the application, high speed mixers and tumble blenders have been successful for dry blends, while propeller mixers work well for wet mixtures such as solvents and oils. Glass bead mills should be used for relatively high viscosity mixtures and roll mills for very high viscosity applications, such as lubricating greases and oils.

## Supply Form

PTFE Micropowder J24 is supplied in 200 lb. drums with a polyethylene liner.

## Storage

PTFE Micropowder J24 has a 3 year shelf life. It should be kept in a clean and dry place in its original unopened container at temperatures below 30°C (86°F).

**Warranty, Limited Remedy, and Disclaimer:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. Unless a different warranty is specifically stated in the applicable product literature or packaging insert, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except where prohibited by law, 3M will not be liable for any loss or damages arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

**Technical Information:** Technical information, recommendations, and other statements contained in this document or provided by 3M personnel are based on tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

