



# 16 Crepe Paper Tape

## With Thermosetting Rubber Pressure-Sensitive Adhesive Data Sheet

### Applications

Conformable; for use as coil cover and end-turn taping.

<b>Properties</b>	<b>Typical Values</b>
Adhesive	Thermosetting Rubber
Operating Temperature	105°C/221°F
Total Thickness	9.0 mil/.228 mm
Dielectric Breakdown	2500 volts
Insulation Resistance	>1 x 10 <sup>6</sup> megohms
Breaking Strength	25 lbs./in (44 N/mm)
Elongation at Break	10%
Adhesion to Steel	50 oz/in (5.5 N/mm)

Technical information provided consists of typical product data and should not be used for specification purposes. Unless otherwise noted, all tests are performed at room temperature.

3M is a trademark of 3M.

#### Important Notice

All statements, technical information and recommendations related to the Seller's products are based on information believed to be reliable, but the accuracy or completeness thereof is not guaranteed. Before utilizing the product, the user should determine the suitability of the product for its intended use. The user assumes all risks and liability whatsoever in connection with such use.

Any statements or recommendations of the Seller which are not contained in the Seller's current publications shall have no force or effect unless contained in an agreement signed by an authorized officer of the Seller. The statements contained herein are made in lieu of all warranties, expressed or implied, including

but not limited to the implied warranties of merchantability and fitness for a particular purpose which warranties are hereby expressly disclaimed.

SELLER SHALL NOT BE LIABLE TO THE USER OR ANY OTHER PERSON UNDER ANY LEGAL THEORY, INCLUDING BUT NOT LIMITED TO NEGLIGENCE OR STRICT LIABILITY, FOR ANY INJURY OR FOR ANY DIRECT, INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES SUSTAINED OR INCURRED BY REASON OF THE USE OF ANY OF THE SELLER'S PRODUCTS THAT WERE DEFECTIVE.



#### Electrical Products Division

6801 River Place Blvd.  
Austin, TX 78726-9000  
800 676 8381  
<http://www.3m.com/elpd>

© 3M 1998  
78-8124-4752-8(A)