

3M™ Scotchkote™ Fusion-Bonded Epoxy Coating 6233

Data Sheet

Product Description

3M™ Scotchkote™ Fusion-Bonded Epoxy Coating 6233 is a one-part, heat curable, thermosetting epoxy coating powder designed for corrosion protection of pipe.

Properties

| Property | Value |
|---------------------------|--|
| Specific Gravity Powder | 1.44 |
| Coverage based on film | 141 ft ² /lb/mil (0.735 m ² /kg/mm) |
| Color | Govt. Color 14272/Green |
| 6233-4G | |
| Gel Time @ 400°F (205°C) | 9.5 seconds ± 20% |
| Cure Time @ 450°F (232°C) | 30 seconds |
| 6233-8G | |
| Gel Time @ 400°F (205°C) | 17 seconds ± 20% |
| Cure Time @ 450°F (232°C) | 90 seconds |
| 6233-11G | |
| Gel Time @ 400°F (205°C) | 25 seconds ± 20% |
| Cure Time @ 450°F (232°C) | 110 seconds |
| Shelf life @ 80°F (27°C) | 12 months |

Temperature Operating Range

The Scotchkote coating 6233, when properly applied, should perform in a satisfactory manner on pipelines operating between -100°F/-73°C to 230°F/110°C. For temperatures between +170°F/77°C to 230°F/110°C, laboratory tests indicate that the thicker coatings may improve the service capability. However, it is difficult to accurately predict field performance from the laboratory data due to the wide variation in actual field conditions. Soil types, moisture content, temperatures, coating thickness and other factors specific to the area all influence the coating performance and the upper temperature operating limit.

Scotchkote coating 6233 meets the requirements of AWWA C213 and C550.

3M™ Scotchkote™ Fusion-Bonded Epoxy Coating 6233 Test Data

| Property | Test Description | Typical Value |
|----------------------------|--|--|
| Impact | ASTM G14 (modified) | |
| | 1/8 in (3.2 mm) thick plate 3/8 in (9.5 mm) thick plate | 160 in•lbs (18.1 J) 59 in•lbs (6.7 J) |
| Cathodic Disbondment | CAN/CSA-Z245.20-12.8 | |
| | 48 hours, 1.5 volt, 3% NaCl 149°F/65°C | 2.3 mmr |
| | 28 day, 1.5 volt, 3% NaCl 73°F/23°C | 2.5 mmr |
| | 28 day, 1.5 volt, 3% NaCl 149°F/65°C | 4.9 mmr |
| Hot Water Resistance | 24 hours, CAN/CSA-Z245.20-12.14, 203°F/95°C | 1 rating |
| | 48 hours, CAN/CSA-Z245.20-12.14, 167°F/75°C | 1 rating |
| Bendability (Mandrel Bend) | <u>Temperature</u> | <u>°/PD</u> |
| | 73°F/23°C | 10.5 |
| | -22°F/-30°C | 19.1 |
| | | <u>% Elongation</u> |
| | | 5.5 |
| | | 3.0 |
| Compressive Strength | ASTM D 695 | 10,000 psi (705 kg/cm ²) |
| Penetration | ASTM G 17 -40° to 200°F/-40° to 93°C | 0 |
| Thermal Shock | -320° to 310°F/-195° to 154°C | No visible effects |
| | Coated pipe | 10 Cycles |
| Dielectric Strength | 1180 V/mil/46 kV/mm | |

Note: The typical values in this data sheet are based on lab prepared samples. Values shown are not to be interpreted as product specifications.



Handling and Safety Precautions

Read all Health Hazard, Precautionary and First Aid, Material Safety Data Sheet, and/or product label prior to handling or use.

Ordering Information/Customer Service

For ordering technical or product information, or a copy of the Material Safety Data Sheet, call:
Phone: 800/722-6721
Fax: 877/601-1305

3M and Scotchkote are trademarks of 3M Company.

Important Notice

All statements, technical information and recommendations related to 3M Products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using the 3M Product, you must evaluate it and determine if it is suitable for your intended application. Because conditions of Product use are outside of our control and vary widely you assume all risks and liability associated with such use. Any Product-related statements not contained in current 3M publications, or any contrary statements contained in your purchase order, shall have no force or effect unless expressly agreed to in writing by an authorized officer of 3M.

Warranty; Limited Remedy; Limited Liability.

3M warrants that Product will conform to 3M published specifications upon shipment. If Product is proven not to have met the specifications your exclusive remedy and 3M's sole obligation will be, at 3M's option, to replace the Product or to refund the purchase price of the Product. **EXCEPT WHERE PROHIBITED BY LAW, THIS WARRANTY IS MADE IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR THOSE ARISING FROM A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE.** Buyer is an expert in its field and is responsible for determining if Products are suitable for a particular purpose or application. 3M has no obligation under this warranty with respect to any Product that has failed due to inadequate or improper storage, handling, surface preparation, application, or maintenance; failure to follow Product instructions; or alteration or damage to the Product caused by accident, neglect, or misuse. **EXCEPT WHERE PROHIBITED BY LAW, IN NO EVENT SHALL 3M BE LIABLE FOR ANY DIRECT, INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL LOSS OR DAMAGES (INCLUDING LOST PROFITS) ARISING FROM THIS PRODUCT, REGARDLESS OF THE LEGAL THEORY ASSERTED.**



Infrastructure Protection Division

6801 River Place Blvd.
Austin, TX 78726-9000
www.3M.com/corrosion

Please recycle. Printed in USA.
© 3M 2013. All rights reserved.
80-6111-8339-5-K