



Adhesion Promoter N200NT

Technical Data Sheet

May 2008

General Description 3M™ Adhesion Promoter N200NT is a liquid primer used to improve the adhesion of 3M™ Acrylic Foam and Acrylic *Plus* Tapes to Polyvinyl Chloride (PVC), Polyurethane (PU) and SUS. Since formulations and surface energies vary for these materials, each application should be verified through testing. 3M Adhesion Promoter N200NT is specifically formulated to be used with 3M Acrylic Foam and Acrylic *Plus* Tapes for automotive applications. 3M Adhesion Promoter N200NT has also been formulated to significantly reduce the hazardous air pollutant (HAPS) content as compared to 3M™ Adhesion Promoter N200J.

Shelf Life Shelf life is one year from the date of shipment when stored in the original container at 4°C – 38°C (40°F – 100°F), 0-95% relative humidity, and away from light sources. Storage at lower temperatures for short periods will not affect product performance if the primer is warmed to recommended temperatures before application.

Physical Properties	Color	Straw
	Solid Material	Synthetic resin
	Solvent Material	Methylcyclohexane and N-Butyl Acetate
	Solid %	Approximately 4.5%
	HAPS	1% by weight

Equipment 3M Adhesion Promoter N200NT can be applied by a gravity feed wipe, knurled roller, sprayer and felt-tipped applicator or other similar applicator types. Applicator heads should be cleaned or replaced regularly. A convenient application system is available through your 3M Automotive Division representative.

Surface Preparation The bonding surface should be clean and dry. Contaminated surfaces should be cleaned with an untreated, lint-free cloth and an appropriate solvent (typically isopropyl alcohol).*

Application Shake well before using. Apply a thin, uniform coating to the bonding surface, using the minimum amount that will fully coat the surface. A wet coating thickness of 0.002 inch or less ensures a good application. In general, the drying time under standard conditions (23°C and 65% relative humidity) is 30 seconds to 24 hours. Drying time varies depending on the ambient temperature and humidity, as well as the coating thickness. Recommended drying time is 10 minutes to 3 hours under standard conditions. Be sure the primed surface remains free from contaminants prior to laminating the tape. If drying time is more than 24 hours, re-apply the adhesion promoter.

Clean-Up 3M Adhesion Promoter N200NT can be removed with acetone solvent.* Vigorous scrubbing may be required.

***Note:** When using solvents, extinguish all ignition sources and follow the manufacturer's precautions and directions for use.

Technical Data Sheet

3M™ Adhesion Promoter N200NT

Page 2

Safety and Regulatory

IMDS ID# 84678637. This is a published material entry on www.mdssystem.com.

Observe proper handling precautions as outlined in the Material Safety Data Sheet (MSDS), which is available on request. The website address for 3M MSDSs is www.3M.com/msds.

3M is a Trademark of 3M Company.

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

3M

Automotive Division

3M Center, Building 223-1S-02
St. Paul, MN 55144-1000
www.3M.com/autosolutions

© 3M 2008
75-3470-8872-8
Printed in the U.S.A.

Country of Origin: Japan