

For optimum surface smoothness and gloss

40 sec.
Working time.

0:40 – 1:40 min.
Setting time in the mouth.

1:40 min. **Earliest** point of removal from the mouth

1:40 – 2:50 min.
Matrix removal from mouth.

2:50 min. **Latest** point of removal from the mouth

2:50 – 5:00 min.
Final setting.

5:00 min. **Earliest** point of removal from the matrix

From 5:00 min.
Remove oxygen inhibition layer.
Trim margins.
Final finishing.

For faster results

40 sec.
Working time.


0:40 – 1:40 min.
Setting time in the mouth.

1:40 min. **Earliest** point of removal from the mouth and matrix

From 1:40 min.
Remove from mouth and matrix.
Trim margins.
2:50 min.

Latest point of removal from mouth.

From 5:00 min.
Remove oxygen inhibition layer.
Final finishing.



3M ESPE

Dental Products
3M Center
Building 275-2SE-03
St. Paul, MN 55144-1000
U.S.A.
1-800-634-2249

3M, ESPE and Protemp are
trademarks of 3M or 3M ESPE AG.
©3M 2010. All rights reserved.
44000757904/03