April 2012

# 3M<sup>™</sup> Wind Threadlocker W1235 Medium Strength

### Description

3M<sup>™</sup> Wind Threadlocker W1235 is a one-component anaerobic adhesive that cures and seals threaded assemblies in a wide range of applications to prevent loosening and leakage. This product provides excellent vibration, corrosion, and shock resistance.

### Features

Note: The following information and data should be considered representative or typical only, and should not be used for specification purposes. 3M Wind Threadlocker W1235 is a general purpose, medium strength threadlocker for most medium- and coarse-threaded screws, nuts, and bolts and can be removed with hand tools. It is oil tolerant to help secure as-received parts and its thixotropic property prevents run-off, dripping, or migration of the adhesive when applied to threads.

- Corrosion prevention
- Shock and vibration resistance
- Fast set time

# **Typical Uncured Physical Properties**

Properties	Value	
Chemistry	Dimethacrylate	
Color	Blue	
Appearance	Liquid	
Viscosity	3,000 cP	
Set Time	≤20 minutes	
Full Cure Time	24 hours	

Note: Viscosity measured using a Brookfield RVT Viscometer with a #3 spindle at 20 rpm and 25°C.

# **Typical Cured Physical Properties**

Properties	Value	
Color	Blue	
Strength	Medium	
Fastener Size Range	1/2-1 inch	12–25 mm
Breakaway Torque	110-220 in•lb	12.4-24.9 N·m
Prevail Torque	40-130 in•lb	4.5-14.7 N·m
Temperature Range	-65-300°F	-54-149°C

Note: Breakaway and prevail torque values measured using ISO 10964 test method "Adhesives – Determination of Torque Strength of Anaerobic Adhesives on Threaded Fasteners."

### **Directions for Use**

3M Wind Threadlocker W1235 is not recommended for use on most plastics due to potential cracking of plastic parts.

#### For Assembly:

- 1. Ensure parts are clean, dry, and free from oil, grease, and dirt. For best results, clean and dry parts with solvent.
- 2. Shake the adhesive bottle well before use.
- **3.** Avoid touching the metal surfaces with the bottle tip since the metal ions may react with the adhesive upon contact and eventually may clog the bottle tip.
- 4. Apply adhesive into the threaded part where contact will occur during the final assembly. For larger parts, use more adhesive and rotate the threaded part to spread adhesive evenly around the contact area.
- **5.** For through holes, apply several drops of adhesive onto the bolt at the nut engagement area. For blind holes, apply several drops of the adhesive down the internal threads to the bottom of the hole.
- 6. Assemble the nut/fastener and tighten as required.
- **7.** Keep threaded assemblies undisturbed until the set time is reached, before further processing or testing.

#### For Disassembly:

- 1. Loosen or remove with regular hand tools.
- If hand tools do not work due to the assembled parts being well tightened, apply localized heat (approximately 490°F (254°C)) to the nut or bolt and disassemble while parts are still hot.
- Notes: 1. When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use. Use solvents in accordance with local regulations.
  - 2. Use extreme caution when working with heat sources (heat guns, flames, etc.).



### Material Surface Activity and Cure Speed

Anaerobic adhesives rely on the presence of active metal ions on the bonding surfaces for the cure to progress. The list below indicates which metals are generally considered "Active" and result in a fast threadlocker cure, and which metals are "Inactive" and threadlocker curing will happen slowly. These "Inactive" metals will usually require the use of an activator to ensure the cure takes place as expected.

Active (Fast)	Inactive (Slow)
Aluminum alloys	Aluminum
Brass	Anodized aluminum
Bronze	Cadmium
Copper	Chemical black oxide
Iron	Galvanized steel
Manganese	Magnesium
Nickel	Plated parts
Steel	Stainless steel
	Zinc

# **Military Specifications**

 $3M^{\rm TM}$  Wind Threadlocker W1235 has been tested and passed the requirements of MIL-S-46163A.

### Storage

Store product at  $59-77^{\circ}F(15-25^{\circ}C)$  and out of direct sunlight for maximum shelf life.

# Shelf Life

This product has a shelf life of 12 months when stored in the original sealed container at room temperature.

# **Precautionary Information**

Refer to the product label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

For more information on our wind energy product line, contact 3M Renewable Energy at 800-755-2654 or visit us at www.3M.com/wind.

The technical information, recommendations, and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specifications at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including warranty, contract, negligence, or strict liability.



 Renewable Energy Division

 3M Center, Building 235-1S-67

 St. Paul, MN 55144-1000

 1-800-755-2654

 www.3M.com/wind

Please recycle. Printed in USA. © 3M 2012. All rights reserved. Issued: 4/12 8631HB 98-0150-0094-0

3M is a trademark of 3M Company. Used under license by 3M subsidiaries and affiliates.