# 3M™ Wafer De-Taping Tape 3305 for 3M™ WSS

## **Product Description**

3M<sup>™</sup> Wafer De-Taping Tape 3305 is a transparent polyester film with an adhesive specifically designed for the removal of the 3M<sup>™</sup> Wafer Support Systems (WSS) adhesive from the surface of the device wafer after the carrier glass is separated from the silicon wafer.

### **Features and Benefits**

- Enables simple, low-stress, room temperature peeling of 3M<sup>™</sup> Adhesives from thinned silicon wafers after glass carrier debonding
- Transparency allows for inspection without tape removal
- High instant adhesion to substrate
- Good holding power

### **Product Construction**

← Backing: Polyester film	(Nominal 0.038mm thickness)
← PSA: Rubber adhesive	(Nominal 0.030mm thickness)

# **Typical Physical Properties**

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Properties	Unit	Value	Test Method
Tape Thickness	mm	0.068	JIS Z 0237
Tensile Strength	N/cm	78.4	
Elongation	%	125	
Adhesion Strength (SUS)*1	N/cm	9.41	

<sup>\*1:</sup> Adhesion Strength is 180° peel strength on Stainless Steel.

- Substrate: Stainless Steel (SUS304) treated by abrading with #280 abrasive
- Pressure: 2kg rubber roller once for each direction
- Peel speed: 300mm/min.

- Sample width: 25mm

- Dwell time: from 20 to 40 minutes



# 3M<sup>™</sup> Wafer De-Taping Tape 3305 for 3M<sup>™</sup> WSS

## Regulatory

For regulatory information about this product, contact your 3M representative.

## **Technical Information**

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

#### **Product Use**

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

## Warranty, Limited Remedy, and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

# **Limitation of Liability**

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



