

3M™ Dyneon™

Fluoroplastic THV 505ESDZ

Product Description

3M™ Dyneon™ Fluoroplastic THV 505ESDZ is a fluorothermoplastic containing tetrafluoroethylene, hexafluoropropylene and vinylidene fluoride. Because of its well-balanced profile of low temperature processing, low flammability, thermal stability and melt processability, this product should preferably be used for extruded film, profiles and tubes, for example in automotive fuel hoses. This product is suited for high performance applications where electrostatic dissipation is necessary.

Special Features

- Excellent flexibility
- Excellent chemical resistance
- Excellent permeation resistance to fuels
- Bondable to itself and other substrates (for multi-layer constructions)
- Processing profile allows co-processing with olefinic plastics and hydrocarbon elastomers
- Low flammability
- Electrostatic dissipative

Properties	Test method	Unit	Value*
Melting Point	DIN EN ISO 12086	°C	165
Glass Transition (Tg)	ASTM D 4591	°C	26
Melt Flow Index	DIN EN ISO 1133	g/10 min	5
Specific Gravity	DIN EN ISO 12086	g/cm ³	1.97
Tensile at Break	DIN EN ISO 527-1	MPa	15
Elongation at Break	DIN EN ISO 527-1	%	310
Volume resistivity	DIN IEC 93, IEC 60093	Ω*cm	< 300

* typical values

3M™ Dyneon™ Fluoroplastic THV 505ESDZ

Typical Properties

3M™ Dyneon™ Fluoroplastic THV 505ESDZ provides a balance of low temperature processing, low flammability, thermal stability and melt processability along with electrostatic dissipative properties.

Typical Applications

3M™ Dyneon™ Fluoroplastic THV 505ESDZ can be used to prepare moulded parts and extruded films, tubes and profiles. It is useful for applications that require electrostatic dissipation, flexibility, low temperature processing and good chemical resistance.

Processing Recommendations

The processing recommendations depend on a variety of factors and it is best advised to contact a technical service person before embarking on extrusion trials. However, one can use the following as a starting point for the extrusion of THV 505 ESD Z.

Cooling on the feed throat of the extruder to maintain a temperature of 30 – 70 °C, Zone 1 180 °C, Zone 2 220 °C, Zone 3 260 °C, the die and other tooling around 260 °C. Typical processing temperatures for injection moulding are around 260 – 280 °C for the nozzle temperature and 50 – 100 °C for the mould. A screen pack of 1000 µm / 500 µm / 200 µm is recommended. Corrosion resistant equipment and an air exhausting system are highly recommended for safe processing.

Storage and Handling

3M™ Dyneon™ Fluoroplastic THV 505ESDZ has an unlimited shelf life provided it is stored in a clean, dry place. THV 505ESDZ needs to be dried if the container is opened prior to being extruded. We recommend 5 – 24 hours in a dehumidifying oven or hot air oven at 80 °C. Ideally, a moisture level of < 80 ppm should be achieved prior to extruding THV 505ESDZ to insure defect-free extrusion.

Safety Instructions

Follow the normal precautions observed with all fluorothermoplastic materials.

Please consult the Material Safety Data Sheet and Product Label for information regarding the safe handling of the material. By following all precautions and safety measures, processing these products poses no known health risks. General handling/processing precautions include: 1) Process only in well-ventilated areas. 2) Do not smoke in areas contaminated with powder/residue from these products. 3) Avoid eye contact. 4) If skin comes into contact with these products during handling, wash with soap and water afterwards. 5) Avoid contact with hot fluoropolymer.

Potential hazards, including release of toxic vapours, can arise if processing occurs under excessively high temperature conditions. Vapour extractor units should be installed above processing equipment. When cleaning processing equipment, do not burn off any of this product with a naked flame or in a furnace.

Delivery Form

3M™ Dyneon™ Fluoroplastic THV 505ESDZ is delivered in pellet form.

Packaging size is:

- 50 kg cardboard box, containing two PE-bags each with 25 kg content

3M™ Dyneon™ Fluoroplastic THV 505ESDZ

Important Notice

All information set forth herein is based on our present state of knowledge and is intended to provide general notes regarding products and their uses. It should not therefore be construed as a guarantee of specific properties of the products described or their suitability for a particular application. Because conditions of product use are outside Dyneon's control and vary widely, user must evaluate and determine whether a Dyneon product will be suitable for user's intended application before using it.

The quality of our products is warranted under our General Terms and Conditions of Sale as now are or hereafter may be in force.

Technical information, test data, and advice provided by Dyneon personnel are based on information and tests we believe are reliable and are intended for persons with knowledge and technical skills sufficient to analyse test types and conditions, and to handle and use raw polymers and related compounding ingredients. Testing in accordance with DIN, ISO and ASTM.

No license under any Dyneon or third party intellectual rights is granted or implied by virtue of this information.

General recommendations on health and safety in processing, on work hygiene and on measures to be taken in the event of accident are detailed in our material safety data sheets.

You will find further notes on the safe handling of fluoropolymers in the brochure "[Guide for the safe handling of Fluoropolymers Resins](#)" (download link) by PlasticsEurope, Box 3, B-1160 Brussels, Tel. +32 (2) 676 17 32.

You can also download it with your smartphone using the QR code below.



Customer Service

Europe

Phone: 00 800 396 366 27
Fax: 00 800 396 366 39

Italy

Phone: 800 7 910 18
Fax: 800 7 810 19

USA

Phone : +1 800 810 8499
Fax : +1 800 635 8061

Technical Service Fluoroplastics

Dyneon GmbH
3M Advanced Materials Division
Industrieparkstraße 1
84508 Burgkirchen
Germany
Phone: +49 8679 7 4709
Fax : +49 8679 7 5037

Technical Service Fluoroelastomers & Polymer Processing Additives

3M Belgium BVBA / SPRL
3M Advanced Materials Division
Canadastraat 11,
Haven 1005
2070 Zwijndrecht
Belgium
Phone: +32 3 250 7868
Fax: +32 3 250 7905

Technical Service PTFE Compounds

Dyneon B.V.
3M Advanced Materials Division
Tunnelweg 95
6468 EJ Kerkrade
The Netherlands
Phone: +31 45 567 9600
Fax: +31 45 567 9619

We will gladly supply further contact details for our full network of global sales offices. Alternatively, find them [here](#).



Web Site: www.dyneon.eu

Printed in Germany
© Dyneon 2013
Status: Aug. 2013

3M, Dyneon and Dynamar are Trademarks of 3M Company.
All Rights reserved. The present edition replaces all previous versions. Its content is being continuously adjusted to reflect the current level of knowledge. Please make sure and inquire if in doubt whether you have the latest edition.