

3M™ Dyneon™

Fluoroplastic THV 610GZ

Product Description

3M™ Dyneon™ Fluoroplastic THV 610GZ is a fluorothermoplastic containing tetrafluoroethylene, hexafluoropropylene and vinylidene fluoride. Because of its well-balanced profile of low flammability, permeation resistance, thermal stability, and melt processability, this product should preferably be used for extruded film, profiles, and tubes, for example in automotive fuel hoses.

Special Features

- Wide processing window
- Excellent chemical resistance
- Excellent permeation resistance to fuels
- Bondability to other plastics and elastomers without the need for surface treatments
- Low flammability
- High transparency
- Excellent UV stability
- Low refractive index

Properties	Test method	Unit	Value*
Melting Point	DIN EN ISO 12086	°C	190
Glass Transition (T _g)	ASTM D 4591	°C	34
Melt Flow Index	DIN EN ISO 1133	g/10 min	11
Specific Gravity	DIN EN ISO 12086	g/cm ³	2.03
Tensile at Break	DIN EN ISO 527-1	MPa	24
Elongation at Break	DIN EN ISO 527-1	%	450
Flexural Modulus	ASTM D 790	MPa	490
Limiting Oxygen Index	ASTM D 2863	%	> 75
Refractive Index	ASTM D 542	nd	1.35
UV-Vis Light Transmission (100µm film)	300 nm	%	82
	600 nm	%	93
Dielectric Constant (23°C)	ASTM D 150, @ 1MHz		4.66
	ASTM D 150, @ 9.4GHz		2.38
Dissipation Factor	ASTM D 150, @ 1MHz		0.09
	ASTM D 150, @ 9.4GHz		0.08
Dielectric Breakdown Strength	ASTM D 149	kV/mm	56

* typical values

3M™ Dyneon™ Fluoroplastic THV 610GZ

Typical Properties

3M™ Dyneon™ Fluoroplastic THV 610GZ provides a balance of low temperature processing, low flammability, thermal stability, and good permeation resistance. This product exhibits excellent weatherability and good anti-soiling properties.

Typical Applications

3M™ Dyneon™ Fluoroplastic THV 610GZ extends the melting point of THV grades to include those applications which require higher temperature service capabilities than are available from other THV grades. This grade provides good flexibility versus other fluoroplastics, but it is stiffer than the other grades of THV as the data below shows. Its present applications range from barrier layer in automotive hoses to protective layers in photovoltaic backsheets.

Processing Recommendations

The processing recommendations depend on a variety of factors and it is best advised to contact a technical service person before embarking on extrusion trials. However, one can use the following as a starting point for the extrusion of THV 610GZ.

Cooling on the feed throat of the extruder to maintain a temperature of 30 – 70 °C, Zone 1 210 °C, Zone 2 240 °C, Zone 3 265 °C, the die and other tooling around 280 °C. Typical processing temperatures for injection moulding are around 275 – 290 °C for the nozzle temperature and 50 – 100 °C for the mould. A screen pack of 1000 µm / 500 µm / 200 µm is recommended. Corrosion resistant equipment and an air exhausting system are highly recommended for safe processing.

Storage and Handling

3M™ Dyneon™ Fluoroplastic THV 610GZ has an unlimited shelf life provided it is stored in a clean, dry place. THV 610GZ is hydrophobic, and generally does not require drying before processing unless high humidity conditions create surface moisture adsorption.

Safety Instructions

Follow the normal precautions observed with all fluorothermoplastic materials.

Please consult the Material Safety Data Sheet and Product Label for information regarding the safe handling of the material. By following all precautions and safety measures, processing these products poses no known health risks. General handling/processing precautions include: 1) Process only in well-ventilated areas. 2) Do not smoke in areas contaminated with powder/residue from these products. 3) Avoid eye contact. 4) If skin comes into contact with these products during handling, wash with soap and water afterwards. 5) Avoid contact with hot fluoropolymer.

Potential hazards, including release of toxic vapours, can arise if processing occurs under excessively high temperature conditions. Vapour extractor units should be installed above processing equipment. When cleaning processing equipment, do not burn off any of this product with a naked flame or in a furnace.

Delivery Form

3M™ Dyneon™ Fluoroplastic THV 610GZ is delivered in pellet form.

Packaging size is:

- 50 kg cardboard box, containing two PE-bags each with 25 kg content

3M™ Dyneon™ Fluoroplastic THV 610GZ

Important Notice

All information set forth herein is based on our present state of knowledge and is intended to provide general notes regarding products and their uses. It should not therefore be construed as a guarantee of specific properties of the products described or their suitability for a particular application. Because conditions of product use are outside Dyneon's control and vary widely, user must evaluate and determine whether a Dyneon product will be suitable for user's intended application before using it.

The quality of our products is warranted under our General Terms and Conditions of Sale as now are or hereafter may be in force.

Technical information, test data, and advice provided by Dyneon personnel are based on information and tests we believe are reliable and are intended for persons with knowledge and technical skills sufficient to analyse test types and conditions, and to handle and use raw polymers and related compounding ingredients. Testing in accordance with DIN, ISO and ASTM.

No license under any Dyneon or third party intellectual rights is granted or implied by virtue of this information.

General recommendations on health and safety in processing, on work hygiene and on measures to be taken in the event of accident are detailed in our material safety data sheets.

You will find further notes on the safe handling of fluoropolymers in the brochure "[Guide for the safe handling of Fluoropolymers Resins](#)" (download link) by PlasticsEurope, Box 3, B-1160 Brussels, Tel. +32 (2) 676 17 32.

You can also download it with your smartphone using the QR code below.



Customer Service

Europe

Phone: 00 800 396 366 27
Fax: 00 800 396 366 39

Italy

Phone: 800 7 910 18
Fax: 800 7 810 19

USA

Phone : +1 800 810 8499
Fax : +1 800 635 8061

Technical Service Fluoroplastics

Dyneon GmbH
3M Advanced Materials Division
Industrieparkstraße 1
84508 Burgkirchen
Germany
Phone: +49 8679 7 4709
Fax : +49 8679 7 5037

Technical Service Fluoroelastomers & Polymer Processing Additives

3M Belgium BVBA / SPRL
3M Advanced Materials Division
Canadastraat 11,
Haven 1005
2070 Zwijndrecht
Belgium
Phone: +32 3 250 7868
Fax: +32 3 250 7905

Technical Service PTFE Compounds

Dyneon B.V.
3M Advanced Materials Division
Tunnelweg 95
6468 EJ Kerkrade
The Netherlands
Phone: +31 45 567 9600
Fax: +31 45 567 9619

We will gladly supply further contact details for our full network of global sales offices. Alternatively, find them [here](#).



Web Site: www.dyneon.eu

Printed in Germany
© Dyneon 2013
Status: Aug. 2013

3M, Dyneon and Dynamar are Trademarks of 3M Company.

All Rights reserved. The present edition replaces all previous versions. Its content is being continuously adjusted to reflect the current level of knowledge. Please make sure and inquire if in doubt whether you have the latest edition.