

3M™ Dyneon™ PTFE Micropowder TF 9207Z

Product Description

3M™ Dyneon™ PTFE Micropowder TF 9207Z is a white, non-free-flowing agglomerate of fine, low molecular PTFE micropowder. The agglomerate features a particle size of around 4 µm.

Special Features

- Agglomerate
- Almost universal chemical resistance
- Good non-stick properties
- Reduced friction resistance
- Large operating temperature range
- Increased degree of abrasion resistance
- Low molecular PTFE
- Easy deagglomeration
- U.S. Food and Drug Administration (FDA) approved up to 20 % weight in polymer formulations

Properties	Test method	Unit	Value
Mean Particle Diameter	ISO 13320	µm	4
Primary Particle Size	DIN ISO 13321	nm	120
Bulk Density	DIN EN ISO 60	g/l	260
Special Surface BET	DIN ISO 9277	m ² /g	17
Melt Flow Index (372 °C / 2.16 kg / 2.095 mm)	DIN EN ISO 1133	g/10 min	4
Melting Point	DIN EN ISO 12086	°C	330

3M™ Dyneon™ PTFE Micropowder TF 9207Z

Typical Properties

Due to its highly specific particle surface, 3M™ Dyneon™ PTFE Micropowder TF 9207Z can be effective as a rheological additive and significantly increases viscosity when added to liquids. This effect is not temperature-dependent. If TF 9207Z is added to solids or coatings, it can lead to a significant reduction in friction resistance and can also have a positive influence on the non-stick effect of the surface.

Typical Applications

3M™ Dyneon™ PTFE Micropowder TF 9207Z can be added to oils, fats, polymers, paints, elastomers and coatings. Typical additional quantity can vary between < 1 % and 20 % and depends on the selected matrix and the desired properties. Due to the extremely small primary particle size and the very specific surface, TF 9207Z is mainly used in liquids and coatings.

Processing Recommendations

3M™ Dyneon™ PTFE Micropowder TF 9207Z is an agglomerate. With suitable processing techniques it can be broken up and then divided further. This process can take place with the use of bead mills or a Turrax mixer. Deagglomeration should always take place in the intended matrix. These mixing processes ensure that the micropowder is distributed as evenly as possible within the matrix so as to achieve the desired effect.

As PTFE is an extremely inert substance, precautionary measures must be taken to ensure that the polymer remains within the matrix in the desired quantity. In liquids, this can be achieved by adding surfactants or by adjusting the viscosity. In solids, enriching the PTFE on the surface is often desired so as to adjust the ideal reduction of the friction resistance or to improve the non-stick effect.

Storage and Handling

3M™ Dyneon™ PTFE Micropowder TF 9207Z can be stored for a relatively long period of time. It should be kept in a clean, dry place at temperatures below 30 °C.

Safety Instructions

Follow the normal precautions observed with all fluoropolymer materials.

Please consult the Material Safety Data Sheet and Product Label for information regarding the safe handling of the material. By following all precautions and safety measures, processing these products poses no known health risks. General handling/processing precautions include: 1) Process only in well-ventilated areas. 2) Do not smoke in areas contaminated with powder/residue from these products. 3) Avoid eye contact. 4) If skin comes into contact with these products during handling, wash with soap and water afterwards. 5) Avoid contact with hot fluoropolymer.

Potential hazards, including release of toxic vapours, can arise if processing occurs under excessively high temperature conditions. Vapour extractor units should be installed above processing equipment. When cleaning processing equipment, do not burn off any of this product with a naked flame or in a furnace.

Delivery Form

3M™ Dyneon™ PTFE Micropowder TF 9207Z is delivered in agglomerate form.

Packaging sizes are:

- 25 kg cardboard box, containing one PE-bag with 25 kg content
- 300 kg cardboard box, containing 12 PE-bags each with 25 kg content

3M™ Dyneon™ PTFE Micropowder TF 9207Z

Important Notice

All information set forth herein is based on our present state of knowledge and is intended to provide general notes regarding products and their uses. It should not therefore be construed as a guarantee of specific properties of the products described or their suitability for a particular application. Because conditions of product use are outside Dyneon's control and vary widely, user must evaluate and determine whether a Dyneon product will be suitable for user's intended application before using it.

The quality of our products is warranted under our General Terms and Conditions of Sale as now are or hereafter may be in force.

Technical information, test data, and advice provided by Dyneon personnel are based on information and tests we believe are reliable and are intended for persons with knowledge and technical skills sufficient to analyze test types and conditions, and to handle and use raw polymers and related compounding ingredients.

No license under any Dyneon or third party intellectual rights is granted or implied by virtue of this information.

General recommendations on health and safety in processing, on work hygiene and on measures to be taken in the event of accident are detailed in our material safety data sheets.

You will find further notes on the safe handling of fluoropolymers in the brochure "[Guide for the safe handling of Fluoropolymers Resins](#)" (download link) by PlasticsEurope, Box 3, B-1160 Brussels, Tel. +32 (2) 676 17 32.

You can also download it with your smartphone using the QR code below.



Customer Service

Europe
Phone: 00 800 396 366 27
Fax: 00 800 396 366 39
Italy
Phone: 800 7 910 18
Fax: 800 7 810 19
USA
Phone: +1 800 810 8499
Fax: +1 800 635 8061

Technical Service Fluoroplastics

Dyneon GmbH
3M Advanced Materials Division
Industrieparkstraße 1
84508 Burgkirchen
Germany
Phone: +49 8679 7 4709
Fax: +49 8679 7 5037

Technical Service Fluoroelastomers & Polymer Processing Additives

3M Belgium BVBA / SPRL
3M Advanced Materials Division
Canadastraat 11
Haven 1005
2070 Zwijndrecht
Belgium
Phone: +32 3 250 7868
Fax: +32 3 250 7905

Technical Service PTFE Compounds

Dyneon B.V.
3M Advanced Materials Division
Tunnelweg 95
6468 EJ Kerkrade
The Netherlands
Phone: +31 45 567 9600
Fax: +31 45 567 9619

We will gladly supply further contact details for our full network of global sales offices. Alternatively, find them [here](#).



Web Site: www.dyneon.eu

Printed in Germany
© Dyneon 2014
Status: Feb. 2014

3M, Dyneon and Dynamar are Trademarks of 3M Company.
All Rights reserved. The present edition replaces all previous versions. Its content is being continuously adjusted to reflect the current level of knowledge. Please make sure and inquire if in doubt whether you have the latest edition.