

3M™ Dyneon™ PTFE Dispersion TF 5070GZ

Product Description

3M™ Dyneon™ PTFE Dispersion TF 5070GZ is a milky-white, water-based fluoropolymer dispersion. The dispersion has a solids content of around 50 %. The spherical hydrophobic polymer particles have an average size of around 120 nm. The polymer has a density of approximately 2.2 g/ml.

Special Features

- Very small particle size
- Almost universal chemical resistance
- Suitable for manufacturing bimodal systems
- Low settling tendency
- Very good non-stick properties
- Large operating temperature range
- Approved for use with food contact
- U.S. Food and Drug Administration (FDA) listed: 21CFR 177.1550
- Approved by the German Federal Ministry of Health (BGA)

Properties	Test method	Unit	Value
Solids Content	DIN EN ISO 12086	%	50
Emulsifier			non-ionic
Emulsifier Content (based on solids)	Internal Dyneon method	%	8
Particle Size	DIN ISO 13321	nm	120
pH Value	DIN ISO 976		> 9
Viscosity (D = 30 s ⁻¹)	DIN EN ISO 3219	mPas	12



3M™ Dyneon™ PTFE Dispersion TF 5070GZ

Typical Properties

3M™ Dyneon™ PTFE Dispersion TF 5070GZ is supplied with a pH value of 9 – 11. The dispersion can be mixed with fillers or pigments for use in coating formulations. Dilution is possible at any time but should be carried out with desalinated water.

Typical Applications

3M™ Dyneon™ PTFE Dispersion TF 5070GZ is mainly used to formulate non-stick coatings for manufacturing cookware and baking tins. Due to its small particle size, the dispersion is used as an additive to conventional PTFE dispersions so as to achieve a better packing density to the films. These improvements can lead to less corrosion, improved abrasion characteristics and increased shine.

For coating metal surfaces, various techniques such as spray coating, roller coating and silk-screen coating can be employed. The formulations have to be adjusted for each technique.

Processing Recommendations

Dyneon recommends that the dispersion always be gently homogenised before processing and filtered using a 50 µm filter.

When adding pigments and fillers, make sure that these do not negatively influence the excellent stability of the product. If necessary, stabilisers should be added to the mixture. If fillers or pigments require grinding, this should be carried out before they are added to the dispersion.

The dispersion can be used for manufacturing primers, intermediate layers or top coats. For this, the product is added to PTFE dispersions such as TF 5035Z. In order to further optimise the coating result with regard to shine and porosity, Dyneon recommends adding small amounts of fluorothermoplastic polymers such as 3M™ Dyneon™ Fluoroplastic PFA 6900GZ, PFA 6910GZ or FEP 6300GZ.

To dry the layers, a three-step, ideally continuous process is recommended with pre-drying at 90 – 120 °C, intermediate drying at 230 – 320 °C and then final sintering at 360 – 400 °C. The temperatures should be selected taking into account the substrate thickness, coating thickness and throughput speed. A flawlessly sintered polymer layer is always transparent and smoothly coalesced.

Storage and Handling

The aqueous dispersion must be stored under frost-proof conditions (5 – 30 °C). Although 3M™ Dyneon™ PTFE Dispersion TF 5070GZ has a low settling tendency, it should be homogenised once or twice a month by gentle rolling or stirring. Should sediment still build up, it can be redispersed by homogenising the dispersion as described above.

For more information please consult our technical information regarding "[Shelf Life and Storage of 3M™ Dyneon™ Fluoropolymer Dispersion Products](#)".

Safety Instructions

Follow the normal precautions observed with all fluoropolymer materials.

Please consult the Material Safety Data Sheet and Product Label for information regarding the safe handling of the material. By following all precautions and safety measures, processing these products poses no known health risks. General handling/processing precautions include: 1) Process only in well-ventilated areas. 2) Do not smoke in areas contaminated with powder/residue from these products. 3) Avoid eye contact. 4) If skin comes into contact with these products during handling, wash with soap and water afterwards. 5) Avoid contact with hot fluoropolymer.

Potential hazards, including release of toxic vapours, can arise if processing occurs under excessively high temperature conditions. Vapour extractor units should be installed above processing equipment. When cleaning processing equipment, do not burn off any of this product with a naked flame or in a furnace.

Delivery Form

3M™ Dyneon™ PTFE Dispersion TF 5070GZ is delivered as a water-based solution (dispersion).

Packaging sizes are:

- 30 l PE-drum with 40 kg content
- 1000 l IBC container with 1200 kg content

3M™ Dyneon™ PTFE Dispersion TF 5070GZ

Important Notice

All information set forth herein is based on our present state of knowledge and is intended to provide general notes regarding products and their uses. It should not therefore be construed as a guarantee of specific properties of the products described or their suitability for a particular application. Because conditions of product use are outside Dyneon's control and vary widely, user must evaluate and determine whether a Dyneon product will be suitable for user's intended application before using it.

The quality of our products is warranted under our General Terms and Conditions of Sale as now are or hereafter may be in force.

Technical information, test data, and advice provided by Dyneon personnel are based on information and tests we believe are reliable and are intended for persons with knowledge and technical skills sufficient to analyze test types and conditions, and to handle and use raw polymers and related compounding ingredients.

No license under any Dyneon or third party intellectual rights is granted or implied by virtue of this information.

General recommendations on health and safety in processing, on work hygiene and on measures to be taken in the event of accident are detailed in our material safety data sheets.

You will find further notes on the safe handling of fluoropolymers in the brochure "[Guide for the safe handling of Fluoropolymers Resins](#)" (download link) by PlasticsEurope, Box 3, B-1160 Brussels, Tel. +32 (2) 676 17 32.

You can also download it with your smartphone using the QR code below.



Customer Service

Europe

Phone: 00 800 396 366 27
Fax: 00 800 396 366 39

Italy

Phone: 800 7 910 18
Fax: 800 7 810 19

USA

Phone : +1 800 810 8499
Fax : +1 800 635 8061

Technical Service Fluoroplastics

Dyneon GmbH
3M Advanced Materials Division
Industrieparkstraße 1
84508 Burgkirchen
Germany
Phone: +49 8679 7 4709
Fax : +49 8679 7 5037

Technical Service Fluoroelastomers & Polymer Processing Additives

3M Belgium N.V.
3M Advanced Materials Division
Canadastraat 11
Haven 1005
2070 Zwijndrecht
Belgium
Phone: +32 3 250 7868
Fax: +32 3 250 7905

Technical Service PTFE Compounds

Dyneon B.V.
3M Advanced Materials Division
Tunnelweg 95
6468 EJ Kerkrade
The Netherlands
Phone: +31 45 567 9600
Fax: +31 45 567 9619

We will gladly supply further contact details for our full network of global sales offices. Alternatively, find them [here](#).



Web Site: www.dyneon.eu

Printed in Germany
© Dyneon 2016
Status: April 2016

3M, Dyneon and Dynamar are Trademarks of 3M Company.
All Rights reserved. The present edition replaces all previous versions. Its content is being continuously adjusted to reflect the current level of knowledge. Please make sure and inquire if in doubt whether you have the latest edition.