

# 3M™ Dyneon™

## Perfluoroelastomer PFE 90

### Gum

#### Product Description

3M™ Dyneon™ Perfluoroelastomer PFE 90 is a technically advanced perfluoroelastomer designed to meet the challenges of demanding sealing applications. Its fully fluorinated backbone structure provides a very broad chemical and thermal stability.

#### Special Features

- Outstanding chemical resistance against most chemicals such as acids, alkalines, fuel, ketones, aldehydes, esters, alcohols and amines.
- Excellent long term compression set resistance
- Good processability, scorch resistance and de-mouldability.
- Excellent heat ageing properties
- Excellent physical properties

#### Typical Applications

Dyneon PFE finished products like Dyneon Perfluoroelastomer PFE 90 can be used in applications such as mechanical seals, valves, pumps, reactors, mixers, ink/printing systems, painting systems, rubber-metal bonding parts, among others.

#### Typical Polymer Properties

Property	Test method	Unit	Value
Colour			Opaque, Off-white
Fluorine Content	QCM 50.18.3C	%	72.2
Mooney Viscosity (raw gum) ML 1 + 10 @ 121°C	QCM 2.14.4C	Mooney Unit	90
Specific Gravity	QCM 14.10		1.98

#### Storage and Handling

Store and use Dyneon Perfluoroelastomer PFE 90 only in a well ventilated area. The shelf life of Dyneon Perfluoroelastomer PFE 90 is 2 years from date of manufacturing.

#### Delivery Form

Dyneon Perfluoroelastomer PFE 90 is delivered in crumb form.

Packaging sizes are:

- 5 kg cardboard box, containing PE-bags with 1kg to 5 kg content each

#### Processing Recommendations

N/A

**3M™ Dyneon™**  
**Perfluoroelastomer PFE 90**  
**Gum**

### Typical Properties

Compound	Amount (in Parts/100)
PFE 90	100
Carbon Black MT N-990	20
ZnO	5.0
TAIC (70 %)	2.5
Trigonox 101-50D	1.5

### Typical Rheological Properties

Alpha Technologies Moving Die Rheometer (MDR 2000), 100 cpm, 0.5° Arc, (QCM 2.19.1)  
 Test Condition, 6' @ 177°C

Property	Unit	Value
ML, Minimum Torque	dNM	3.5
MH, Maximum Torque	dNM	20.0
ts2	Minutes	0.5
t'50, Time to 50 % cure	Minutes	0.7
t'90, Time to 90 % cure	Minutes	1.9

### Typical Physical Properties

Press Cured 10' @ 177 °C  
 Post Cured 16 hours @ 230 °C

Property	Unit	Value
<b>Physical Properties DIN 53504 (S2 DIE)</b>		
100 % Modulus	MPa	13.1
Tensile	MPa	19.8
Elongation at break	%	134
Hardness (ASTM D2240)	Shore A	73

### Compression Set on O-rings ASTM D395 method B

70 hours @ 200 °C	%	29
70 hours @ 230 °C	%	37

### Lower Temperature Property

TR10 (ASTM D1329)	°C	- 2
-------------------	----	-----

# 3M™ Dyneon™

## Perfluoroelastomer PFE 90

### Gum

#### Safety Instructions

Follow the normal precautions observed with all fluoropolymer materials.

Please consult the Material Safety Data Sheet and Product Label for information regarding the safe handling of the material. By following all precautions and safety measures, processing these products poses no known health risks. General handling/processing precautions include: 1) Process only in well-ventilated areas. 2) Do not smoke in areas contaminated with powder/residue from these products. 3) Avoid eye contact. 4) If any skin comes into contact with these products during handling, wash with soap and water afterwards. 5) Avoid contact with hot fluoropolymer.

Potential hazards, including release of toxic vapours, can arise if processing occurs under excessively high temperature conditions. Vapour extractor units should be installed above processing equipment. When cleaning processing equipment, do not burn off any of this product with a naked flame or in a furnace.

#### Important Notice

All information set forth herein is based on our present state of knowledge and is intended to provide general notes regarding products and their uses. It should not therefore be construed as a guarantee of specific properties of the products described or their suitability for a particular application. Because conditions of product use are outside Dyneon's control and vary widely, user must evaluate and determine whether a Dyneon product will be suitable for user's intended application before using it.

The quality of our products is warranted under our General Terms and Conditions of Sale as now are or hereafter may be in force.

Technical information, test data, and advice provided by Dyneon personnel are based on information and tests we believe are reliable and are intended for persons with knowledge and technical skills sufficient to analyze test types and conditions, and to handle and use raw polymers and related compounding ingredients.

No license under any Dyneon or third party intellectual rights is granted or implied by virtue of this information.

General recommendations on health and safety in processing, on work hygiene and on measures to be taken in the event of accident are detailed in our material safety data sheets.

You will find further notes on the safe handling of fluoropolymers in the brochure "[Guide for the safe handling of Fluoropolymers Resins](#)" (download link) by PlasticsEurope, Box 3, B-1160 Brussels, Tel. +32 (2) 676 17 32.

You can also download it using the QR code below with your smartphone.



#### Customer Service

Europe  
Phone: 00 800 396 366 27  
Fax: 00 800 396 366 39  
Italy  
Phone: 800 7 910 18  
Fax: 800 7 810 19  
USA  
Phone: +1 800 810 8499  
Fax: +1 800 635 8061

#### Technical Service Fluoroplastics

Dyneon GmbH  
3M Advanced Materials Division  
Industrieparkstraße 1  
84508 Burgkirchen  
Germany  
Phone: +49 8679 7 4709  
Fax: +49 8679 7 5037

#### Technical Service Fluoroelastomers & Polymer Processing Additives

3M Belgium N.V.  
3M Advanced Materials Division  
Canadastraat 11  
Haven 1005  
2070 Zwijndrecht  
Belgium  
Phone: +32 3 250 7868  
Fax: +32 3 250 7905

#### Technical Service PTFE Compounds

Dyneon B.V.  
3M Advanced Materials Division  
Tunnelweg 95  
6468 EJ Kerkrade  
The Netherlands  
Phone: +31 45 567 9600  
Fax: +31 45 567 9619

We will gladly supply further contact details for our full network of global sales offices. Alternatively, find them [here](#).



Web Site: [www.dyneon.eu](http://www.dyneon.eu)

Printed in Germany  
© Dyneon 2020  
Status: Jul. 2020

3M, Dyneon and Dynamar are Trademarks of 3M Company.  
All Rights reserved. The present edition replaces all previous versions. Its content is being continuously adjusted to reflect the current level of knowledge. Please make sure and inquire if in doubt whether you have the latest edition.