



# Scotch™ Filament Tape 8956

## Product Data Sheet

October 2009  
Supersedes: December 2003

**Product Description** A utility packaging tape reinforced with continuous glass filaments which gives tensile strength to the tape.

**Key Features** The ScotchPro™ bi-axially oriented polypropylene backing provides abrasion, moisture and scuff resistance. The adhesive is formulated to adhere adequately to fiberboard surfaces.

### Construction

<b>Adhesive Type</b>	Synthetic Rubber Resin (Hot Melt)
<b>Backing</b>	BOPP
<b>Reinforcement</b>	Glass Yarns
<b>Total Thickness</b> AFERA 5006	120 µm
<b>Core size (ID)</b>	76 mm (3")
<b>Colour</b>	Transparent

### Performance Characteristics

<b>Adhesion to Stainless Steel</b> AFERA 5001	8,0 N/cm
<b>Tensile Strength</b> AFERA 5004	260 N/cm
<b>Elongation at Break</b> AFERA 5004	6 %
<b>Static Shear</b> AFERA 5012	2000+ minutes

---

<b>Storage</b>	Store in clean dry place. Temperature of 21 °C and 50 % relative humidity are recommended.
<b>Shelf Life</b>	Scotch 8956 has a shelf life of 12 months from date of dispatch by 3M.
<b>Precautionary Information</b>	Refer to product label and Material Safety Data Sheet for health and safety information before using the product. For information please contact your local 3M Office. <a href="http://www.3M.com">www.3M.com</a>
<b>For Additional Information</b>	To request additional product information see address below
<b>Important Notice</b>	All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

---

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications.

This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

---

**3M United Kingdom PLC**  
2M Centre, Cain Road, Bracknell  
RG12 8HT  
United Kingdom

**3M Svenska AB**  
Herrjärva torg 4  
170 67 Solna  
Sweden

**3M Eesti OÜ**  
Pärnu mnt. 158  
11317 Tallinn  
Estonia

**3M Ireland Ltd**  
The Iveagh Building, 3rd Floor  
The Park, Carrickmines 18  
Ireland

**3M a/s**  
Hannemanns Allé 53  
DK-2300 Copenhagen S.  
Denmark

**3M Latvia SIA**  
K.Ulmaņa gatve 5  
Rīga, LV-1004  
Latvia

**3M Belgium bvba/sprl**  
Hermeslaan 7  
1831 Diegem  
Belgium

**3M Norge AS**  
Tærudgata 16  
2004 Lillestrøm  
Norway

**3M Lietuva UAB**  
A.Goštauto g. 40  
Vilnius LT- 03163  
Lithuania

**3M Nederland B.V.**  
Molengraaffsingel 29  
2629 JD Delft  
The Netherlands

**Suomen 3M Oy**  
Keilaranta 6  
02150 Espoo  
Finland