

3M™ Flame Barrier FRB-NC Laminate

Data Sheet

August 2012

Description 3M™ Flame Barrier FRB-NC Laminate series is 3M™ Flame Barrier FRB-NC laminated to both sides of Polyester (PET) film.

These barriers are available in roll or sheet form.

The flame barrier FRB-NC laminated series provides the reliability you need from 3M, a trusted company with over 30 years of experience providing insulating solutions that protect people, equipment, and property around the globe.

Applications The flame barrier FRB-NC laminate series provides both electric shock and flame protection for electrical and electronic device applications such as:

- Appliance enclosures (timers, drip and contact shields)
- Lighting
- Electrical devices (e.g., timers, actuators, switches)

Features The flame barrier FRB-NC laminate series is:

- Composed of inorganic-based, halogen free UL 94 V-0, 5VA outer layers
- Made with UL Recognized UL 94 VTM-2 PET film inner layer
- Strong physical and dielectric properties
- Dimensionally stable, Easily slit, cut, formed and die cut
- Available in thicknesses from 15 to 17.5 mils (0.380 to 0.445 mm)

Regulatory The flame barrier FRB-NC laminate series is:

- **REACH compliant.** Product contains no Substances of Very High Concern (SVHC's) on the REACH candidate lists according to article 59 of Regulation (EC) No 1907/2006 up to June 2012. For current status, go to www.3M.com/REACH
- **RoHS Meets MCVs 2011/65/EU.** "RoHS meets MCVs" means that the product or part does not contain any of the substances in excess of the maximum concentration values ("MCVs") in EU RoHS Directive 2011/65/EU. The MCVs are by weight in homogeneous materials.
- **Halogen Free** defined as both 1) no halogen compounds are intentionally added to the product or used in the manufacturing process for the product and 2) any impurities present are less than 900 ppm bromine, less than 900 ppm chlorine, and/or less than 1500 ppm total bromine and chlorine. The latter are the levels set forth in certain industry standards, such as the International Electrotechnical Commission (IEC) 61249-2-21 standard.
- The above information represents 3M's knowledge and belief which may be based in whole or in part on information provided by 3rd party suppliers to 3M.

Flammability The UL 94 test method is used to classify materials based on results from specified small-scale flame tests. These classifications (5VA, 5VB, V-0, V-1, V-2, HB), listed in decreasing order of flame resistance, are used to distinguish a material's burning characteristics after test specimens have been exposed to a specified test flame under controlled laboratory conditions. These classifications typically apply to materials used in manufacturing enclosures, structural parts, and insulators found in consumer electronic products.

A material classified as 5VA or 5VB is subjected to a flame ignition source that is approximately five times more severe than that used in the V-0, V-1, V-2 and HB tests. Furthermore, specimens in 5VA or 5VB may not drip any flaming particles and 5VA rated specimens may not develop any burn-through holes during the test.

3M™ Flame Barrier FRB-NC Laminate Series

Typical Properties for FRB-NC Laminates

Technical information provided consists of typical product data and should not be used for specification purposes. All tests are performed at room temperature unless otherwise noted.

Property	Units	Test Method	FRB-NC Laminate 5-5-5	FRB-NC Laminate 5-7.5-5
Nominal Thickness	mm mil	ASTM D-645	0.380 15.0	0.445 17.5
Color			Ivory	Ivory
Construction			FRB-NC127 PET 5 mil FRB-NC127	FRB-NC127 PET 7.5 mil FRB-NC127
Physical Properties				
Basis Weight	g/m ² lb/yd ²	ASTM D-202	391 0.72	495 0.91
Density	g/cc		1.0	1.1
Moisture Absorption	%	ASTM D-644	<1	<1
Mechanical Properties				
Tensile Strength, MD	lb/inch N/cm	ASTM D-828	125 219	160 280
Tensile Strength, CD	lb/inch N/cm	ASTM D-828	110 193	190 333
Elongation to Break, MD	%	ASTM D-828	3	3
Elongation to Break, CD	%	ASTM D-828	4	4
Elmendorf Tear, MD	g N	ASTM D-689	515 5.0	773 7.5
Elmendorf Tear, CD	g N	ASTM D-689	615 6.0	923 9.0
Electrical Properties				
Dielectric Breakdown Voltage	kV	ASTM D-149	16	20

3M™ Flame Barrier FRB-NC Laminate Series

Typical Properties for Outer Layers of FRB-NC Laminates

Flame barrier FRB-NC laminate is made using UL Recognized flame barrier FRB-NC series insulation.

Technical information provided consists of typical product data and should not be used for specification purposes. All tests are performed at room temperature unless otherwise noted.

Property	Units	Test Method	FRB-NC127
Nominal Thickness	Mm mil	ASTM D-645	0.127 5.0
Color			Ivory
Physical Properties			
Flame Rating (UL File E65069)	Flammability rating	UL94	V-0, 5VA
Electrical Properties			
High-Voltage Arc Tracking Rate (HVTR)	PLC assigned	UL 746A	0
Comparative Tracking Index (CTI)	PLC assigned	UL 746A	0
Hot Wire Ignition (HWI)	PLC assigned	UL 746A	4
High Current Arc to Ignition (HAI)	PLC assigned	UL 746A	3
High Volt, Low Current Arc Resistance	PLC assigned	ASTM D-495	5
Dielectric Breakdown Voltage	kV	ASTM D-149	0.9
Dielectric Breakdown Strength	V/mil	ASTM D-149	180

3M™ Flame Barrier FRB-NC Laminate Series

Typical Properties for Inner Layer of FRB-NC Laminates (Electrical Grade Polyester Film)

Flame barrier FRB-NC laminate is made using UL Recognized QMFZ2 polyester film.

Technical information provided consists of typical product data and should not be used for specification purposes. All tests are performed at room temperature unless otherwise noted.

Property	Units	Test Method	5 mil	7.5 mil
Nominal Thickness	mm mil	ASTM D-645	0.127 5	0.191 7.5
Color			Clear	Clear
Physical Properties				
Basis Weight	g/m ² lb/yd ²	ASTM D-202	175 0.32	271 0.50
Density	g/cc		1.39	1.39
Tensile Strength, MD	lb/in N/cm	ASTM D-828	125 219	188 328
Tensile Strength, CD	lb/in N/cm	ASTM D-828	125 219	188 328
Elongation to Break, MD	%	ASTM D-828	130	130
Electrical Properties				
Dielectric Breakdown Voltage	kV	ASTM D-149	15	19

3M™ Flame Barrier FRB-NC Laminate Series

Shelf Life & Storage

This product has a 5-year shelf life from date of manufacture when stored in a humidity controlled storage (from 10°C / 50°F to 27°C / 80° F and <75% relative humidity)

Availability

For availability, please contact your local distributor. Names and addresses are available from 3M.com/electrical [Where to Buy] or call 1-800-676-8381.

Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

Warranty; Limited Remedy; Limited Liability

This product will be free from defects in material and manufacture at the time of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.**

3M is a trademark of 3M Company.
All other trademarks are property of their respective owners.



Electrical Markets Division
6801 River Place Blvd.
Austin, TX 78726-9000
800.676.8381
FAX 800.828.9329
www.3M.com/OEM

Please recycle.
© 3M 2012 All rights reserved.
78-8141-5612-7 Rev A