

3M Advanced Materials Division

3M™ Dyneon™ High Temperature Perfluoroelastomer PFE 132TB

Features and Benefits

- Ideal for dry side (thermal processes) semiconductor applications including plasma
- Upper use temperature of 315°C
- Excellent compression set resistance offering enhanced sealing force retention and seal life
- Very low metal ion content with low extractables

Typical Properties

Property	Units	Value
Specific Gravity		2.0
Color		White
Form		Crumb
TR 10	°C (°F)	-2°C (28°F)
Brittleness Point	°C (°F)	-35°C (-31°F)
Mooney Viscosity ML 1 + 10 @ 121°C (250°F)	MU	100

Product Description

3M™ Dyneon™ PFE 132TB is a technically advanced high temperature perfluoroelastomer (HT PFE). It is designed to meet the challenges of higher temperature applications. It is classified as FFKM per ASTM D1418. Its fully fluorinated backbone structure provides a very broad chemical and thermal stability.

Delivered Product Form

Dyneon PFE 132TB is packaged in crumb form. It is available in 1 kg and 10 kg boxes.

Note: Package size(s) may vary by region.

Safety/Toxicology

Before processing 3M™ Dyneon™ Perfluoroelastomers, read and follow all precautions and directions for use contained in the product label and Safety Data Sheet (SDS). General handling precautions and directions for use include: (1) Store and use all Dyneon perfluoroelastomers only in well ventilated areas; (2) Do not smoke in areas contaminated with dust from perfluoroelastomers; (3) Avoid eye contact; (4) After handling Dyneon perfluoroelastomers wash any contacted skin with soap and water. Potential hazards, including evolution of toxic vapors, can occur during compounding or processing under excessively high temperature conditions. Appropriate local exhaust ventilation such as vapor extractor units should be installed above compounding or processing equipment. When compounding, be sure to read and follow all precautions and directions for use from other compound ingredient suppliers.

Note: Data in this document are not for specification purposes.

ISO Registrations

All Dyneon fluoroelastomers are manufactured at ISO 9001 and 14001 registered facilities.

Typical Properties of Vulcanizate

Compound	phr
3M™ Dyneon™ Perfluoroelastomer PFE 132TB	94
Aerosil® R972	1.5
3M™ Dyneon™ Perfluoroelastomer Curative PFE 01CZ	7.5
TiO ₂	5

Typical Rheological Properties [ASTM D5289]

Moving Die Rheometer (MDR) 100 cpm, 0.5° Arc
12 Minutes @ 188°C (370°F)

Property	Units	Result
ML, Minimum Torque	dN m (inch-lb)	1.5 (1.3)
ts2, Time to 2 Inch-lb Rise from Minimum	Minutes	1.7
t'50, Time to 50% Cure	Minutes	2.8
t'90, Time to 90% Cure	Minutes	6.2
MH, Maximum Torque	dN m (inch-lb)	18.1 (16.0)

Typical Physical Properties [ASTM D412]

Press Cure 15 Minutes @ 188°C (370°F)
Post Cure 24 Hours @ 250°C (482°F)

Property	Units	Result
Tensile	MPa (psi)	15.6 (2260)
100% Modulus	MPa (psi)	6.9 (1002)
Elongation at Break	%	241
Durometer Type A Hardness [ASTM D2240]	Points	79

Compression Set Resistance [ASTM D395 Method B, -214 O-rings]

Property	Units	Result
70 Hours @ 232°C (450°F) – 25% Deformation	%	36
70 Hours @ 300°C (572°F) – 25% Deformation	%	73

Customer Service

Europe

Dyneon GmbH
3M Advanced Materials Division
Carl-Schurz-Straße
41453 Neuss
Germany
Phone: +00 800 396 366 27
Fax: +00 800 396 366 39
www.dyneon.eu

Italy

Phone: 0 800 7 910 18
Fax: 0 800 7 910 19

Latin America

3M Brasil
Via Anhanguera km
110 Sumare
Sao Paulo CEP 13181-900
Brasil
Phone: 0800 0132333

3M Mexico
Santa Fe 190, Col. Santa Fe
Deleg. Alvaro Obregon
Mexico D.F., C.P. 01210
México
Phone: 0052 5552700 400
Ext 82935

Asia

3M Japan
6-7-29, Kita-Shinagawa
Shinagawa-ku
Tokyo 141-8684
Japan
Phone: 81 570 022 123

3M Korea
19F, 82, Uisadang-daero
Yeongdeungpo-gu, Seoul, 150-705
Korea
Phone: 82 2 3771 4027

3M Taiwan
6F, No.95, Sec. 2
Dunhua S. Rd.
Taipei 10682
Taiwan
Phone: 886 2 2704 9011

3M Thailand
150 Soi Chalongsongkrong 31
Ladkrabang Bangkok, 10520
Thailand
Phone: 66 2739 4803 9
Ext 2354

USA

3M Advanced Materials Division
3M Center, 280-01W-03
St. Paul, MN 55144-1000
United States
Phone: 1 800 810 8499

Please visit 3M.com/fluoropolymers for additional regional contact information.

Warranty, Limited Remedy, and Disclaimer: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. User is solely responsible for evaluating third party intellectual property rights and for ensuring that user's use of 3M product does not violate any third party intellectual property rights. Unless a different warranty is specifically stated in the applicable product literature or packaging insert, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OF NON-INFRINGEMENT OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damages arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

Technical Information: Technical information, recommendations, and other statements contained in this document or provided by 3M personnel are based on tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.



3M Advanced Materials Division

3M Center
St. Paul, MN 55144 USA

Phone 1-800-367-8499
Web www.3M.com/fluoroelastomers

3M and Dyneon are trademarks of
3M Company. Used under license.

Please recycle. Printed in USA © 3M 2020.
All rights reserved. Issued: 6/20 16248HB