

3M™ Dyneon™

High Temperature Perfluoroelastomer

PFE 133TBZ

Features and Benefits

- Upper use temperature of 315°C
- Excellent compression set resistance offering enhanced sealing force retention and seal life
- Ideal for dry side (thermal processes) semiconductor applications including plasma
- Low metal ion content with low extractables

Note: Data in this document are not for specification purposes.

Typical Properties

Property	
Specific Gravity	2.0
Color	White
Form	Crumb
TR 10	-2°C (28°F)
Brittleness Point	-35°C (-31°F)
Mooney Viscosity – ML (1+10) @ 121°C	110

Product Description

3M™ Dyneon™ PFE 133TBZ is a technically advanced high temperature perfluoroelastomer (HT PFE). It is designed to meet the challenges of higher temperature plasma applications. It is classified as FFKM per ASTM D1418. Its fully fluorinated backbone structure provides a very broad chemical and thermal stability.

Product Form

Dyneon PFE 133TBZ is packaged in crumb form. It is available in 2 kg and 10 kg boxes.

Safety/Toxicology

Before processing 3M perfluoroelastomers, read and follow all precautions and directions for use contained in the product label and Material Safety Data Sheet (MSDS). General handling precautions and directions for use include: (1) Store and use all 3M perfluoroelastomers only in well ventilated areas; (2) Do not smoke in areas contaminated with dust from 3M perfluoroelastomers; (3) Avoid eye contact; (4) After handling 3M perfluoroelastomers wash any contacted skin with soap and water. Potential hazards, including evolution of toxic vapors, can occur during compounding or processing under excessively high temperature conditions. Appropriate local exhaust ventilation such as vapor extractor units should be installed above compounding or processing equipment. When compounding, be sure to read and follow all precautions and directions for use from other compound ingredient suppliers.

Note: Data in this document are not for specification purposes.

Typical Properties of Vulcanizates

Compound	phr
PFE 133TBZ	94
Aerosil® R972	1.5
PFE 01CZ	7.5
TiO ₂	5

Typical Rheological Properties [ASTM D5289] Moving Die Rheometer (MDR) 100 cpm, 0.5° Arc, 15 Minutes @ 188°C (370°F)

Property	
ML, Minimum Torque, Inch-lb (dN m)	1.5 (1.7)
t ₂ , Time to 2 Inch-lb Rise from Minimum – Minutes	1.8
t'50, Time to 50% Cure – Minutes	2.7
t'90, Time to 90% Cure – Minutes	5.8
MH, Maximum Torque, Inch-lb (dN m)	15.5 (17.5)

Typical Physical Properties Press Cure 15 Minutes @ 188°C (370°F) Post Cure 24 Hours @ 250°C (482°F)

Property	
Tensile, psi (MPa)	2323 (16.0)
100% Modulus, psi (MPa)	1327 (9.1)
Elongation at Break, %	192
Hardness, Shore A [ASTM D2240]	79

Compression Set Resistance [ASTM D395 Method B, -214 O-rings]

70 Hours @ 232°C (450°F) – 25% Deformation	26
168 Hours @ 232°C (450°F) – 25% Deformation	39
70 Hours @ 300°C (572°F) – 25% Deformation	60

Product Stewardship – Replacement Emulsifier: Dyneon™ and Dynamar™ products identified with a “Z” at the end of the product name indicate products that are made using a replacement emulsifier. This emulsifier, which Dyneon, a 3M subsidiary, began using in the manufacturing processes for these products in 2008, is a polymerization aid used to manufacture certain fluoropolymers and is not an intended ingredient in the polymers. The new emulsifier eliminates the use of the former polymerization aid, APFO (ammonium perfluorooctanoate, the ammonium salt of perfluorooctanoic acid (PFOA)), in the manufacture of these fluoropolymers. The use of the replacement emulsifier in the manufacture of these products is consistent with our product stewardship principles and our commitment to US EPA’s Voluntary PFOA Stewardship Program under which fluoropolymer manufacturers agreed to work towards eliminating PFOA in emissions and product content by the year 2015. **We are pleased to report that Dyneon completely eliminated the use of APFO in its manufacturing processes in December 2008.**

Warranty, Limited Remedy, and Disclaimer: Many factors beyond 3M’s control and uniquely within user’s knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user’s method of application. Unless a different warranty is specifically stated in the applicable product literature or packaging insert, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M’s option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damages arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

Technical Information: Technical information, recommendations, and other statements contained in this document or provided by 3M personnel are based on tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.



3M Center
St. Paul, MN 55144-1000
1-800-810-8499
www.3M.com

Please recycle. Printed in USA.
© 3M 2013. All rights reserved.
Issued: 3/13 8358HB
98-0800-0515-4

3M, Dynamar and Dyneon are trademarks of 3M.
Used under license.
Aerosil is a registered trademark of Evonik Industries.