

3M™ Dyneon™

Perfluoroelastomer PFE 7502BZ Black Compound

Product Description

The new Dyneon Perfluoroelastomer compound PFE 7502BZ provides an unusual combination of very broad chemical resistance and excellent physical properties at continuous high service temperatures up to 275°C. It is ideally suited for applications in the chemical processing industry as it provides long-term reliable sealing in the most extreme environments.

PFE 7502BZ is compliant to the relevant FDA standards. Please contact us for more details.

Special Features

- 75 Shore A black compound
- Proprietary gum / cure system
- Designed for mid and high temperature applications
- Excellent chemical resistance
- Continuous operating temperature of 275 °C
- Excellent long term high temperature compression set
- Conforms to USP VI
- FDA compliant

Typical Applications

Dyneon PFE Black Compound finished products like PFE 7502BZ can be used in applications such as mechanical seals, valves, pumps, reactors, mixers and rubber-metal bonding parts, among others.

Typical Polymer Properties

Property	Test method	Unit	Value
Colour			Black
Specific Gravity	QCM 14.10		2.02

Storage and Handling

Store Dyneon Perfluoroelastomer PFE 7502BZ in a fridge or climate controlled area in an air-sealed bag away from moisture. Allow conditioning to room temperature in the bag prior to use. The shelf life of Dyneon Perfluoroelastomer PFE 7502BZ is 1 year from date of manufacturing.

Delivery Form

Dyneon Perfluoroelastomer PFE 7502BZ is delivered in extruder ready strip form.

Packaging sizes are:

- 5 kg cardboard box, containing PE /Aluminium / Epoxy layered bags with 1 kg content each

Processing Recommendations

N/A

3M™ Dyneon™
Perfluoroelastomer PFE 7502BZ
Black Compound

Typical Properties

Compound	Amount (in Parts/100)
N/A	

Typical Rheological Properties

Alpha Technologies Moving Die Rheometer (MDR 2000), 100 cpm, 0.5° Arc, (QCM 2.19.1)
Test Condition, 30' @ 177°C

Property	Unit	Value
ML, Minimum Torque	dNm	1.1
MH, Maximum Torque	dNm	20.6
ts2	Minutes	0.9
t'50, Time to 50 % cure	Minutes	5.8
t'90, Time to 90 % cure	Minutes	19.4

Typical Physical Properties

Press Cured 15' @ 177 °C
Post Cured 24 hours @ 250 °C

Property	Unit	Value
----------	------	-------

Physical Properties DIN 53504 (S2 DIE)

100 % Modulus	MPa	11.6
Tensile	MPa	15.8
Elongation at break	%	129
Hardness (ASTM D2240)	Shore A	76

Compression Set on O-rings ASTM D395 method B

70 hours @ 200 °C	%	15
70 hours @ 275 °C	%	40

Lower Temperature Property

TR10 (ASTM D1329)	°C	0
-------------------	----	---

3M™ Dyneon™ Perfluoroelastomer PFE 7502BZ Black Compound

Safety Instructions

Follow the normal precautions observed with all fluoropolymer materials.

Please consult the Material Safety Data Sheet and Product Label for information regarding the safe handling of the material. By following all precautions and safety measures, processing these products poses no known health risks. General handling/processing precautions include: 1) Process only in well-ventilated areas. 2) Do not smoke in areas contaminated with powder/residue from these products. 3) Avoid eye contact. 4) If any skin comes into contact with these products during handling, wash with soap and water afterwards. 5) Avoid contact with hot fluoropolymer.

Potential hazards, including release of toxic vapours, can arise if processing occurs under excessively high temperature conditions. Vapour extractor units should be installed above processing equipment. When cleaning processing equipment, do not burn off any of this product with a naked flame or in a furnace.

Important Notice

All information set forth herein is based on our present state of knowledge and is intended to provide general notes regarding products and their uses. It should not therefore be construed as a guarantee of specific properties of the products described or their suitability for a particular application. Because conditions of product use are outside Dyneon's control and vary widely, user must evaluate and determine whether a Dyneon product will be suitable for user's intended application before using it.

The quality of our products is warranted under our General Terms and Conditions of Sale as now are or hereafter may be in force.

Technical information, test data, and advice provided by Dyneon personnel are based on information and tests we believe are reliable and are intended for persons with knowledge and technical skills sufficient to analyze test types and conditions, and to handle and use raw polymers and related compounding ingredients.

No license under any Dyneon or third party intellectual rights is granted or implied by virtue of this information.

General recommendations on health and safety in processing, on work hygiene and on measures to be taken in the event of accident are detailed in our material safety data sheets.

You will find further notes on the safe handling of fluoropolymers in the brochure "[Guide for the safe handling of Fluoropolymers Resins](#)" (download link) by PlasticsEurope, Box 3, B-1160 Brussels, Tel. +32 (2) 676 17 32.

You can also download it with your smartphone using the QR code below.



Customer Service

Europe
Phone: 00 800 396 366 27
Fax: 00 800 396 366 39
Italy
Phone: 800 7 910 18
Fax: 800 7 810 19
USA
Phone: +1 800 810 8499
Fax: +1 800 635 8061

Technical Service Fluoroplastics

Dyneon GmbH
3M Advanced Materials Division
Industrieparkstraße 1
84508 Burgkirchen
Germany
Phone: +49 8679 7 4709
Fax: +49 8679 7 5037

Technical Service Fluoroelastomers & Polymer Processing Additives

3M Belgium BVBA / SPRL
3M Advanced Materials Division
Canadastraat 11,
Haven 1005
2070 Zwijndrecht
Belgium
Phone: +32 3 250 7868
Fax: +32 3 250 7905

Technical Service PTFE Compounds

Dyneon B.V.
3M Advanced Materials Division
Tunnelweg 95
6468 EJ Kerkrade
The Netherlands
Phone: +31 45 567 9600
Fax: +31 45 567 9619

We will gladly supply further contact details for our full network of global sales offices. Alternatively, find them [here](#).

