



Super Fast Repair Adhesive - Black

04248

Technical Data Sheet

June 2017

3M Part No.(s)	3M Part Descriptor(s)
04248	3M™ Super Fast Repair Adhesive - Black

Product Description

3M™ Super Fast Repair Adhesive - Black is a two-part urethane formulated to be used on many substrates as a fast curing general purpose bonding adhesive with gap filling capabilities. 3M™ Super Fast Repair Adhesive - Black also functions for replacing worn or stripped threads, as well as for repairing and replacing broken or missing mounting tabs on plastic parts.

Features

- Two Part Urethane Technology
- 200 ml Dual - Syringe Cartridge
- Metered Static Mixing

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Container	200 ml Dual-Syringe cartridge	
Base	Urethane	
Density	Part A - 9.7 lbs/gal	Part B - 8.6 lbs/gal
Color	Clear	Black
Solids Content	100%	
Consistency	Liquid	
Service Temperature	-20° to 180°F	

Product Uses

A two-part urethane formulated to be used on most plastic substrates as a fast curing adhesive with excellent gap filling capabilities, works well to bond and repair mounting brackets on parts such as tail lamps, head lamps, mirrors, and other automotive exterior and interior trim parts. 3M™ Super Fast Repair Adhesive - Black may also be used on industrial and architectural surfaces needing minor repairs. For best results use in conjunction with **3M™ Polyolefin Adhesion Promoter (PN 05907) when repairing low surface energy type plastics.**

Note: Do not apply polyester body filler directly over this product.

Use with the following applicators: PN 08571 (manual), PN 08117 (manual), and PN 09930 (pneumatic).

3M™ Static Mixing Nozzle: PN 08193 (6/bag), PN 08194 (50/box).

For professional use only. Not intended for retail sale.

3M™ Super Fast Repair Adhesive - Black

04248

Performance Properties **The following times have been determined with ambient air temperature and substrate temperature @ 70°F (21°C) and are considered typical values.**

WORK TIME:

25 seconds

MIX NOZZLE DWELL TIME:

15 seconds

SAND TIME:

5 minutes

CLAMP TIME

1 hour

PAINT TIME:

30 minutes

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Lap Shear, TPO	240 PSI	ASTM D1002 / 2" per minute
Lap Shear, PP	340 PSI	ASTM D1002 / 2" per minute
Lap Shear, TEO	230 PSI	ASTM D1002 / 2" per minute

Overlap shear test method: Over lap shear test for adhesion determined in accordance with ASTM D1002. Substrate dimensions 1" x 4" x .12" with an overlap area of 1" x 1" and a bond thickness of 0.030". Plastics cleaned with 3M™ General Purpose Adhesive Cleaner PN 08984 and DA sanded with P80 abrasive. Thermopolyolefin and Polypropylene plastics coated with 3M™ Polyolefin Adhesion Promoter PN 05907.

Glass bead spacers - 30 mil were used.

Directions for Use

SURFACE PREPARATION:

1. Wash surface with soap and water to remove water soluble contaminants. Follow the soap and water wash with an appropriate VOC compliant product for removal of surface contaminants.
2. Sand the surface with a grade 80 or 180 abrasive.
3. Remove dust from surface using clean, un-oiled compressed air and a clean, dry rag.
4. **Apply 3M™ Polyolefin Adhesion Promoter (PN 05907) following label directions.**

3M™ Super Fast Repair Adhesive - Black

04248

Directions for Use (continued)

PRODUCT PREPARATION:

1. Insert cartridge into applicator gun.
2. Remove retaining collar and plug from end of cartridge. Discard plug, save retaining collar.
3. Extrude a small amount of product until both parts A and B dispense equally.
NOTE: Parts A and B of this product are very runny prior to mixing. It is recommended that you extrude the material with the dispensing end of the cartridge facing upward, into a paper towel. Continue to hold the cartridge in this position until you have completed the next step (4).
4. Attach 3M™ Mixing Nozzle (PN 08193, 08194) to cartridge and lock in place with retaining collar.

CAUTION: *Before proceeding with next step have all parts accessible and ready for repair.*

5. Dispense a small amount of material and discard.

PRECAUTIONARY INFORMATION:

Before using this product, please reference Product Label and/or Material Safety Data Sheet for Health and Safety Information.

GENERAL REPAIR PROCESS:

1. Apply adhesive to one of the parts and assemble the parts **immediately**.
2. Hold parts together for 30 to 45 seconds.

NOTE: Allow to cure 1 hour before putting repaired part into service.

APPLICATION WARNINGS:

Do not apply polyester fillers or putties over this product.

CLEANUP:

Unmixed material may be cleaned from most surfaces with an appropriate VOC compliant product.

Applications

General bonding repairs of many plastic substrates also for use on metal and other architectural substrates as a bonder. For best results use in conjunction with 3M™ Polyolefin Adhesion Promoter (PN 05907) when repairing low surface energy type plastics.

Storage and Handling

HANDLING

Avoid breathing of dust created by cutting, sanding, grinding or machining. Do not breathe vapors. Avoid prolonged or repeated skin contact. Do not eat, drink or smoke when using this product. Wash exposed areas thoroughly with soap and water.

STORAGE

When stored at the recommended conditions in original, unopened containers, this product has a shelf life of 12 months from the date of manufacture. Store away from acids. Keep container in well-ventilated area.

After use, leave mix nozzle in place to seal the cartridge.

3M™ Super Fast Repair Adhesive - Black

04248

Precautionary Information

Before using this product, please reference Product Label and/or Safety Data Sheet for Health and Safety Information. Note: Laws controlling the acceptable amounts of Volatile Organic Compounds (VOC's) vary by state, and in some cases by locality. For surface preparation and clean-up activities, consult federal, state and local regulations regarding use of products containing VOCs in your area.

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



Automotive Aftermarket Division

3M Center, Building 223-6N-01
St. Paul, MN 55144-1000
1-877-666-2277 (1-877-MMM-CARS)
www.3MCollision.com

3M is a trademark of 3M Company.
Printed in U.S.A.
©3M 2017. All rights reserved.
(7/17)

This is the last page