

## 3M™ Dyneon™ PTFE Powder TF 1702

### Product Description

Non-free-flowing suspension PTFE compression moulding powder developed especially for thin skived film applications.

### Special Features

- Meets ASTM D 4894 Type II classification
- Produced by suspension polymerisation
- Very fine particle size
- Low moulding pressure
- Dense polymer structure
- Lower deformation under load
- Increased gel stability
- Improved weldability
- Good electrical and mechanical properties
- Lower permeation rate compared to TF 1750
- Excellent chemical inertness
- Low friction behaviour
- Good flame retardance
- Exceptional temperature resistance

Properties	Test method	Unit	Value*
Bulk Density	DIN EN ISO 60	g/l	410
Average Particle Size	ISO 13320	µm	27
Powder Flow Properties			Non-free-flowing
Tensile Strength, 0.1 mm film	DIN EN ISO 527-3	MPa	42
Elongation at Break, 0.1 mm film	DIN EN ISO 527-3	%	590
Specific Gravity	DIN EN ISO 12086	g/cm <sup>3</sup>	2.16
Shrinkage, Cylinder 45 mm diameter	Internal Dyneon method	%	5.2
Dielectric Strength, 0.1 mm film	DIN EN ISO 12086	kV/mm	90

\* typical values

## 3M™ Dyneon™ PTFE Powder TF 1702

### Typical Properties

PTFE moulding powder with very small particle size is preferred for moulded parts requiring a dense polymer structure supporting its low permeation performance. Furthermore TF 1702 shows a lower deformation under load, good electrical and mechanical properties and an improved weldability. During processing it requires only a relatively low moulding pressure.

### Typical Applications

3M™ Dyneon™ PTFE Powder TF 1702 is a non-free-flowing compression moulding powder for applications like skived films, sheets and gaskets.

### Processing Recommendations

3M™ Dyneon™ PTFE Powder TF 1702 can be processed by compression moulding and in the next step by sintering of the moulded part. This type of product is used to fill moulds manually, because particle size is relatively small. It does not flow properly and cannot be fed sufficiently e.g. in automatic moulding technologies. To achieve optimum properties, compression moulding should be carried out within a temperature range of 23 °C to 26 °C at a recommended pressure of 15 MPa.

The necessary pressure holding time varies with the size of moulded part. Lower moulding pressures usually result in inferior physical properties. For the following sintering process step a programmable oven is a prerequisite for good physical properties of the moulded part. In this sintering cycle the temperature is raised slowly from room temperature up to 375 °C and then cooled down at a certain rate. Sintering time, interim holding steps at lower temperature levels and cooling rate depend on the dimension of the compressed mould and determine the quality of the finished product.

### Storage and Handling

3M™ Dyneon™ PTFE Powder TF 1702 can be stored for a relatively long period of time. It should preferably be stored in a clean, dry place at a temperature of less than 30 °C. Before processing, it is advisable to store the material in a sealed container for 24 hours in the production area. This is particularly important when ambient temperature is low; in such cases the material should be conditioned for up to 72 hours in the production area. If transport or storage temperatures are too high the material may agglomerate in its container. In such cases, it is advisable to store the material for 48 hours at below 23 °C and then sieve it (mesh size 4 mm) before filling the mould.

### Safety Instructions

Follow the normal precautions observed with all fluoropolymer materials.

Please consult the Material Safety Data Sheet and Product Label for information regarding the safe handling of the material. By following all precautions and safety measures, processing these products poses no known health risks. General handling/processing precautions include: 1) Process only in well-ventilated areas. 2) Do not smoke in areas contaminated with powder/residue from these products. 3) Avoid eye contact. 4) If skin comes into contact with these products during handling, wash with soap and water afterwards. 5) Avoid contact with hot fluoropolymer.

Potential hazards, including release of toxic vapours, can arise if processing occurs under excessively high temperature conditions. Vapour extractor units should be installed above processing equipment. When cleaning processing equipment, do not burn off any of this product with a naked flame or in a furnace.

### Delivery Form

3M™ Dyneon™ PTFE Powder TF 1702 is delivered in powder form.

Packaging size is:

- 25 kg plastic drum

## 3M™ Dyneon™ PTFE Powder TF 1702

### Important Notice

All information set forth herein is based on our present state of knowledge and is intended to provide general notes regarding products and their uses. It should not therefore be construed as a guarantee of specific properties of the products described or their suitability for a particular application. Because conditions of product use are outside Dyneon's control and vary widely, user must evaluate and determine whether a Dyneon product will be suitable for user's intended application before using it.

The quality of our products is warranted under our General Terms and Conditions of Sale as now are or hereafter may be in force.

Technical information, test data, and advice provided by Dyneon personnel are based on information and tests we believe are reliable and are intended for persons with knowledge and technical skills sufficient to analyze test types and conditions, and to handle and use raw polymers and related compounding ingredients.

No license under any Dyneon or third party intellectual rights is granted or implied by virtue of this information.

General recommendations on health and safety in processing, on work hygiene and on measures to be taken in the event of accident are detailed in our material safety data sheets.

You will find further notes on the safe handling of fluoropolymers in the brochure "[Guide for the safe handling of Fluoropolymers Resins](#)" (download link) by PlasticsEurope, Box 3, B-1160 Brussels, Tel. +32 (2) 676 17 32.

You can also download it with your smartphone using the QR code below.



#### Customer Service

Europe  
Phone: 00 800 396 366 27  
Fax: 00 800 396 366 39  
Italy  
Phone: 800 7 910 18  
Fax: 800 7 810 19  
USA  
Phone: +1 800 810 8499  
Fax: +1 800 635 8061

#### Technical Service Fluoroplastics

Dyneon GmbH  
3M Advanced Materials Division  
Industrieparkstraße 1  
84508 Burgkirchen  
Germany  
Phone: +49 8679 7 4709  
Fax: +49 8679 7 5037

#### Technical Service Fluoroelastomers & Polymer Processing Additives

3M Belgium N.V.  
3M Advanced Materials Division  
Canadastraat 11  
Haven 1005  
2070 Zwijndrecht  
Belgium  
Phone: +32 3 250 7868  
Fax: +32 3 250 7905

#### Technical Service PTFE Compounds

Dyneon B.V.  
3M Advanced Materials Division  
Tunnelweg 95  
6468 EJ Kerkrade  
The Netherlands  
Phone: +31 45 567 9600  
Fax: +31 45 567 9619

We will gladly supply further contact details for our full network of global sales offices. Alternatively, find them [here](#).



Web Site: [www.dyneon.eu](http://www.dyneon.eu)

Printed in Germany  
© Dyneon 2013  
Status: Jul. 2013

3M, Dyneon and Dynamar are Trademarks of 3M Company.  
All Rights reserved. The present edition replaces all previous versions. Its content is being continuously adjusted to reflect the current level of knowledge. Please make sure and inquire if in doubt whether you have the latest edition.