



# Extreme Sealing Tape 4411G

## Product Data Sheet

September 2012  
Supersedes: New

### Product Description

3M™ Extreme Sealing Tape 4411G is a single coated, pressure sensitive adhesive (very conformable multipurpose acrylic) tape designed for difficult sealing applications. The backing on this tape is an ionomer film (acrylic and ethylene copolymer) that is very tough yet flexible and abrasion resistant. The very soft and thick acrylic adhesive has excellent sealing properties and good long term, outdoor durability. This single coated tape is designed to seal over an existing joint, seam, or penetration. The adhesive is designed to adhere well to the ionomer film so that overlap layers of this tape can be used and still provide a tight seam to itself and the joint or seam to be sealed.

### Physical Properties

<b>Thickness</b> (ASTM D-3652) Adhesive Ionomer Backing Total	0,90 mm 0,10 mm 1,00 mm
<b>Density</b>	820 kg/m <sup>3</sup>
<b>Release Liner</b>	0,08 mm, matte finish, translucent, polyester film
<b>Tape Colour</b>	Translucent grey

### Performance Characteristics

<b>Peel Adhesion</b> (acc. to AFERA 5001 F) Stainless steel, 90° peel, 23°C, 72h dwell, jaw speed 300mm/min, with Al peel strip and 9460 backing	14,2 N/cm
<b>Tensile</b> (acc. to AFERA 5004 A) 12mm x 100mm, jaw speed 300mm/min.	19,7 N/cm
<b>Tensile Elongation</b> (acc. to AFERA 5004 A) 12mm x 100mm, jaw speed 300mm/min.	554,7 %
<b>Temperature Performance</b> Max (hours/minutes) Max Continuous (days / weeks)	150 °C 90 °C

## Application Guidelines

Depending on the surfaces to be sealed, one of three basic surface preparations will be required:

- 1) Good cleaning with a 50:50 mixture of isopropyl alcohol and water to remove contaminants;
- 2) Fine abrading with e.g. a 180x grit or finer abrasive followed by good cleaning with a 50:50 mixture of isopropyl alcohol and water; or
- 3) Good cleaning with a 50:50 mixture of isopropyl alcohol and water followed by application of an adhesion promoter or primer.

Ideal tape application is accomplished when temperature is between 21 °C and 38 °C (70 °F and 100 °F) and the bond is allowed to dwell 24 hours. Tape application to surfaces at temperatures below 10 °C (50 °F) is generally not recommended. Once properly applied, low temperature holding is generally satisfactory. With the protective release liner still attached to the tape, apply tape by hand using light hand pressure. If applying the tape over a “step” or ridge, use a thin plastic tool to press the tape tightly into the corners of adjoining surfaces and around other irregularities. Using a soft roller, such as a medium nap paint roller, apply medium pressure to conform tape on contours, seam edges, rivets, or screw heads. Peel off the protective release liner. To optimize adherence and conformance to uneven surfaces, a final tape roll down should be done after the non-stretchy, release liner has been removed. As an extra measure of sealing insurance, a very small dab of 3M™ 4000UV Hybrid Adhesive Sealant Fast Cure should be used at the end of any cut length of 3M™ Extreme Sealing Tape 4412N where the tape is sealing over an irregular surface.

---

## Storage

Store in original cartons between 4 °C and 38 °C and 0 % to 90 % relative humidity. Optimum storage conditions are 21 °C and 50 % relative humidity.

---

## Shelf Life

When stored under proper conditions, product retains its performance and properties for 24 months from date of manufacture.  
The date of manufacture is listed as a run number beginning with the letter “K” and followed by a 5 digit Julian calendar code (YYDDD). The first two digits refer to the year of manufacture. The last three digits refer to the days after January 1, e.g.; run #K12273 would translate to a September 30, 2012 date of manufacture.

---

## For Additional Information

To request additional product information or to arrange for sales assistance, please see below for contact details.

---

## Important Notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application.

All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

---

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

---

3M is a trademark of the 3M Company.



### **3M Svenska AB Industri**

Bollstanäsvägen 3  
191 89 Sollentuna

Tel: 08-92 21 00

Fax: 08-92 22 88

E-post:

[kundservice@mmm.co](mailto:kundservice@mmm.co)

[m](http://www.3m.se/tejp)

[www.3m.se/tejp](http://www.3m.se/tejp)

### **3M a/s Industri**

Hannemanns Allé 53  
2300 København S

Tlf.: 43 48 01 00

Fax.: 43 20 15 65

E-mail:

[dkindustri@mmm.co](mailto:dkindustri@mmm.co)

[m](http://www.3mindustri.dk)

[www.3mindustri.dk](http://www.3mindustri.dk)

### **3M Norge AS Avd. Industri**

Hvamveien 6  
2013 Skjetten

Tel: 0 63 84

Fax: 63 84 17 88

E-post:

[Kundeservice@mmm.co](mailto:Kundeservice@mmm.co)

[m](http://www.3m.no/tape)

[www.3m.no/tape](http://www.3m.no/tape)

### **Suomen 3M Oy**

#### **Teollisuustuotteet**

PL 600

Keilaranta 6

02151 Espoo

Puh: 09-525 21

Fax: 09-525 2279

<http://www.3m.fi/teollisuus>

S