

# CoTran™ 9720 Backing

## 3M™ Polyethylene Monolayer Film


Effective: 01 Jul 2022

Supersedes all previous versions

### Features and Benefits:

- Translucent, Matte Finish both sides
- Corona Treated both sides
- Conformable
- DMF filed with FDA
- Printable
- Controlled Caliper
- Can be Laminated to Adhesives
- Heat sealable

### Composition: Film is 3 mils [76.2 um] target thickness.

<b>PE Layer</b>		3 mils [76.2 um] Polyethylene, matte finish
-----------------	---	---

Please note - The following technical information should be considered representative or typical only and should not be used for specification purposes.

### Typical Properties:

<b>Tensile at break minimum</b>	<b>MD</b>	5 lbs./inch (2250 g/25 mm)
<b>Elongation at break, % minimum</b>	<b>MD</b>	250%
<b>Moisture Transmission Rate, MVTR</b>		6.0 g/m <sup>2</sup> /24 hrs.
<b>Oxygen Transmission Rate, OTR</b>		3840 cc/m <sup>2</sup> /24 hrs.

### Roll Description: Supplied on 3-inch (76 mm) diameter cores. (6 inch available)

<b>Length, Maximum</b>	2000 yards (1829 meters)
<b>Width, Maximum Usable</b>	48 inches (122 cm)
<b>Single Roll</b>	48 inches (122 cm)

### Rollstock Shelf Life and Recommended Storage:

Product as supplied by 3M in original packaging will maintain stated properties for a period of two (2) years from date of manufacture when stored at temperatures below 86F (30C) and relative humidity less than 75 percent in roll formation.

Please see next page for important product, safety, and warranty information.

**Product and Safety Information:** User is solely responsible for determining the suitability of 3M samples and products for the intended use including any necessary safety or toxicity assessment. 3M will provide a summary of biocompatibility testing upon request. In every case, before using any product in full scale production users should conduct their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purposes under their own operating conditions.

**Notice:** Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendations to practice any invention covered by any patent, without authority from the owners of this patent.

### **Warranty Information**

All statements, technical information and recommendations herein are based on tests 3M believes to be reliable, but the accuracy or completeness thereof is not guaranteed. 3M warrants only that products will meet 3M's specifications at the time of shipment to the customer. 3M does not offer any other warranty and does not warrant the performance, safety or such other characteristics of Products in combination with other materials. 3M specifically DOES NOT warrant Products for any intended or unintended uses (whether or not foreseeable); for compatibility or suitability with other components or compatibility with any methods of manufacture or conversion. The foregoing warranty is made in lieu of all other warranties, expressed or implied, including the implied warranties of merchantability, fitness for a particular purpose and freedom from non-infringement.

**Limitation of Remedies:** If products are proven not to meet 3M's specifications, the sole and exclusive remedy available and 3M's only obligation shall be, at 3M's option, to replace such quantity of Products which are proven out of specification or to refund the purchase price paid for Products.

**Limitations of Liabilities:** The remedies provided herein are exclusive remedies against 3M for any alleged or actual nonconformance to specifications or defect or other failure in products or for 3M's performance of its supply obligations. Under no circumstances is 3M liable for any direct, indirect, incidental, special or consequential damages (including lost profits) in any way related to the product under any theory of law including, but not limited to, negligence and strict liability.

### **Ordering Information**

Call us at Customer Service to place an order: 800-742-1994 (U.S.). Visit our website:

**[www.3M.com/MedTech](http://www.3M.com/MedTech)** for product and services information, news about conferences we will be attending, new product highlights or to make a direct inquiry.

To have a sales representative contact you, to request samples or clinical and safety summaries, please contact us at 3M HELPLINE 800-228-3957 (U.S.) or for international inquiries, please contact your local country representative.



#### **3M Medical Materials & Technologies**

3M Center, Building 275-5W-05  
St. Paul, MN 55144-1000 USA

Tel.: +1-800-228-3957  
Web: [www.3M.com/MedTech](http://www.3M.com/MedTech)

Please recycle. Printed in USA  
Scotchpak™ and CoTran™ are  
trademarks of 3M.  
© 3M 2021. All rights reserved.  
December 2021