

3M Scotchpak™ 9723 Backing


Polyester Film Laminate

A flexible laminate of pigmented polyethylene and polyester with excellent occlusive and barrier properties. The 3M proprietary lamination process does not use solvents or adhesives, minimizing potential for drug and/or excipient interactions.

Characteristics:

- Tan
- Occlusive
- Conformable
- Printable
- Matte finish
- Non-corona treated
- Can be laminated directly to adhesives


Properties	Nominal Value (U.S.)	Nominal Value (Metric)
Caliper	1.7 mils	43.2 µm
Tensile		
MD	15 lbs/in	66.7 N/25.4 mm
CD	20 lbs/in	89 N/25.4 mm
Elongation		
MD		75%
CD		50%
MVTR (g/m²/24 hr)		10
Oxygen transmission (cc/m²/24 hr)		100
Length		
Maximum	1500 yds on 3 in I.D. cores	1372 m on 76 mm I.D. cores
Approximate roll diameters	1500 yds – 11.5 in	1372 m – 30 cm
Width		
Maximum single roll width	40 in	101.6 cm
Maximum useable width	50 in	127.0 cm
Sample roll	6 in X 25 yds	15 cm X 23 m



1.1 mil Polyethylene and Pigmented Polyethylene
0.56 mil Polyester



3M Drug Delivery Systems
Enabling your success
www.3M.com/DDS



Scan the code
or visit www.3M.com/DDS
for more information.

Drug Delivery Systems
3M Center
Building 275-03-E-10
St. Paul, MN
55144-1000 USA
(1) 800-643-8086
Fax (1) 651 737-5265

Drug Delivery Systems
3M House,
Morley Street
Loughborough, Leicestershire
LE11 1EP England
(44) 1509 613626
Fax (44) 1509 613099

Drug Delivery Systems
3M Korea
19F, Hana Daetoo
Securities Bldg.
27-3 | Yoido
Yeongdeungpo-gu
Seoul 150-705 Korea
(82) 80 033 4114

Drug Delivery Systems
3M Japan
6-7-29, Kita-Shinagawa
Shinagawa-ku, Tokyo
141-8684 Japan
(81) 3 6409 3553
Fax (81) 3 6409 5805

3M is a trademark of
3M Company.

Scotchpak™ and CoTran™ are
trademarks of 3M Company.
©3M 2014.

All Rights Reserved.